

PPG FLOORING 912 LV Epoxy Primer

Formerly known as Milamar ICO Primer LV

DESCRIPTION

100% solids, low viscosity penetrating epoxy primer/sealer that can be applied to dry or partially damp surfaces

PRINCIPAL CHARACTERISTICS

- 100% solids
- Low viscosity
- Low odor
- Seals concrete surfaces, helping to eliminate outgassing
- Bonds to concrete, masonry, metal and wood
- Roller, squeegee or brush application
- Helps reduce the effects of moisture vapor transmissions
- Provides a Class 1 Vapor Barrier at 20 mils
- A high relative humidity (maximum 100%) of concrete substrate during application and curing does not influence the quality of the coating
- TYPICAL USES:
- Self-priming floor toppings and coatings
- Penetrating primer/sealer for concrete walls and floors

COLOR AND GLOSS LEVEL

- Clear, Light Gray, Medium Gray, Black, Safety Red

BASIC DATA AT 70°F (21°C)

Data for mixed product	
Number of components	Two
Mass density	9.0 lb/US gal (1.1 kg/l)
Volume solids	100 ± 2%
VOC (Supplied)	EPA Method 24: 0.3 lb/US gal (40.0 g/L)
Recommended dry film thickness	6.0 - 20.0 mils (152 - 508 µm) per coat
Theoretical spreading rate	256 ft ² /US gal for 6.0 mils (6.2 m ² /l for 152 µm) 80 ft ² /US gal for 20.0 mils (2.0 m ² /l for 508 µm)
Dry to touch	6 hours
Overcoating Interval	Minimum: Coating should no longer leave residue when touched with a gloved finger Maximum: 24 hours
Curing time	9 hours
Full cure after	7 days
Shelf life	Part A: at least 12 months when stored cool and dry Part B: at least 12 months when stored cool and dry

Notes:

PPG FLOORING 912 LV Epoxy Primer

Formerly known as Milamar ICO Primer LV

- Curing time reflects ready for service time
- Full cure after reflects maximum hardness and chemical resistance at 77°F (25°C)
- Material should be stored in dry conditions, out of direct sunlight, and in unopened original factory containers.
- See ADDITIONAL DATA - Drying time

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Concrete

- Surface must be clean, uniform, sound, and free from contamination (such as oil, grease, rust, scale, or deposits)
- Prepare the surface in accordance with SSPC SP-13 standards
- Concrete pH must be between 7.0 and 14.0
- New concrete must cure a minimum of 28 days prior to application of this product
- Surface condition should be Saturated Surface Dry (SSD) or dryer
- Can be applied to concrete slabs with a 100% relative humidity when relative humidity for concrete substrate is conducted according to ASTM F2170 specifications.

Other Substrates

- Check with PPG PMC Technical Service for preparation instructions for substrates other than concrete.

SYSTEM SPECIFICATION

- Helps block vapor transmissions at the following DFTs, per ASTM F1869:
- At one coat of 6 mil (152 µm): 5 lb/1000 ft²/24 hr (204 g/1000 m²/24 hr)
- At one coat of 10 mil (254 µm): 10 lb/1000 ft²/24 hr (408 g/1000 m²/24 hr)
- At one coat of 20 mil (508 µm): 20 lb/1000 ft²/24 hr (816 g/1000 m²/24 hr)
- Provides an E96 Class 1 Vapor Barrier at 20 mils

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 2.05:1

- Before mixing, ensure that the surface is completely prepared and ready and that all tools and equipment are handy
- Mix components according to the prescribed ratio
- Mix Part A and Part B together using a low speed Jiffy-type mixer for 2 minutes
- Do not add solvents; product is a 100% solids epoxy

Note:

- CAUTION: Product reacts quickly; pour all contents out of container and spread with squeegee immediately after mixing, especially at temperatures greater than 70°F (21°C)

PPG FLOORING 912 LV Epoxy Primer

Formerly known as Milamar ICO Primer LV

Application

- Pour the mixture onto the floor in a continuous ribbon and spread with a squeegee
- Completely empty mixed material from pail onto the floor before moving on to the next step
- Be sure to work the primer into any porous surfaces
- Back roll with 3/8" (9.5 mm) nap roller
- Re-prime any dry appearing areas
- Must be tack-free before overcoating
- Re-priming may be necessary if pinholes or porous spots appear

Note:

- Working time varies with temperature.

Pot life

45 minutes at 70°F (21°C)

Notes:

- The pot life will vary substantially with temperature
- See ADDITIONAL DATA – Pot life

Brush/roller

- Apply mixed material with squeegee, brush or roller
- Apply at approximately 200-250 ft²/gal (4.9-6.1 m²/l), depending on surface porosity
- Re-prime any areas that appear dry

Recommended thinner

No thinner should be added

ADDITIONAL DATA

Working Time

- 120 minutes at 50°F (10°C)
- 90 minutes at 70°F (21°C)
- 45 minutes at 90°F (32°C)

Physical data of cured material	
Characteristic	Value
Adhesion to Concrete (ASTM D4541)	>400 psi (>2.8 MPa); 100% concrete failure
Adhesion to Concrete (ASTM D7234)	10 mil: 539 psi (3.7 MPa); 100% concrete failure
Adhesion to Concrete (ASTM D7234)	20 mil: 759 psi (5.2 MPa); 100% concrete failure

PPG FLOORING 912 LV Epoxy Primer

Formerly known as Milamar ICO Primer LV

Drying time		
Substrate temperature	Dry to touch	Dry to service
50°F (10°C)	17 hours	30 hours
70°F (21°C)	6 hours	9 hours
90°F (32°C)	3 hours	4 hours

Notes:

- Maximum hardness achieved after 7 days @ 77°F (25°C)
- All drying times have been measured at a DFT of 10 mils (254 µm). Higher thicknesses will take longer to dry. Contact PPG Technical Services for drying times at higher thicknesses.

Pot life (at application viscosity)	
Mixed product temperature	Pot life
50°F (10°C)	60 minutes
70°F (21°C)	45 minutes
90°F (32°C)	15 minutes

Product Qualifications

- Compliant with USDA Incidental Food Contact Requirements

DISCLAIMER

- For industrial or professional use only
- This product is specifically suitable for use on the substrates mentioned in this document. For application on any other substrates, please always contact your distributor or PPG representative for specific instructions and in order to make sure that the product performance can be maintained.

SAFETY PRECAUTIONS

- Read all label and Safety Data Sheet (SDS) information prior to use

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

- Information sheet | Explanation of product data sheets

PPG FLOORING 912 LV Epoxy Primer

Formerly known as Milamar ICO Primer LV

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

AVAILABILITY OF PACKAGING

Packaging

- 1-gallon and 4-gallon kits

