

MEGASEAL™ CR

(also branded as AMERCOAT® 965)

DESCRIPTION

Acrylic modified cement concrete repair compound

PRINCIPAL CHARACTERISTICS

- Excellent for repairing deteriorated concrete
- Can be used as a masonry block filler
- Can be trowelled to a feather edge to re-pitch floors
- 0 VOC, LEED Compliant, HAPs Free
- 2,000 psi compressive strength
- Low odor during application
- Non-flammable

COLOR AND GLOSS LEVEL

- Gray
- Flat

BASIC DATA AT 68°F (20°C)

| Data for mixed product | |
|--------------------------------|--|
| Number of components | Two |
| Volume solids | 75 ± 5% |
| VOC (Supplied) | max. 0.0 lb/US gal (approx. 0 g/l) |
| Recommended dry film thickness | 125.0 - 500.0 mils (3125 - 12500 µm) depending on system |
| Theoretical spreading rate | 2 ft²/US gal for 500.0 mils (0.0 m²/l for 12500 µm) |
| Shelf life | Liquid: at least 12 months when stored cool and dry Powder: at least 12 months when stored cool and dry |

Notes:

- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time
- Final volume solids varies depending on mixing ratio. Film shrinkage is minimal

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- Surface must be free from grease, salts and any contamination
- Mechanical surface preparation should expose sub-surface voids and provide a surface profile equivalent to 60 grit sandpaper or coarser



MEGASEAL™ CR

(also branded as AMERCOAT® 965)

Masonry

- Clean surface in accordance with ASTM D 4261 requirements to remove any surface contaminants and loose particles
-

Substrate temperature and application conditions

- Surface temperature during application should be between 32°F (0°C) and 110°F (43°C)
 - The surface temperature must be at least 5°F (3°C) above dew point
 - Ambient temperature during application and curing should be between 35°F (2°C) and 110°F (43°C)
 - Relative humidity during application and curing should not exceed 85%.
-

INSTRUCTIONS FOR USE

- Mix with a pneumatic air mixing at moderate speeds to homogenize the container
 - During hot, dry conditions, the concrete may be pre-moistened with water to assist in application of the product directly to the concrete or masonry
 - Prime surface with AMERLOCK Sealer or Amercoat 965 Liquid. Apply Amercoat 965 when AMERLOCK Sealer is still wet or tacky. When using Amercoat 965 liquid to prime, apply the 965 cement within the same day and after the liquid is dry to touch.
 - AMERCOAT 965 is packaged in 2 components which must be mixed together before use. A kit consists of 8 lbs of liquid and 48 lbs of powder. Do not mix more material than can be used within the working time of 30 minutes. If necessary, mix smaller quantities at the ratio of 6 parts powder to 1 part liquid by weight. Material which has begun to set is unsatisfactory and must be discarded
 - Power mixing using a suitable 1/2 inch power drill and mixer is recommended. When mixing more than a unit of material at a time, a 3-6 ft³ revolving drum mixer or mortar mixer is recommended. The material can also be mixed by hand using a mortar box or wheel barrel using a mortar hoe.
 - Shake the 1 gallon polyethylene bottle of liquid to disperse any sediment. Pour the liquid into the mixing vessel. Gradually add powder and mix until the cement is uniformly blended to a workable consistency
 - If the cement is to be applied in thickness greater than 1/4 inch, a stiffer consistency can be achieved by adding additional powder. For application and thickness above 1 inch or for filling deep pitted concrete sections, add gravel to the mix. Add 36 lbs of 1/4 – 3/4 inch clean gravel to each 56 lb unit of material. Immediately after mixing, the AMERCOAT 965 cement is ready to use
 - Spread and trowel to the desired finish using typical concrete finishing tools
-

Application

- Area should be sheltered from airborne particulates and pollutants

Material temperature

Material temperature during application should be between 50°F (10°C) and 90°F (32°C)

Cleaning solvent

Tap water



MEGASEAL™ CR

(also branded as AMERCOAT® 965)

ADDITIONAL DATA

| Overcoating interval for DFT up to 500.0 mils (12700 µm) | | | | |
|--|----------|-------------|-------------|-------------|
| Overcoating with... | Interval | 50°F (10°C) | 70°F (21°C) | 90°F (32°C) |
| thin film epoxies | Minimum | 12 hours | 6 hours | 4 hours |
| | Maximum | Unlimited | Unlimited | Unlimited |
| Amercoat epoxy surfacers | Minimum | 6 days | 3 days | 48 hours |
| | Maximum | Unlimited | Unlimited | Unlimited |

Note: For slabs on grade, ensure the floor has been tested for moisture content and transmission in accordance with the allowable levels for the epoxy coating or surface used

| Curing time for DFT up to 500.0 mils (12700 µm) | |
|---|--------------------|
| Substrate temperature | Light traffic |
| 50°F (10°C) | 24 hours |
| 70°F (21°C) | 8 hours - 12 hours |
| 90°F (32°C) | 6 hours - 8 hours |

SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

| | | |
|--|-------------------|------|
| • CONVERSION TABLES | INFORMATION SHEET | 1410 |
| • EXPLANATION TO PRODUCT DATA SHEETS | INFORMATION SHEET | 1411 |
| • SAFETY INDICATIONS | INFORMATION SHEET | 1430 |
| • SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD | INFORMATION SHEET | 1431 |

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.



MEGASEAL™ CR

(also branded as AMERCOAT® 965)

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

| Product code | Description |
|--------------|-------------|
| 99-96510 | Liquid |
| 99-96555 | Powder |

Note: Packaging: liquid, 8 lbs. in a 1-gallon polyethylene bottle and powder, 48 lbs. in a fiber drum

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

