

# PPG SIGMACOVER™ 350

## DESCRIPTION

Two-component, high-build polyamide cured epoxy primer/coating based upon pure epoxy technology

## PRINCIPAL CHARACTERISTICS

- Surface tolerant primer/coating for wide use in Marine and Protective Coatings
- Marine use: suitable on topsides, decks, superstructures and cargo holds
- Excellent corrosion resistance
- Compatible with various aged coatings
- Suitable as floor coating for pedestrian traffic with dry to walk on time of 6 hours at 20°C (68°F)
- Good impact and abrasion resistance
- Smooth film, easy to clean
- Resistant to splash and spillage of a wide range of chemicals

## COLOR AND GLOSS LEVEL

- Standard and custom colors, including aluminum
- For Cargo holds gray ( 5177 ) and redbrown ( 6179 ) only
- Semi-gloss

Notes:

- Epoxy coatings will chalk and fade upon exposure to sunlight, elevated temperatures, or chemical exposure. Discoloration and normal chalking do not impact performance. Light colors will darken over time. Some batch-to-batch variation in color is to be expected. Color matches are approximate.
- The addition of a UV stable topcoat should be considered when using epoxy coatings in cosmetic areas

## BASIC DATA AT 20°C (68°F)

Data for mixed product	
<b>Number of components</b>	Two
<b>Mass density</b>	1.4 kg/l (11.7 lb/US gal)
<b>Volume solids</b>	72 ± 2%
<b>VOC (Supplied)</b>	Directive 2010/75/EU, SED: max. 263.0 g/kg max. 361.0 g/l (approx. 3.0 lb/US gal)
<b>Recommended dry film thickness</b>	100 - 150 µm (4.0 - 6.0 mils) for airless spray
<b>Theoretical spreading rate</b>	5.8 m <sup>2</sup> /l for 125 µm (231 ft <sup>2</sup> /US gal for 5.0 mils) 4.8 m <sup>2</sup> /l for 150 µm (192 ft <sup>2</sup> /US gal for 6.0 mils)
<b>Dry to touch</b>	2 hours
<b>Overcoating Interval</b>	Minimum: 6 hours
<b>Full cure after</b>	7 days
<b>Shelf life</b>	Base: at least 24 months when stored cool and dry Hardener: at least 24 months when stored cool and dry



# PPG SIGMACOVER™ 350

## Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time

---

## RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

### Substrate conditions

- Steel; blast cleaned to ISO-Sa2½ for excellent corrosion protection, blasting profile 40 – 70 µm (1.6 – 2.8 mils)
- Steel; blast cleaned to ISO-Sa2, blasting profile 40 – 70 µm (1.6 – 2.8 mils) or power tool cleaned to minimum ISO-St2 for good corrosion protection
- Coated steel; hydrojetted to VIS WJ2/3L
- Surface must be dry and free from any contamination
- Existing sound epoxy systems and most sound alkyd coating system; sufficiently roughened

---

### Substrate conditions of concrete for thinned version

- Dried for at least 28 days in good ventilation conditions
- Moisture content should not exceed 4.5%
- Concrete must be sound, dry, free from laitance and any contamination
- Rough surface; eventually abraded by power tool or diamond abrading tool

---

### Coated concrete

- Existing sound coating systems; sufficiently roughened, dry and cleaned
- To ensure compatibility, rub the existing coating with a cloth with Xylene or MEK for 10 seconds, and remove existing coatings if dissolving occurs
- Rough surface; eventually abraded by power tool or diamond abrading tool

---

### Substrate temperature and application conditions

- Substrate temperature during application and curing should be above 5°C (41°F)
- Substrate temperature during application and curing should be at least 3°C (5°F) above dew point

---

## SYSTEM SPECIFICATION

- SIGMACOVER 350: 2 x 125 µm (5.0 mils) DFT
-

# PPG SIGMACOVER™ 350

## INSTRUCTIONS FOR USE

### **Mixing ratio by volume: base to hardener 4:1**

- The temperature of the mixed base and hardener should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
  - Adding too much thinner results in reduced sag resistance
  - Thinner should be added after mixing the components
- 

### **Pot life**

3 hours at 20°C (68°F)

Note:

- See ADDITIONAL DATA – Pot life
- 

### **Air spray**

#### **Recommended thinner**

THINNER 91-92

#### **Volume of thinner**

5 - 10%, depending on required thickness and application conditions

#### **Nozzle orifice**

1.8 - 2.0 mm (approx. 0.070 - 0.079 in)

#### **Nozzle pressure**

0.3 - 0.4 MPa (approx. 3 - 4 bar; 44 - 58 p.s.i.)

---

### **Airless spray**

#### **Recommended thinner**

THINNER 91-92

#### **Volume of thinner**

0 - 5%, depending on required thickness and application conditions

#### **Nozzle orifice**

Approx. 0.48 - 0.53 mm (0.019 - 0.021 in)

#### **Nozzle pressure**

15.0 MPa (approx. 150 bar; 2176 p.s.i.)

---

# PPG SIGMACOVER™ 350

## Brush/roller

### Recommended thinner

THINNER 91-92

### Volume of thinner

0 – 5%

Note:

- 10 - 15% when applied as a primer direct to concrete

## Cleaning solvent

- THINNER 90-53

## ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
100 µm (4.0 mils)	7.2 m <sup>2</sup> /l (289 ft <sup>2</sup> /US gal)
125 µm (5.0 mils)	5.8 m <sup>2</sup> /l (231 ft <sup>2</sup> /US gal)
150 µm (6.0 mils)	4.8 m <sup>2</sup> /l (192 ft <sup>2</sup> /US gal)

Note:

- Maximum DFT when brushing: 100 µm (4.0 mils)

Overcoating interval for DFT up to 150 µm (6.0 mils) - For application in cargo holds, on decks and marine areas subject to non-permanent splash and spillage of seawater and/or chemicals						
Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself and various two-pack epoxy coatings	Minimum	16 hours	9 hours	6 hours	4 hours	3 hours
	Maximum	1 month	1 month	21 days	14 days	7 days
polyurethanes	Minimum	48 hours	30 hours	18 hours	9 hours	5 hours
	Maximum	1 month	21 days	14 days	7 days	3 days



# PPG SIGMACOVER™ 350

Overcoating interval for DFT up to 150 µm (6.0 mils) - For application in atmospheric exposure and industrial PC						
Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself and various two-pack epoxy coatings	Minimum	16 hours	9 hours	6 hours	4 hours	3 hours
	Maximum	Extended	Extended	Extended	Extended	Extended
polyurethanes	Minimum	48 hours	10 hours	18 hours	9 hours	5 hours
	Maximum	6 months	5 months	2.5 months	1.5 months	14 days
various single pack coatings (such as alkyds and acrylics)	Minimum	24 hours	24 hours	16 hours	8 hours	5 hours
	Maximum	14 days	14 days	14 days	7 days	4 days

Notes:

- Actual maximum overcoating times will be influenced by local conditions
- A detergent wash with PREP 88 or equivalent is recommended prior to application of topcoats after 30 days of exposure if chalking or contamination is present
- To ensure optimal adhesion of the next coat, the surface must be dry and free from all contaminations (oil, grease, chalking, etc...) which would require cleaning and/or abrading

Curing time for DFT up to 150 µm (6.0 mils)			
Substrate temperature	Dry to touch	Dry to handle	Full cure
5°C (41°F)	12 hours	16 hours	25 days
10°C (50°F)	6 hours	9 hours	15 days
20°C (68°F)	2 hours	6 hours	7 days
30°C (86°F)	1 hour	4 hours	4 days
40°C (104°F)	1 hour	3 hours	48 hours

Notes:

- Adequate ventilation must be maintained during application and curing
- Should SIGMACOVER 350 or the total coating system (2 x 125 µm/2 x 5.0 mils) be applied in excess of the specified dry film thickness, then the time necessary to reach full cure will be increased
- For cargo hold application: for full cure for hard angular cargoes, please contact your nearest PPG Protective & Marine Coatings sales office



# PPG SIGMACOVER™ 350

Pot life (at application viscosity)	
Mixed product temperature	Pot life
15°C (59°F)	4 hours
20°C (68°F)	3 hours
30°C (86°F)	2 hours
40°C (104°F)	1 hour

## SAFETY PRECAUTIONS

- See Safety Data Sheet and product label for complete safety and precaution requirements
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

## WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

## REFERENCES

- Guide | PPG SIGMACARE PLUS | Online guide to maintenance at sea
- Information sheet | Explanation of product data sheets

## WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

## LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at [www.ppgmc.com](http://www.ppgmc.com). The English text of this sheet shall prevail over any translation thereof.

