

**PRIZMATIQUE®**

# DX78

DX78 PRIZMATIQUE® special effect pigment is part of the VIBRANCE COLLECTION® custom paint finish line and contains special multicolored flakes that create a finish that glitters and sparkles with a rainbow of color.

*Prizmatique* custom colors can be added to color blenders, midcoats, and RADIANCE® II dyes and used as a Midcoat/pearlcoat effect.

For procedures relating to custom and/or restoration work refer to PPG's Custom Restoration Guide available at [ppgrefinish.com](http://ppgrefinish.com) under Training.



## Compatible Products and Systems

*Prizmatique* flake is used in conjunction with the systems shown below:

- DELTRON® DBC 2000 Refinish System - Follow P-175 *Deltron* DBC recommendation for proper preparation and compatible primers.
- DELTRON® NXT Refinish System - Follow P-251 *Deltron* NXT recommendation for proper preparation and compatible primers.
- ENVIROBASE® High Performance Refinish System - Follow EB-143 *Envirobase* High Performance recommendations for proper preparation and compatible primers.
- DBC500 Color Blender - Follow P-176 *Deltron* DBC500 recommendations for proper preparation and compatible primers..
- VWM5556 VIBRANCE COLLECTION® Waterborne Midcoat - Follow VB-15 recommendations for proper preparation and use.
- VWM500 *Vibrance Collection* Custom Midcoat - Follow VB-22 recommendations for proper preparation and use.

Note: Custom or exotic finishes are excluded from coverage under the PPG Paint Performance Guarantee.

## Directions for use

### Surface Preparation:



- When working on custom finishes close attention to the details outlined for standard basecoat preparation, sanding, and cleaning is needed to achieve the optimum results.
- *Prizmatique* colors are designed to be applied over properly cleaned, sanded, and primed surfaces.

**DX78**

**Mixing Ratio:**  
(adding DX78 to a basecoat color or blender)

For a custom formulation you may add a maximum of 10% (by weight) *Prizmatique* pigments to unreduced color or 5% (by weight) to ready-to-spray DBC, NXT, EHP, DBC500, VWM5556, or VWM500.

**Reducing:**  
(basecoat color or blender already containing DX78)



**Reduction of basecoat color or blender already containing DX78**

For detailed *Deltron* DBC 2000 reduction specifics see data sheet P-175\*\*

For detailed *Deltron* NXT reduction specifics see data sheet P-251\*\*

For detailed *Envirobase* High Performance EHP reduction specifics see data sheet EB-143

For detailed DBC500 reduction specifics see data sheet P176\*\*

For detailed VWM5556 reduction specifics see data sheet VB-15

For detailed VWM500 reduction specifics see data sheet VB-22

\*\*DX57 activator **must** be used in DBC or NXT colors containing *Prizmatique* special effects pigment. When using *Prizmatique* tri-coat custom colors, DX57 activator **must** be used in both the ground coat and midcoat colors.

Pot Life: See specific product data sheet listed above  
Using activated material beyond 1 hour may result in wrinkling or other product failures (especially on multiple colors).



**Additives:**



See specific product data sheet listed above

**Air Pressure And Gun Setup:**



**HVLP:** 8 - 10 psi at the air cap  
**Compliant:** 29 - 40 psi at the gun  
**Gun Setup:** 1.1 - 1.5 mm or equivalent

Refer to spraygun manufacturer's recommendations for inlet air pressures.

**Application:**



**Apply:** Sufficient number of coats to achieve desired effect. Spraying a test panel is recommended to determine desired effect.

**Drying Times**



**Between Coats:** See specific product data sheet listed above



**Air Dry:**  
**Tape Time:** See specific product data sheet listed above



**Dry to Clearcoat:** See specific product data sheet listed above  
24 hour maximum to clear coat

**Note:** Basecoat colors are designed to dry low in gloss. This makes color match and its approval difficult to see until the clearcoat is applied. **A good technique is to spray the basecoat and clearcoat on a small test panel before spraying the job.**

If the basecoat color is allowed to dry more than 24 hours, it must be scuffed and new basecoat color applied.

**DX78**

**Tri-coat Mixing:** When applying *Deltron* basecoat , 5% DX57 Basecoat Activator must be added to the reduced basecoat prior to spraying in **BOTH** the ground coat and mid-coat.

*Prizmatique* flakes can be blended as a mid-coat color with DBC500, VWM5556 Waterborne Midcoat, or VWM500 Custom Midcoat. In doing so you achieve more transparency, when combined with varying ground coat colors and create different degrees of custom effects.

**Striping or Two Toning**

**Tape Times:**

Tape time of DBC and NXT is 30 - 60 minutes at 70°F (21°C) and 50% relative humidity.  
Tape time of EHP and VWM5556 is 30 - 35 minutes at 70°F (21°C) and 50% relative humidity.  
Tape time of VWM500 is 45 - 60 minutes (additional coats may require longer dry time).

All striping, two toning must be completed within 24 hours. If allowed to dry for more than 24 hours, it must be sanded and reapplied.

When applying DBC or NXT basecoats, 5% DX57 Basecoat Activator **must** be added to the reduced basecoat prior to spraying in **BOTH** the ground coat and mid coat.

**Clearcoating:**

Due to the large particle size of *Prizmatique* pigment, you **must** apply 2.5 - 3.0 mils of clear (usually 3 - 4 coats) to cover the basecoat.

Clear with any *Vibrance Collection* clearcoat or any clearcoat recommended for *Deltron* DBC, NXT, or *Envirobase* High Performance.

**Equipment Cleaning:**

Spray guns, gun cups, storage pots, etc., should be cleaned thoroughly after each use with any appropriate PPG general purpose solvent.

Technical Data	<u>DBC</u>	<u>NXT</u>	<u>EHP</u>
Package VOC Actual	4.86 - 6.16 lbs./gal (582 - 738 g/L)	5.91 - 6.42 lbs./gal (708 - 769 g/L)	0.39 - 1.04 lbs./gal (47 - 125 g/L)
Package VOC Regulatory (Less water, less exempts)	4.86 - 6.16 lbs./gal (582 - 738 g/L)	5.91 - 6.42 lbs./gal (708 - 769 g/L)	1.70 - 3.30 lbs./gal (203 - 395 g/L)
RTS Volume Ratio	1:1 + 5%	1:1 + 5%	1:10 - 30%
RTS VOC Regulatory (Less water, less exempts)	5.49 - 6.20 lbs./gal (658 - 743 g/L)	5.91 - 6.42 lbs./gal (708 - 769 g/L)	1.77 - 3.50 lbs./gal (212 - 419 g/L)

	<u>DBC500</u>	<u>VWM500</u>	<u>VWM5556</u>
Package VOC Actual	5.20 - 5.62 lbs./gal (623 - 673 g/L)	1.52 - 1.55 lbs./gal (182 - 189 g/L)	0.37 - 0.49 lbs./gal (44 - 59 g/L)
Package VOC Regulatory (Less water, less exempts)	5.20 - 5.62 lbs./gal (623 - 673 g/L)	3.33 - 3.66 lbs./gal (400 - 439 g/L)	1.61 - 1.69 lbs./gal (193 - 203 g/L)
RTS Volume Ratio	1:1 + 5%	1:1 + 5%	4:1
RTS VOC Regulatory (Less water, less exempts)	5.87 - 6.49 lbs./gal (704 - 778 g/L)	5.50 - 5.88 lbs./gal (659 - 705 g/L)	2.03 - 2.30 lbs./gal (252 - 276 g/L)

For detailed DBC recommendations and VOC specifics see data sheet P-175  
For detailed NXT recommendations and VOC specifics see data sheet P-251  
For detailed EHP recommendations and VOC specifics see data sheet EB-143

For detailed DBC500 recommendations and VOC specifics see data sheet P176  
For detailed VWM5556 recommendations and VOC specifics see data sheet VB-15  
For detailed VWM500 recommendations and VOC specifics see data sheet VB-22

**See Safety Data Sheet and Labels for additional safety information and handling instructions.**



**Important:** The contents of this package must be blended with other components before the product can be used. Before opening the packages, be sure you understand the warning messages on the labels of all components since the mixture will have the hazards of all its parts. Improper spray technique may result in a hazardous condition. Follow spray equipment manufacturer's instructions to prevent personal injury or fire. Follow directions for respirator use. Wear eye and skin protection. Observe all applicable precautions.

**EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION (412) 434-4515; IN CANADA (514) 645-1320**


Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the public. Products mentioned may be hazardous and should only be used according to direction, while observing precautions and warning statements listed on label. Statements and methods described are based upon the best information and practices known to PPG Industries. Procedures for applications mentioned are suggestions only and are not to be construed as representations or warranties as to performance, results, or fitness for any intended use, nor does PPG Industries warrant freedom from patent infringement in the use of any formula or process set forth herein.

PPG Automotive Refinish  
19699 Progress Drive  
Strongsville, OH 44149  
800.647.6050

PPG Canada Inc.  
2301 Royal Windsor Drive, Unit #6  
Mississauga, Ontario L5J 1K5  
888.310.4762

Follow us online:  

[www.ppgrefinish.com](http://www.ppgrefinish.com)



The PPG Logo, *We protect and beautify the world*, *Prizmatique*, *Deltron*, *Radiance*, *Envirobase*, and *Vibrance Collection* are trademarks of PPG Industries Ohio, Inc.  
© 2025 PPG Industries, Inc. All rights reserved.