

PPG Flooring 980 Clear Epoxy Coating

Formerly known as Milamar PM100 Series Floor Coating

DESCRIPTION

Water clear, moisture insensitive multipurpose epoxy floor coating.

PRINCIPAL CHARACTERISTICS

- 100% solids
- Clear, low-ambering epoxy
- Available in multiple cure rates
- Versatile, can be used in multiple applications
- Excellent abrasion and impact resistance
- Very good chemical resistance
- Low odor
- Moisture tolerant epoxy
- TYPICAL USES:
- Clear finish for decorative and architectural applications
- Primer, mortar, or self-leveling coating in industrial and commercial applications

Notes:

- Information Sheet available with test and certification data
- This product was previously sold as Milamar PM100 Floor Coating

COLOR AND GLOSS LEVEL

- Clear
- High gloss

BASIC DATA AT 75°F (24°C)

Data for mixed product	
Number of components	Two
Volume solids	100 ± 2%
VOC (Supplied)	EPA Method 24: 0.1 lb/US gal (6.8 g/l)
Theoretical spreading rate	200 ft²/US gal for 8.0 mils (4.9 m²/l for 203 µm)
Dry to touch	10 hours
Overcoating Interval	Maximum: 24 hours Minimum: Coating should no longer leave residue when touched with a gloved finger
Curing time	36 hours
Dry to walk on	24 hours
Full cure after	7 days



PPG Flooring 980 Clear Epoxy Coating

Formerly known as Milamar PM100 Series Floor Coating

Data for mixed product

Shelf life

Base: at least 12 months
Hardener: at least 12 months

Notes:

- Curing time reflects ready for service time
- Material should be stored in dry conditions, out of direct sunlight, in unopened original factory containers, at temperatures above 50°F (10°C) and below 90°C (32°C)
- If overcoat time is exceeded, abrade and clean surface before recoating
- Listed data for mixed product using standard hardener.

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- Moisture vapor transmission should not exceed 5 lb/1000 ft² (24.4 g/m²) over 24 hours

Concrete

- Surface must be clean, uniform, sound, and free from contamination (such as oil, grease, rust, scale, or deposits)
- Dry concrete is preferred. Product may also be applied to concrete that is damp but not wet.
- New concrete must cure a minimum of 28 days prior to application of this product
- Prepare in accordance with SSPC SP-13 guidelines
- Ambient temperature should be at least 50°F (10°C) during application
- Ambient temperature should be at least 3°F (5°C) above dew point during application

SYSTEM SPECIFICATION

- Avoid applications where ambient operating temperatures exceed 170°F (77°C).

Chemical Resistance (Splash/Spill)

- Ammonium Hydroxide 28%
- Bleach
- Ethylene Glycol
- Gasoline
- Isopropyl Alcohol 98%
- Mineral Spirits
- Sulfuric Acid 45%
- Sodium Hydroxide 30%

Notes:

- Some discoloration may occur after prolonged contact with certain chemicals, though the coating integrity will remain intact.
- To maximize service life, chemical splash and spills should be cleaned promptly.
- A more complete list of chemical resistances is available by request from PPG PMC Technical Services.



PPG Flooring 980 Clear Epoxy Coating

Formerly known as Milamar PM100 Series Floor Coating

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 2:1

- Mix Part A and Part B together using a low speed Jiffy-type mixer for 2 minutes

Pot life

20 minutes at 75°F (24°C)

Note: Indicated pot life is for product with standard hardener

Application

- Pour entire mix onto floor in a continuous ribbon. Level the mixture with a flat squeegee or trowel, then back roll with medium nap phenolic core roller
- If a slip resistant finish is required, lightly and evenly broadcast aggregate into first coat after back rolling but before product begins to set
- Working time is 30 minutes at 75°F (23.9°C)

Note: Indicated working time is for product with standard hardener. See ADDITIONAL DATA for other working times.

ADDITIONAL DATA

Working time for product with fast cure (FC) hardener

- Working time is 10 minutes at 75° (23.9°C)

Pot life for product with fast cure (FC) hardener

- Pot life is 8-10 minutes at 75°F (23.9°C)

Working time for product with rapid cure (RPD) hardener

- Working time is 20 minutes at 75° (23.9°C)

Pot life for product with rapid cure (RPD) hardener

- Pot life is 10-15 minutes at 75°F (23.9°C)

Drying time with standard hardener		
Substrate temperature	Dry to touch	Dry to service
75°F (24°C)	10 hours	36 hours

Note: Provides best clarity for use as top coat.



PPG Flooring 980 Clear Epoxy Coating

Formerly known as Milamar PM100 Series Floor Coating

Drying time with rapid cure (RPD) hardener		
Substrate temperature	Dry to touch	Dry to service
75°F (24°C)	7 hours	24 hours

Note: Can be used as top coat.

Drying time with fast cure (FC) hardener		
Substrate temperature	Dry to touch	Dry to service
75°F (24°C)	3 hours	24 hours

- Notes:
- Not recommended for use as top coat.
 - Primarily intended for use in colder temperatures (50° (10°C) minimum) and fast applications of double broadcast systems.

Physical data of cured material	
Characteristic	Value
Compressive strength (ASTM C579)	>12,000 psi (>82.7 MPa)
Tensile Strength (ASTM D638)	5,992 psi (41.3 MPa)
Tensile Elongation (ASTM D638)	14%
Flexural Strength (ASTM C580)	7,127 psi (49.1 MPa)
Adhesion to Concrete (ASTM D4541)	>300 psi (>2.1 MPa)
Linear Shrinkage (ASTM C883)	None
Hardness, Shore D (ASTM D2240)	82-85
Water Absorption (ASTM C413)	<0.01%
Abrasion resistance (ASTM D4060)	70 mg loss
Indentation (MIL-D-3134F)	0.003 in (0.076 mm)

Note: The value ranges stated in this Technical Data Sheet are based on system processing under laboratory conditions. Equipment configurations and/or field application conditions may produce variances in final system values.

DISCLAIMER

- For industrial or professional use only
- This product is specifically suitable for use on the substrates mentioned in this document. For application on any other substrates, please always contact your PMC representative for specific instructions and in order to make sure that the product performance can be safeguarded.



PPG Flooring 980 Clear Epoxy Coating

Formerly known as Milamar PM100 Series Floor Coating

SAFETY PRECAUTIONS

- Read all label and Safety Data Sheet (SDS) information prior to use

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

- SAFETY INDICATIONS
- INFORMATION SHEET1430

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.