

JBX 3.5 VOC Acrylic Basecoat

Background

SHOP-LINE® JBX is a fast drying basecoat designed for today's automotive collision centers. For VOC compliance JBX must be top coated with a compliant *Shop-Line* clear coat.

Components

Color

JBX 3.5 VOC Acrylic Basecoat

Reducer

JR554 Fast 55-65°F (13-18°C)
 JR555 Medium 65-75°F (18-24°C)
 JR556 Slow 75-85°F (24-29°C)
 JR557 Retarder 85-95°F (29-35°C)

Compatible Products

Can be applied over:

Cured, cleaned and sanded OEM and refinish coatings.
 JP390 2.1 VOC Epoxy Primer
 JP221 2.1 VOC 1K Primer Surfacer
 JP35x 2.1 VOC Multi-Purpose Primers
 JP36x 2.1 VOC Urethane Sealers

Can be topcoated with:

JC7100 2.1 VOC HS European Multi-Panel Clearcoat
 JC7200 2.1 VOC HS European Clearcoat
 JC780 2.1 Polyurethane Speed Clear
 JC781 2.1 Polyurethane High Gloss Clear
 JC830 2.1 VOC Production Clear

Preparation

Surface Cleaning:

SXA330 Wax and Grease Remover
 SWX350 (H₂O-SO-CLEAN®)
 SX1009 2.9 VOC Bug and Tar Remover

Sanding

400 grit (machine or dry hand) or 500 (wet) on old finishes and primer surfaces.

Mixing



Ratios:

JBX	:	JR55X Reducer
1	:	1

Note: JBX may be reduced at a 2:1 ratio to improve hiding. At the 2:1 reduction, the flash times between coats may be extended. For metallic and pearl colors, the 1:1 ratio should be used for the final coat to improve metallic control and orientation



Pot Life:

Indefinite

Tinting:

JBX color may be tinted up to 10% with *Shop-Line* mixing bases and equal parts J136 JBX converter.



Additives:

Optional
 The hardener that will be used in the clearcoat selected for the repair may also be added to catalyze the basecoat as follows:
 10% to unreduced RTS or
 5% to reduced RTS

Air Pressure and Gun Setup



HVLP: 8 - 10 psi at the air cap
Compliant: 29 - 40 psi at the gun
Gun Setup: 1.3 - 1.6 mm or equivalent

Note: For best overall results, refer to spraygun manufacturer's recommendations for inlet air pressures.

Application



Coats: 2 - 3 coats or until proper color is achieved

Dry Times



Between Coats: 5 - 10 minutes at 70°F (21°C)



Air Dry: Tape: 45 minutes



Clearcoat: 20 minutes minimum, 24 hours maximum at 70°F (21°C)

Clean Up

Clean spray guns, gun cups, storage pots, etc., thoroughly with JR reducers, JT571 0.21 VOC General Purpose Solvent or another appropriate clean up solvent after each use.

Follow EPA guidelines for proper storage and disposal of solvent-borne waste paint.

Properties

Film Build Per Coat:

JBX Applied 1:1 0.5 - 0.6 mil

Square foot coverage at 1 mil

JBX Applied 1:1 245 - 277 sq. ft. / gal. at 100% transfer

RTS Combinations:	JBX Color (Package)	JBX : JR55x	JBX : JR55x
Volume Ratio:	N/A	1:1	2:1
Applicable Use Category	Color Coating	Color Coating	Color Coating
VOC Actual (g/L)	175 - 283	87 - 141	117 - 186
VOC Actual (lbs/gal)	1.46 - 2.36	0.73 - 1.18	0.97 - 1.55
VOC Regulatory (less water less exempt) (g/L)	338 - 417	338 - 417	336 - 417
VOC Regulatory (less water less exempt) (lbs/gal)	2.82 - 3.48	2.82 - 3.48	2.81 - 3.48
Density (g/L)	973 - 1191	1094 - 1267	1074 - 1242
Density (lbs/gal)	8.12 - 9.94	9.13 - 10.57	8.94 - 10.36
Volatiles wt. %	50.5 - 62.4	76.7 - 84.2	67.2 - 77.2
Solids wt. %	37.6 - 49.5	15.8 - 23.3	22.8 - 32.8
Water wt. %	0.0	0.0	0.0
Exempt wt. %	29.9 - 44.6	68.4 - 76.3	55.4 - 66.7
Water vol. %	0.0	0.0	0.0
Exempt vol. %	32.3 - 48.8	66.1 - 74.4	55.2 - 65.7



Limitations

Shop-Line products should not be combined with components of other product lines.

Precautionary Information:

The contents of this package may have to be blended with other components before the product can be use. Before opening the packages be sure you understand the warning messages on the labels of all components since the mixture will have the hazards of all of its parts. Spray equipment must be handled with due care and in accordance with manufacturer's recommendations. Follow label directions for respirator use. Wear eye and skin protection. Observe all applicable precautions.

Medical Response:

EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION (412) 434-4515; IN CANADA (514)-645-1320

See Material Safety Data Sheet and Labels for additional safety information and handling instructions.

Material Data Safety Sheets for the PPG products mentioned in this publication are available through your PPG *Shop-Line* brand distributor. To the best of our knowledge, the technical information in this bulletin is accurate; however, since PPG Industries is constantly improving its coating and paint formulas, the current technical data may vary somewhat from what was available when this bulletin was printed. Contact your *Shop-Line* brand distributor or visit www.ppgrefinish.com for the most up-to-date information.

The PPG Logo, *Shop-Line*, and *H₂O-So-Clean* are trademarks of PPG Industries Ohio, Inc.