

PPG HI-TEMP™ 808

DESCRIPTION

Water based acrylic insulative coating

PRINCIPAL CHARACTERISTICS

- 100% adherent, low permeability seamless composite insulation material that can be applied to metal at temperatures up to 149°C (300°F)
- Excellent for use as a personnel protection material, reducing burn injuries and reportable lost time accidents
- Offers an economical alternative to conventional insulation and jacketing for process equipment and piping up to 177°C (350°F)
- Reduces energy needs
- Enhances process stability
- Reduces total installation time compared to traditional insulation
- No cutting, tapping, or special hangers. Special fabrication is not required.
- Prevents Corrosion Under Insulation (CUI)
- Applicable to many substrates
- Non-combustible. Class A Fired Rated
- No pot life. Single component and water based
- Can easily be repaired if mechanically damaged
- Contains no harmful chlorides or toxins
- Successive coats will increase insulating capabilities

COLOR AND GLOSS LEVEL

- White, gray
- Flat

BASIC DATA AT 20°C (68°F)

Data for product	
Number of components	One
Volume solids	78 ± 2%
VOC (Supplied)	max. 12.1 g/l (approx. 0.1 lb/US gal)
Temperature resistance (Continuous)	To 350°F (177°C)
Recommended dry film thickness	15.0 - 20.0 mils (375 - 500 µm) depending on system
Theoretical spreading rate	63 ft ² /US gal for 20.0 mils (1.6 m ² /l for 500 µm)
Dry to overcoat	4.5 hours
Shelf life	At least 18 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Curing time



PPG HI-TEMP™ 808

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- Coating performance is, in general proportional to the degree of surface preparation. All surfaces must be dry and free of oil, grease, and other surface contamination.

Hot application

- Consult PPG technical service for instructions on hot application

Application equipment

- HT 808 may be applied with airless spray or a specialized small application sprayer. Consult PPG for details on the small application sprayer.

Substrate temperature and application conditions

- Surface temperatures during application and curing must be greater than 60 °F though ambient temperatures may be lower.
- The surface temperature must be at least 5°F (3°C) above dew point
- Relative humidity should not exceed 85%; surface must be free of visible moisture
- Mild steel must be primed with a recommended primer prior to the application of HT 808.
- Steel surfaces should be abrasive blasted to an SSPC SP-6 condition or higher prior to achieve the recommended profile for the specified primer.
- For steel structures operating at less than 200°F, power tool cleaning per SSPC SP-3 may be acceptable.
- Non-ferrous metals, stainless steel, and new galvanized steel may should be brush blasted per SSPC SP-16 requirements. Galvanizing with at least 12 months exterior weathering may be primed with an epoxy primer after solvent wiping per SSPC SP-1 standards.

SYSTEM SPECIFICATION

- Approved primers include Amercoat 5105, Amerlock 400, Sigmatherm 230
- Consult PPG for other approved primers.
- See table below for HT 808 thickness recommendations
- Durethane DTM may be applied as a topcoat.

THICKNESS RECOMMENDATIONS

Insulation and Personnel Protection		
Temperature	Recommended thickness	Number of layers
275°F (140°C)	1000 µm (40.0 mils)	3
300°F (150°C)	1523 µm (60.0 mils)	4
325°F (160°C)	2032 µm (80.0 mils)	5
350°F (180°C)	3048 µm (120.0 mils)	7

Notes:



PPG HI-TEMP™ 808

- Multiple coats will be applied to achieve the recommended film thickness for the operating temperature. A minimum of 40 mils is recommended.
 - Spray a light 5-10 mil initial tack coat to deter sliding of the product.
 - Normal thickness per coat is 20-24 wet mils.
 - In cold weather, apply multiple thin (10-12 mils) coats.
-

INSTRUCTIONS FOR USE

- Store product in a cool dry area and keep from freezing. Approximately 8 hours prior to use, turn pails up-side-down to allow product to soften and become easier to mix.
- Place feet on both sides of the container to prevent it from spinning while mixing. Mix thoroughly using a 1/2" reversible drill motor and 1/2" sheet rock mud mixing paddle (blade style). Reverse setting is important because mixing on forward setting can shear plastic off bucket walls, contaminating the coating. Mix the product until a uniform consistency is obtained. Note that over-mixing (more than 5 minutes at normal room temperature) may adversely affect the product.
- Flush all equipment with 20-30 gallons of tap water prior to use.
- Mask/cover all areas subject to over-spray.

Note:

- A topcoat should be specified on structures where ponding water is expected.
-

Airless spray

- Use a 3/8" or larger fluid hose with a maximum of 3 feet of 1/4" whip. A 1/2" fluid hose is strongly recommended for lengths greater than 50 feet.
- Hoses should normally be kept as short as possible
- Remove gun and pump suction filters

Recommended thinner

- No thinner should be added

Nozzle orifice

0.019 – 0.025 in (approx. 0.48 – 0.64 mm)

Nozzle pressure

3000 - 3500 p.s.i. (approx. 207 - 242 bar; 20.7 - 24.1 MPa)

Note:

- A 0.017" tip works well for spraying tight, complex areas and small parts
-

Brush/roller

- Roller application is not recommended
 - Small damaged or bare areas and random pinholes or up by brush. Repair larger areas by spray.
-

PPG HI-TEMP™ 808

Cleaning solvent

- Tap water
- Clean-up immediately after use with potable water. Discard clean up material in accordance with federal and local environmental regulations

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
40.0 mils (1000 µm)	31 ft ² /US gal (0.8 m ² /l)
80.0 mils (2000 µm)	16 ft ² /US gal (0.4 m ² /l)
120.0 mils (3000 µm)	11 ft ² /US gal (0.3 m ² /l)

Note:

- High humidity conditions may adversely affect film build characteristics

Overcoating Intervals up to 20 mils DFT based on Relative Humidity Ranges					
Overcoating with...	Interval	10°C (50°F)	15°C (59°F)	20°C (68°F)	30°C (86°F)
itself up to 30% RH	Minimum	8 hours	6 hours	4 hours	1.5 hours
	Maximum	Extended	Extended	Extended	Extended
itself 31-50% RH	Minimum	10 hours	8 hours	4.5 hours	2 hours
	Maximum	Extended	Extended	Extended	Extended
itself 51-70% RH	Minimum	12 hours	10 hours	6 hours	2.5 hours
	Maximum	Extended	Extended	Extended	Extended
Recommended Topcoats up to 30% RH	Minimum	3 days	60 hours	42 hours	20 hours
	Maximum	Extended	Extended	Extended	Extended
Recommended Topcoats 31-50% RH	Minimum	3.5 days	3 days	48 hours	25 hours
	Maximum	Extended	Extended	Extended	Extended
Recommended Topcoats 51-70% RH	Minimum	4 days	3.5 days	60 hours	30 hours
	Maximum	Extended	Extended	Extended	Extended



PPG HI-TEMP™ 808

SAFETY PRECAUTIONS

- The product is for use only by professional applicators in accordance with information in this product data sheet and the applicable material safety data sheet (MSDS). Refer to the appropriate MSDS before using this material. All use and application of this product should be performed in compliance with all relative federal, state and local, health, safety and environmental regulations or in compliance with all pertinent local, regional and national regulations as well as good safety practices for painting, and in conformance with recommendations in SSPC PA 1, "Shop, Field and Maintenance Painting of Steel."

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

- Information sheet | Explanation of product data sheets

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgmc.com. The English text of this sheet shall prevail over any translation thereof.