

# COLTURA EP FLOORING EVO 3MM

## DESCRIPTION

Three-component, solvent-free, self-leveling epoxy floor coating

## PRINCIPAL CHARACTERISTICS

- Self-leveling, thick coating applicable to 3 mm
- Good abrasion and impact resistance
- Easy cleaning
- Good chemical resistance
- Antiskid properties can be achieved in several ways
- EDF approved for nuclear industry

## COLOR AND GLOSS LEVEL

- A wide range of colors are available
- Gloss

## BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Three
Mass density	1.73 kg/l (14.44 lb/US gal)
Volume solids	98%
VOC (Supplied)	max. 90.0 g/l (approx. 0.8 lb/US gal)
Recommended dry film thickness	3000 µm (120.0 mils)
Theoretical spreading rate	0.3 m <sup>2</sup> /l for 3000 µm (120 ft <sup>2</sup> /US gal for 120.0 mils) depending on the roughness of the substrate
Dry to touch	14 hours
Dry to walk on	24 hours
Overcoating Interval	Minimum: 24 hours Maximum: 7 days
Full cure after	7 days
Shelf life	Base: at least 12 months when stored cool and dry Hardener: at least 12 months when stored cool and dry Filler: at least 36 months when stored cool and dry

Note:

- The spreading rate is depending on the roughness of the substrate



# COLTURA EP FLOORING EVO 3MM

## RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

### Primed concrete

- Suitable primer must be dry and free from any contamination
  - Moisture content should not exceed 4.5%
- 

### Substrate temperature and application conditions

- Ambient temperature during application and curing should be between 10°C (50°F) and 35°C (95°F)
  - Relative humidity during application and curing should not exceed 80%
  - Substrate temperature during application and curing should be between 10°C (50°F) and 30°C (86°F)
  - Substrate temperature during application should be at least 3°C (5°F) above dew point
- 

## INSTRUCTIONS FOR USE

### Mixing ratio by weight: base to hardener to filler 14.0:3.1:12.0

- Material temperature should be between 10°C (50°F) and 30°C (86°F)
  - Mix base and hardener with a variable-speed mechanical mixer thoroughly for 1 minute
  - Add the filler while stirring and stir thoroughly for 2 minutes
  - Pour the mixture into another can and mix for 2 minutes, until homogeneous
  - The speed of the mixer should not exceed 800 rpm to avoid air entrapment
- 

### Induction time

0 minute

Note:

- No induction time required
- 

### Pot life

25 minutes at 20°C (68°F)

---

### Trowel / Swedish knife

- Pour an appropriate amount of mixture on the primed concrete and spread it evenly by trowel or Swedish knife
- Use a spiked roller to avoid air entrapment

### Recommended thinner

No thinner should be added

---

# COLTURA EP FLOORING EVO 3MM

## **Brush/roller**

- Use a spiked roller to avoid air entrapment

## **Recommended thinner**

No thinner should be added

## **Cleaning solvent**

- DILUANT Nº1 Bis

## **SAFETY PRECAUTIONS**

- See Safety Data Sheet and product label for complete safety and precaution requirements
- Although this is a solvent-free paint, care should be taken to avoid inhalation of spray mist, as well as contact between the wet paint and exposed skin or eyes

## **WORLDWIDE AVAILABILITY**

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

## **REFERENCES**

- Information sheet | Explanation of product data sheets

## **WARRANTY**

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

## **LIMITATIONS OF LIABILITY**

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at [www.ppgmc.com](http://www.ppgmc.com). The English text of this sheet shall prevail over any translation thereof.