

# PU66 5462 8H NL Topcoat Matt

## TECHNICAL DATA SHEET

### Product Description

5462 is a two-component flexible polyurethane topcoat of the PU 66 range, designed for internal / external protection and decoration of aircraft structures.

- Conventional solids
- Excellent fluid resistance including skydrol hydraulic fluid
- Outstanding UV resistance & long term durability

### Components



#### Mix Ratio (by volume)

- |                         |  |
|-------------------------|--|
| • 5462/.... (Base)      | 1 part   |
| • 0730/9000 (Activator) | 1 part   |
| • 0491/9000 (Thinner)   | to viscosity (refer to viscosity section of this document) |

### Specifications



5462 is qualified to:

- BLGG 140301
- MDL 5041

5462 meets the performance requirements of:

- MIL-PRF-85285

#### Product Compatibility

5462 is compatible with the following primer specifications:

- |                  |             |
|------------------|-------------|
| • AIMS 04-04-002 | • RPS 661-2 |
| • BLGG 900101    | • S27-7004  |

*Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information*

### Surface Preparation and Pretreatment



Ensure surface is clean, dry and intact using a high performance solvent cleaner - DeSoto® CN20 or Desoclean™ 45 solvent cleaners are recommended. Observe recommended over coating window for primers. For further information, refer to technical data sheets for the relevant primers.

# PU66 5462 8H NL Topcoat Matt

## Instructions for Use



Base may require mechanical agitation. Ensure all components are adequately dispersed. Before adding the activator to the base, thoroughly stir or shake the base component until a smooth uniform mix is obtained. Slowly add activator to the base while stirring, then add required thinner while stirring.

*Note: All products and components should be placed in ambient conditions of 15-30°C (59-86°F) for at least 24 hours prior to mixing and application.*



### **Induction Time:**


Not required



### **Viscosity:** ( 23°C/73°F)

• AFNOR2.5	45 - 55 seconds
• AFNOR4	14 - 16 seconds
• BSB3	23 - 30 seconds
• BSB4	18 - 20 seconds
• FORD4	13 - 15 seconds
• ISO3	30 - 50 seconds
• ISO4	17 - 22 seconds
• ZAHN2	15 - 20 seconds

*Note: Viscosities quoted are typical ranges obtained when using specified mix ratio.*



### **Pot Life:**

4 hours @ 21 - 25°C (70 - 77°F)

## Application Guidelines

### **Recommended Application Conditions:**

Temperature	15 - 35°C (59 - 95°F)
Relative Humidity	30 - 85%

### **Application:**

Apply 2 cross coats to achieve the recommended dry film thickness.




### **Theoretical Coverage:** (ready for use unthinned)

6 - 8 m<sup>2</sup>/Lt @ 40 µm dry film thickness  
240 - 320 ft<sup>2</sup>/US gal @ 1.6 mil dry film thickness

# PU66 5462 8H NL Topcoat Matt

**Recommended Dry Film Thickness:**

30 - 50 µm  
1.2 - 2 mil



**Dry Film Density:**

1.3 - 1.6 g/cm<sup>3</sup> (depending on colour)  
10.8 - 13.3 lbs/US gal

**Dry Film Weight:**

51 - 65 g/m<sup>2</sup> @ 40 µm dry film thickness  
0.010 - 0.013 lbs/ft<sup>2</sup> @ 1.6 mil dry film thickness

*Note: These application guidelines represent PPG's best advice for usage in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.*

**Equipment:**



Equipment Type	Tip Size (mm)	Pressure
HVLP Air Spray	1.2	22 to 29 psi (1.5 to 2 bar)
Pressure Pot	1.5	43 to 72 psi (3 to 5 bar)



**Equipment Cleaning:**

Clean spray equipment before use and as soon as possible after use. DeSoto<sup>®</sup> CN20, CN44 or Desoclean<sup>™</sup> 45 solvent cleaners are recommended.

**Physical Properties**



**Colour:**

This product is available in a wide range of colours. Please contact PPG Aerospace to discuss specific requirements.



**Gloss:**


≤ 5 units with a 60° gloss meter

# PU66 5462 8H NL Topcoat Matt



DRYING TIMES @ 50 % R.H	23°C (73°F)	60°C (140°F)
Dust Free	2 hours	
Dry to Handle	5 hours	
Dry to Tape	8 hours	30 minutes
Dry to Overcoat	1 hour (min.) 72 hours (max.)	15 minutes
Full Cure	7 days	

*Note: Drying times listed above are dependent upon film thickness applied, air flow conditions and application technique.*



**Flash Off Time:**

15 - 30 minutes prior to force dry.



**VOC: (ASTM)**

Mixed ready for use	>600 g/Lt
5462 Base Component	460 g/Lt
0730/9000 Activator	705 g/Lt
0491/9000 Thinner	840 g/Lt



**Flash Point:**

5462 Base Component	2°C (61°F)
0730/9000 Activator	13°C (55°F)
0491/9000 Thinner	-2°C (28°F)

**Shelf Life:**

5462 Base Component	24 months in original unopened container
0730/9000 Activator	24 months in original unopened container
0491/9000 Thinner	10 years in original unopened container

*Note: Shelf life may vary due to OEM specification requirements. Refer to container label for specific shelf life information.*

*Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.*

## PU66 5462 8H NL Topcoat Matt

### Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

*Note: When procuring to a qualified material specification, follow those storage instructions.*



# PU66 5462 8H NL Topcoat Matt

## Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

**For industrial use only. Keep away from children.**

**Additional information can be found at: [www.ppgaerospace.com](http://www.ppgaerospace.com)**

**For sales and ordering information call the local PPG office at the numbers listed below:**

### **Asia Pacific**

#### **ASC – Australia**

Tel 61 (3) 9335 1557  
Fax 61 (3) 9335 3490

#### **ASC – Japan**

Tel 81 561 35 5200  
Fax 81 561 35 5201

#### **ASC – South East Asia**

Tel 65 6861 1119  
Fax 65 6861 6162

#### **ASC – Suzhou**

Tel (86-512) 6661 5858  
Fax (86-512) 6661 6868

#### **ASC – Tianjin**

Tel (86-022) 2482 8625  
Fax (86-022) 2482 8600

### **Americas**

1 (818) 362-6711 or 1-800-AEROMIX

### **Europe and Middle East**

#### **ASC – Central Europe**

Tel 49 (40) 742 193 10  
Fax 49 (40) 742 139 69

#### **ASC – Middle East & India**

Tel (971) 4 883 9666  
Fax (971) 4 883 9665

#### **ASC – North Europe**

Tel 44 (0) 1388 770222  
Fax 44 (0) 1388 770288

#### **ASC - South Europe**

Tel 33 (0) 235 53 43 71  
Fax 33 (0) 235 53 54 44

Desoclean, and DeSoto are trademarks of PRC-DeSoto International, Inc.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PPG Aerospace  
Sealants and Coatings  
Darlington Road  
Shildon, Co Durham UK  
DL4 2QP  
[www.ppgaerospace.com](http://www.ppgaerospace.com)

Issue Date: 07/16  
Lit: 4204