

# DIMETCOTE® 302 H

## DESCRIPTION

Reinforced inorganic zinc primer

## PRINCIPAL CHARACTERISTICS

- Provides outstanding corrosion resistance
- Fast dry times for rapid topcoating
- Low VOC
- Excellent corrosion resistance

## COLOR AND GLOSS LEVEL

- Green
- Flat

## BASIC DATA AT 68°F (20°C)

Data for mixed product	
Number of components	Two
Volume solids	78 ± 2%
VOC (Supplied)	max. 2.6 lb/US gal (approx. 312 g/l)
Temperature resistance (Continuous)	To 400°F (204°C)
Recommended dry film thickness	2.0 - 4.0 mils (50 - 100 µm) depending on system
Theoretical spreading rate	417 ft <sup>2</sup> /US gal for 3.0 mils (10.4 m <sup>2</sup> /l for 75 µm)
Shelf life	Base: at least 12 months when stored cool and dry Hardener: at least 12 months when stored cool and dry

### Notes:

- See ADDITIONAL DATA - Overcoating intervals
- See ADDITIONAL DATA - Curing time
- Color will drift at elevated temperatures

## RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- Coating performance is proportional to the degree of surface preparation
- All previous coats must be free of contaminants



# DIMETCOTE® 302 H

## **Steel**

- Abrasive Blast to SSPC SP-6 or higher with a 1.0-3.0 mil surface profile
  - Higher surface profiles up to 5 mils (125 µm) are acceptable, but the product must be applied in a thickness great enough to achieve a minimum of 2.5 mils (65 µm) dry film thickness
  - Apply this product as soon as possible to avoid rusting of blasted surfaces
  - Keep moisture, oil, grease and other organic matter off surface before coating
  - For touch up and repair, power tool cleaning in accordance with SSPC SP-11 is acceptable
- 

## **Atmospheric exposure conditions**

- Ambient temperature during application and curing should be between 20 °F (-6 °C) and 120 °F (49 °C)
  - Maximum 85% relative humidity during application and curing
- 

## **Substrate temperature and application conditions**

- Surface temperature during application should be between 20°F (-7°C) and 130°F (54°C)
  - Surface temperature during application should be at least 5°F (3°C) above dew point
- 

## **SYSTEM SPECIFICATION**

- Primers: Direct to metal, can be used to touch up inorganic zincs such as DIMETCOTE 9-SERIES
  - Topcoats: AMERCOAT Epoxies, PITTGUARD Epoxies
- 

## **INSTRUCTIONS FOR USE**

### **Mixing ratio by volume: base to hardener 90:10 (9:1)**

- Pre-mix base component with a power mixer for 1-2 minutes until thoroughly homogenized. Add the hardener under agitation and mix for another 1-2 minutes until incorporated. Strain from one container to another through a 30 mesh strainer to remove any undispersed lumps.
- 

### **Pot life**

8 hours at 70°F (21°C)

Note: See ADDITIONAL DATA – Pot life

---

### **Application**

- Area should be sheltered from airborne particulates and pollutants
- Ensure good ventilation during application and curing
- Provide shelter to prevent wind from affecting spray patterns

### **Material temperature**

Material temperature during application should be between 40°F (4°C) and 90°F (32°C)

---



# DIMETCOTE® 302 H

---

**Air spray**

- Separate air and fluid pressure regulators and a moisture and oil trap in the main air supply line are recommended.
- Use standard conventional equipment

**Recommended thinner**

THINNER 91-82 (AMERCOAT T-10), THINNER 21-25 (AMERCOAT 101) (recommended for > 90°F (32°C))

**Volume of thinner**

0 - 10%

**Nozzle orifice**

Approx. 0.070 in (1.8 mm)

---

**Airless spray**

- 45:1 pump or larger

**Recommended thinner**

THINNER 91-82 (AMERCOAT T-10), THINNER 21-25 (AMERCOAT 101) (recommended for > 90°F (32°C))

**Volume of thinner**

0 - 5%

**Nozzle orifice**

0.017 – 0.019 in (approx. 0.43 – 0.48 mm)

---

**Brush/roller**

- Use a high-quality natural-bristle brush. Brush application is only recommended for small touch-up and/or repair areas. Roller application is not recommended
- Ensure the brush/roller is well-loaded to avoid air entrainment. Level air bubbles with a brush. Multiple coats may be necessary to achieve adequate film build

**Recommended thinner**

AMERCOAT T-10, AMERCOAT 101 (recommended for >90°F (32°C))

**Volume of thinner**

0 - 5%

---

**Cleaning solvent**

AMERCOAT 12 CLEANER or AMERCOAT 65 THINNER (xylene)

# DIMETCOTE® 302 H

## ADDITIONAL DATA

Overcoating interval for DFT up to 3.0 mils (75 µm)					
Overcoating with...	Interval	40°F (4°C)	50°F (10°C)	70°F (21°C)	90°F (32°C)
various two-pack solvent-borne epoxy coatings	Minimum	8 hours	4 hours	1.5 hours	45 minutes
	Maximum	3 months	3 months	3 months	3 months

Note: Surface must be power washed as needed to remove all surface contaminants including zinc salts. Surface must be clean and dry

Curing time for DFT up to 3.0 mils (75 µm)	
Substrate temperature	Dry hard
40°F (4°C)	36 hours
50°F (10°C)	18 hours
70°F (21°C)	6 hours
90°F (32°C)	3 hours

Pot life (at application viscosity)	
Mixed product temperature	Pot life
50°F (10°C)	16 hours
70°F (21°C)	8 hours
90°F (32°C)	4 hours

## Product Qualifications

- Zinc dust meets ASTM D520 type 2 standards

## SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

## WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.



# DIMETCOTE® 302 H

## REFERENCES

• CONVERSION TABLES	INFORMATION SHEET	1410
• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431

## WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

## LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at [www.ppgmc.com](http://www.ppgmc.com). The English text of this sheet shall prevail over any translation thereof.

Packaging: Available in 1-gallon and 5-gallon kits

Product code	Description
DI302H-5A	Base
DI302H-B	Hardener

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

