



PR-1425 Class B windshield and canopy sealant

Description

PR-1425 Class B is an aircraft windshield and canopy sealant. It has a service temperature range from -65°F (54°C) to 250°F (121°C), with intermittent excursions up to 275°F (135°C). This material is designed for fillet sealing of properly prepared glass, polycarbonate, acrylic and other aircraft sealing applications. This product is specifically formulated not to craze substrates. The cured sealant exhibits excellent resistance to UV and weather exposure.

PR-1425 Class B is a two-part, dichromate cured polysulfide compound. The uncured material is a low sag, thixotropic paste, suitable for application by extrusion gun or spatula.

PR-1425 Class B is available in preformed parts using PPG's proprietary Ambient Reactive Extrusion (PPG ARE™) additive printing technology.

This sealant has excellent adhesion to common aircraft substrates. The following tests are in accordance with PRC-DeSoto International and other OEM specification test methods.

Application properties (typical)

| | | | |
|--|--------------------------|------------------------|---------------------|
| Color | | | |
| Part A | Black | | |
| Part B | Black | | |
| Mixed | Black | | |
| Mixing Ratio | | Part A:Part B | |
| By weight | | 12:100 | |
| Base viscosity, Poise (Pa-s) | | 16,000 (1,600) | |
| (Brookfield #7 @ 2 rpm) | | | |
| Slump, inches (mm) | | | |
| | Initial | 50 minutes | 90 minutes |
| B-1/2 | 0.20 (5.08) | --- | --- |
| B-1 | 0.15 (3.81) | --- | --- |
| B-2 | 0.20 (5.08) | 0.25 (6.35) | 0.25 (6.35) |
| Application life and cure time @ 77 °F (25 °C), 50% RH | | | |
| | | | Cure time to 30 |
| | Application life (hours) | Tack free time (hours) | Durometer A (hours) |
| B-1/2 | 1/2 | < 8 | 24 |
| B-1 | 1 | < 24 | 48 |
| B-2 | 2 | < 24 | 48 |

Performance properties (typical)

| | |
|--|----------|
| Cured 14 days @ 77 °F (25 °C), 50% RH | |
| Cured specific gravity | 1.49 |
| Nonvolatile content, % | 93 |
| Ultimate cure hardness, Durometer A | 55 |
| Peel strength, pli (N/25 mm), 100% cohesion, 14 days @ 77 °F (25 °C) | |
| No exposure | |
| AMS-G-25667 (glass) | 50 (222) |
| MIL-PRF-8184 (acrylic)* | 48 (214) |
| AMS-P-83310 (polycarbonate)* | 46 (205) |
| AMS5516 (stainless steel) | 46 (205) |
| AMS4911 (titanium comp. C) | 46 (205) |
| AMS4045 (aluminum) | 46 (205) |

*Abraded with 220 grit sandpaper and primed with PR-142 Adhesion Promoter

Thermal rupture resistance – retains pressure of 10 psi with only negligible deformation, both before and after immersion in JRF.

Low temperature flexibility @ -65 °F (-54 °C) – no cracking, checking or loss of adhesion.

Corrosion resistance – no corrosion, adhesion loss, softening, or blistering after 20-day immersion in 2-layer saltwater/JRF @ 140 °F (60 °C).

Flexibility – no cracks after bending 180 degrees over 0.125 inch (3.18 mm) mandrel.

Repairability to itself – excellent to both fresh cured as well as fuel-aged and abraded fillets.

Resistance to other fluids – excellent resistance to water, alcohols, petroleum-base and synthetic lubricating oils, and petroleum-based hydraulic fluids.

Fungus resistance non nutrient

Note: The application and performance property values above are typical for the material but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions, and configurations.

PR-1425 Class B windshield and canopy sealant

Surface preparation

Immediately before applying sealant to primed substrates, the surfaces should be cleaned with solvents. Contaminants such as dirt, grease and/or processing lubricants must be removed prior to sealant application.

A progressive cleaning procedure should be employed using appropriate solvents and a new lint-free cloth. (Reclaimed solvents or tissue paper should not be used.) Always pour solvent on the cloth to avoid contaminating the solvent supply. Wash one small area at a time.

It is important that the surface is dried with a second clean cloth prior to the solvent evaporating to prevent the redeposition of contaminants on the substrate.

Substrate composition can vary greatly. This can affect sealant adhesion. It is recommended that adhesion characteristics to a specific substrate be determined prior to application on production parts or assemblies.

For a more thorough discussion of proper surface preparation, please consult the SAE Aerospace Information Report AIR 4069. This document is available through SAE, 400 Commonwealth Avenue, Warrendale, PA 15096-0001.

Packing options

PR-1425 Class B is supplied in two-part can kits, Semkit® injection kits, and pre-mixed and frozen Semco® cartridges.

PR-1425 Class B is also available in preformed parts using *PPG ARE technology*.

Storage life

The storage life of PR-1425 Class B stored in two-part can kits and *Semkits* is at least 9 months when stored at temperatures between 40 °F (4.5 °C) and 80 °F (27 °C) in original, unopened containers.

The storage life of PR-1425 Class B in pre-mixed and frozen *Semco* cartridges is at least 28 days when stored at temperatures below -40 °F (-40 °C).

Health precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS) which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available upon request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

**For emergency medical information call
1-800-228-5635**

**Additional information can be found at:
www.ppgaerospace.com**

**For sales and ordering information call
1-800-AEROMIX (237-6649).**

Permapol, ARE, Semkit, and Semco are registered trademarks of PRC-DeSoto International Inc., registered with the U.S. Patent Office.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller. Printed in the U.S.A.

This document has been reviewed by the PPG Aerospace Export Control Department and has been determined to contain only EAR99 controlled data.

PRC-DeSoto International, Inc.
12780 San Fernando Road
Sylmar, CA 91342
Telephone (818) 362-6711
Toll Free (800) AEROMIX
www.ppgaerospace.com

Issue Date: 03/24
Supersedes: 07/17
Lit: 0161