


## Desothane® HS CA8800 Polyurethane Topcoats

### Product Description

Desothane® HS Buffable topcoats are polyurethane coatings used to protect the exterior of aircraft. These high solids topcoats are designed to be applied over Desoprime™ epoxy primers and Desofill™ surfacers.

- Compatible with epoxy primers, surfacers, and intermediate coating
- May be buffed to remove minor imperfections
- Excellent gloss and image reflection
- Retains gloss and color in harsh exterior environments
- Can be applied in a wide range of conditions
- Excellent impact and erosion resistance
- Compatible with all current spray equipment
- Skydrol® resistant
- Service temperature -54°C to 177°C (-65°F to 350°F)

### Components



#### **Mix ratio (by volume) for gloss colors:**

- |                                 |         |
|---------------------------------|---------|
| • CA8800/XXXX (base component)  | 2 parts |
| • CA8800Z (activator component) | 1 part  |
| • CA8800CT (thinner component)  | 1 part  |

*Note: Desothane® HS Buffable thinners are available in various options based on dry time requirements: CA8800CT, CA8800CTR, CA8800CT1, CA8800CT2, CA8800CT3, CA8800CT4 and CA8800CT5*

### Specifications



CA8800 series topcoats are qualified to:

- |                                     |                      |
|-------------------------------------|----------------------|
| • AMS 3095                          | • GAMPS 3209         |
| • BAMS 565-009 Grade B Type II      | • MEP 10-069         |
| • BMS 10-125 Type III & VI Grade D  | • MM1276 Type II     |
| • DHMS C4.04 Type 6 Class B Grade B | • MS100029E Class HS |
|                                     | • PAI 3760           |
|                                     | • VMS C4.04          |

CA8800 series topcoats meet the requirements of:

- |                                     |                               |
|-------------------------------------|-------------------------------|
| • BMS 10-60 Type II Class B Grade D | • BMS 10-125 Type III Grade D |
| • BMS 10-72 Type VIII               | • BMS 10-126 Type I Grade D   |

CA8800 series topcoats are listed on the following process standards:

- |           |            |
|-----------|------------|
| • D6-1816 | • DPM 6546 |
|-----------|------------|

*Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.*

### **Product Compatibility:**

CA8800 topcoats are compatible with the following primer specifications:

- 299-947-322 Type I
- AMS 3095
- BAMS 565-008 Grade A & B Type II
- BMS 10-72 Type VIII & IX Class NC
- BMS 10-79 Type II & III
- BMS 10-103 Type I Grade A
- BMS 10-118 Type I & II Grade B
- BMS 10-123 Type I Grade B
- CMS-CT-201 Class A & B Grade A & B
- CMS-CT-206 Type I Class A
- DHMS C4.01 Type 3 Grade A
- DHMS C4.18 Type III Class A Grade B
- GAMPS 3103
- GP110AEE
- HMS 16-1738
- HMS 16-2122
- MEP 10-060 Type I & II Class A & B
- MEP 10-068 Class A & B
- MEP 10-070
- MM1275 Type I & II
- MS100016E Class S
- PWA 36525 Type 1
- SMS-111204 Type 1 Class 1 Form 1 & 2
- SMS-111207 Type 7
- STMGK 189
- TCE-M-20710-14
- VMS C4.01 Type 3 Grade A
- VMS C4.18 Type 3 Class A Grade B

## **Surface Preparation and Pretreatments**



CA8800 high solids topcoats can be applied over clean, dry, intact urethane compatible epoxy primers, surfacers, or intermediate coating. The surface may be cleaned with DeSoto® CN20, DeSoto® CN44, or Desoclean™ 110 solvent cleaner. Observe over coating window for primers or intermediate coating. For further information, refer to the Technical Data Sheets for the above mentioned primers and intermediate coating.

## **Instructions for Use**



### **Mixing Instructions:**

Prior to mixing, thoroughly shake the base component. Add one volume of CA8800Z buffable activator component to two volumes of base component and stir well. While mixing, add one volume of CA8800CT series thinner component and maintain constant agitation for 10 minutes. CA8800CT series component must be added to ensure adequate pot life and spray properties.

*Note: It is important to condition the paint for 24 hours prior to mixing by placing all materials in the shop or hangar, with ambient temperatures between 13° and 35°C (55° to 95°F). The minimum temperature of the paint components should be 13°C (55°F) prior to mixing.*


**Induction Time:**

Not Required

**Viscosity:** (23°C/73°F)

- #2 Signature Zahn cup 18 to 22 seconds
- #4 Ford cup 14 to 17 seconds
- ISO 4mm cup 19 to 30 seconds
- BSB3 cup 48 to 71 seconds
- BSB4 cup 17 to 22 seconds
- AFNOR #2.5 cup 56 to 70 seconds
- AFNOR #4 cup 16 to 18 seconds

*Note: Viscosities quoted are the typical ranges obtained when using specified mix ratio.*

**Pot Life:** 21 - 25°C (70 - 77°F)

Thinner	Time
CA8800CT	3 hours
CA8800CTR	3 hours
CA8800CT1	2 hours
CA8800CT2	1 hour
CA8800CT3	45 minutes
CA8800CT4	30 minutes
CA8800CT5	15 minutes

**Application Guidelines****Recommended Application conditions:**

Temperature 15 - 30°C (59 - 86°F)  
Relative Humidity 20 - 90%

**Application:**


Ground the aircraft and the application equipment before top coating. Stir the topcoat slowly during the application. The suggested film thickness is 50 to 75 microns (2.0 to 3.0 mils). This can be accomplished by two or three medium coats with a 50% overlap. Note the first coat should be allowed to tack up before applying the second coat. If the second is applied before the first coat has tacked up, sagging may occur. If the first coat is completely dry, a heavy orange peel could result.

*These application guidelines represent PPG's best advice in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.*

**Theoretical Coverage:**

20 square meters/liter at 25 microns dry film (825 square feet/gallon at 1 mil dry film)

Recommended dry film thickness; 50 to 75 microns (2 to 3 mils)

**Dry Film Density:**

1.48 grams/cubic centimeter (12.32 pounds/gallon)

**Dry Film Weight:**

37 grams/square meter at 25 microns dry film (0.0068 pounds/square feet at 1 mil dry film)

**Equipment:**

CA8800 high solids topcoats are compatible with all current forms of spray equipment.

Equipment Type	Tip Size	Pot Pressure	Atomization Pressure at the Cap
Electrostatic Air Spray Gun	1.2 mm or 1.5 mm	10 to 20 psi (0.69 to 1.4 bar)	45 to 60 psi (3.1 to 4.1 bar)
Electrostatic Air Assisted Airless Spray Gun	#611 or #613 (Graco Nomenclature)	700 to 1200 psi (48 to 82 bar)	40 to 60 psi (2.8 to 4.1 bar)
High Volume Low Pressure Spray Gun (HVLP)	1.0 mm to 1.4 mm	10 to 20 psi (0.69 to 1.4 bar)	10 psi maximum (0.69 bar)
Conventional Air Spray Gun	1.2 mm to 1.8 mm	10 to 20 psi (0.69 to 1.4 bar)	45 to 60 psi (3.1 to 4.1 bar)

**Equipment Cleaning:**

Clean spray equipment as soon as possible after use. Flush spray equipment with DeSoto® CN20, DeSoto® CN44, or Desoclean™ 45 high performance solvent cleaner.

**Physical Properties (product)**

**Color:** Various



**Gloss:** 90+ G.U at 60°



**Dry Times at Various Temperatures:**

<b>20°C (68°F)</b>				
<b>Thinners</b>	<b>Dry to Tape</b>	<b>Wet Edge</b>	<b>Time Between Coats</b>	<b>Dry to Fly</b>
CA8800CT	9 - 12 hours	45 - 60 minutes	50 - 100 minutes	90 hours
CA8800CT1	7 - 10 hours	25 - 40 minutes	40 - 60 minutes	65 hours
CA8800CT2	4 - 5 hours	15 - 30 minutes	35 - 45 minutes	40 hours
CA8800CT3	3 - 4 hours	10 - 15 minutes	30 - 40 minutes	24 hours
CA8800CT4	2 - 3 hours	5 - 10 minutes	15 - 20 minutes	12 hours
CA8800CT5	1 - 2 hours	3 - 5 minutes	10 - 15 minutes	8 hours
<b>25°C (77°F)</b>				
<b>Thinners</b>	<b>Dry to Tape</b>	<b>Wet Edge</b>	<b>Time Between Coats</b>	<b>Dry to Fly</b>
CA8800CT	8 - 12 hours	30 - 45 minutes	45 - 60 minutes	72 hours
CA8800CT1	5 - 7 hours	15 - 30 minutes	30 - 45 minutes	48 hours
CA8800CT2	3 - 4 hours	10 - 15 minutes	20 - 30 minutes	24 hours
CA8800CT3	1 ½ - 2 ½ hours	8 - 12 minutes	15 - 20 minutes	12 hours
CA8800CT4	1 - 1 ½ hours	3 - 5 minutes	10 - 15 minutes	8 hours
CA8800CT5	45 - 60 minutes	2 - 4 minutes	7 - 13 minutes	6 hours
<b>30°C (87°F)</b>				
<b>Thinners</b>	<b>Dry to Tape</b>	<b>Wet Edge</b>	<b>Time Between Coats</b>	<b>Dry to Fly</b>
CA8800CT	6 - 9 hours	25 - 40 minutes	40 - 55 minutes	55 hours

CA8800CT1	3 - 6 hours	10 - 25 minutes	25 - 35 minutes	30 hours
CA8800CT2	2 - 4 hours	8 - 15 minutes	15 - 25 minutes	18 hours
CA8800CT3	1 ½ - 3 hours	6 - 12 minutes	10 - 15 minutes	10 hours
CA8800CT4	45 - 60 minutes	5 - 10 minutes	8 - 12 minutes	6 hours
<b>35°C (95°F)</b>				
<b>Thinners</b>	<b>Dry to Tape</b>	<b>Wet Edge</b>	<b>Time Between Coats</b>	<b>Dry to Fly</b>
CA8800CT	5 - 8 hours	20 - 30 minutes	30 - 40 minutes	36 hours
CA8800CTR (Retarder)	5 - 8 hours	30 - 45 minutes	40 - 60 minutes	36 hours
CA8800CT1	3 - 5 hours	10 - 20 minutes	15 - 30 minutes	24 hours
CA8800CT2	2 - 3 hours	5 - 10 minutes	10 - 20 minutes	12 hours

Thinners may also be blended together to customize application and dry times.

Accelerated cure when using CT thinners:

Allow 30 minutes flash off at 24°C (75°F)  
followed by 60 minutes at 49°C (120°F)

*Note: The cure rate of CA8800 topcoats is not affected by humidity.*

## VOC

### VOC:

Mixed, ready for use VOC (EPA method 24)	420 grams/liter
Base Component	338 grams/liter
Activator Component	116 grams/liter
Thinner Component	
CA8800CT	867 grams/liter
CA8800CTR	801 grams/liter



### Flash point closed cup:

Base Component	29°C (84°F)
Activator Component	29°C (84°F)
Thinner Component	

CA8800CT  
CA8800CTR

24°C (75°F)  
43°C (110°F)

### **Shelf Life**

12 months from date of manufacture to most OEM material specifications. Consult the specification to verify shelf life requirements.

24 months from date of manufacture for PRC-DeSoto Standard.

*Note: Shelf life is provided for original, unopened containers.*

*Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.*

### **Storage Recommendations**



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

*Note: When procuring to a qualified material specification, follow those storage instructions.*

### **Health Precautions**

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

**For industrial use only. Keep away from children.**

**Additional information can be found at: [www.ppgaerospace.com](http://www.ppgaerospace.com)**

**For sales and ordering information call the local PPG office at the numbers listed below:**

#### **Asia Pacific**

**ASC – Australia**  
Tel 61 (3) 9335 1557  
Fax 61 (3) 9335 3490

**ASC – Japan**  
Tel 81 561 35 5200  
Fax 81 561 35 5201

#### **Europe and Middle East**

**ASC – Central Europe**  
Tel 49 (40) 742 193 10  
Fax 49 (40) 742 139 69

**ASC – Middle East & India**  
Tel (971) 4 883 9666  
Fax (971) 4 883 9665

**ASC – South East Asia**

Tel 65 6861 1119

Fax 65 6861 6162

**ASC – Suzhou**

Tel (86-512) 6661 5858

Fax (86-512) 6661 6868

**ASC – Tianjin**

Tel (86-022) 2482 8625

Fax (86-022) 2482 8600

**ASC – North Europe**

Tel 44 (0) 1388 770222

Fax 44 (0) 1388 770288

**ASC – South Europe**

Tel 33 (0) 235 53 43 71

Fax 33 (0) 235 53 54 44

**Americas**

1 (818) 362-6711 or 1-800-AEROMIX

**Desoclean, Desofill, Desoprime, Desothane, DeSoto, and Skydrol are trademarks of PRC-DeSoto International, Inc.**

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PRC-DeSoto International, Inc.  
12780 San Fernando Road  
Sylmar, CA 91342

[www.ppgaerospace.com](http://www.ppgaerospace.com)

Issue Date: 11/18

Lit: 2016