

PPG HI-TEMP™ 1027 HD

DESCRIPTION

Two-component, ambient cured multi-polymeric heat resistant coating system

PRINCIPAL CHARACTERISTICS

- Designed to prevent corrosion under insulation (CUI) of carbon steel and stainless steel
- Enhanced wear resistant coating for ease of transport
- New-build, shop, and field application
- Cyclic temperature resistance from -196°C (-320°F) to 540°C (1000°F)
- Resistant to thermal shock / cycling and intermittent immersion and boiling water
- Resistant to dry operating windows up to 650°C (1200°F)
- Good UV resistance
- Designed for single coat application, may be used in two coats if so specified or on complex structures
- Cures at temperatures down to -10°C (14°F)

COLOR AND GLOSS LEVEL

- Grey, Dark Grey
- Flat

Note: Minor color differences may occur due to batch variation and from exposed service above 316°C (600°F)

BASIC DATA AT 20°C (68°F)

Data for product	
Number of components	Two
Mass density	1.8 kg/l (14.7 lb/US gal)
Volume solids	65 ± 2%
VOC (Supplied)	max. 408.0 g/l (approx. 3.4 lb/US gal)
Recommended dry film thickness	125 - 300 µm (5.0 - 12.0 mils) per coat
Theoretical spreading rate	2.6 m ² /l for 250 µm (104 ft ² /US gal for 10.0 mils)
Dry to touch	2 hours
Dry to handle/ship	24 hours
Overcoating Interval	See overcoating tables
Shelf life	Base: at least 12 months when stored cool and dry Hardener: at least 12 months when stored cool and dry

Note: See ADDITIONAL DATA – Curing time



PPG HI-TEMP™ 1027 HD

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions of carbon steel for insulated and non-insulated service

- Must be free of oil, dirt, grease and all other contaminants, especially salts
- Round off all rough welds and sharp edges. Remove weld spatter
- Recommended is dry abrasive blast cleaning to SSPC-SP 6, "Commercial Blast" (ISO-Sa 2) with a 25 to 50 µm (1.0 to 2.0 mils) profile

Substrate conditions of stainless steel for insulated and non-insulated service

- Must be free of oil, dirt, grease and all other contaminants, especially salts
- Round off all rough welds and sharp edges. Remove weld spatter
- Lightly abrasive blast in accordance with SSPC SP-16 requirements or otherwise abrade the surface to ensure a uniform and dense surface profile of at least 25 µm (1.0 mil)
- Small surfaces may be cleaned with a chlorinated-free solvent. Large surfaces may be cleaned utilizing a high- or low-pressure wash or steam cleaning with an alkaline detergent (such as Prep 88), followed by a freshwater rinse. Water used should be potable grade or better and should be checked to assure minimal salt content. Do not use any chemical additives in the rinse water

Note: Do not use chlorinated solvents on stainless steel surfaces

Substrate temperature and application conditions

- Substrate temperature during application should be between 10°C (50°F) and 149°C (300°F)
- Substrate temperature during application should be at least 3°C (5°F) above dew point
- Relative humidity during curing should be above 20% and below 90%

Initial high temperature exposure

Note: For initial high temperature exposure, substrate temperature should be increased slowly at a rate of 1 - 2°C per minute to 177°C - 204°C (350°F - 400°F) and held for 2 hours. After this procedure has been completed, full film properties and thermal cycling resistance will be achieved.

SYSTEM SPECIFICATION

Non-insulated service: carbon and stainless steel

- PPG HI-TEMP 1027 HD: minimum 200-250 µm (8-10 mils) DFT continuous application using multiple spray passes. Refer to application guide for additional details
- Designed for single coat application, specified thickness can also be built up in 2 coats
- Compatible PPG HI-TEMP topcoats to their respective maximum service temperatures: PPG HI-TEMP 500 or PPG HI-TEMP 1000. Consult a PPG representative for application to hot substrates.

PPG HI-TEMP™ 1027 HD

Insulated service: carbon steel

- PPG HI-TEMP 1027 HD: minimum 250-300 µm (10-12 mils) DFT continuous application using multiple spray passes. Refer to application guide for additional details
 - Designed for single coat application, specified thickness can also be built up in 2 coats
-

Insulated service: stainless steel

- PPG HI-TEMP 1027 HD: minimum 250-300 µm (10-12 mils) DFT continuous application using multiple spray passes. Refer to application guide for additional details
 - Designed for single coat application, specified thickness can also be built up in 2 coats
-

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 2:1

- Pre-mix each component with a pneumatic air mixer at moderate speeds to homogenize the container. Add hardener to base and agitate with a power mixer for 1-2 minutes until completely dispersed
-

Air spray

- No thinner is recommended

Nozzle orifice

1.8 – 2.2 mm (approx. 0.070 – 0.087 in)

Nozzle pressure

0.4 - 0.6 MPa (approx. 4 - 6 bar; 58 - 87 p.s.i.)

Airless spray

- No thinner is recommended

Nozzle orifice

Approx. 0.43 – 0.53 mm (0.017 – 0.021 in)

Nozzle pressure

13.8 MPa (approx. 138 bar; 2002 p.s.i.)

Brush/roller

- Spray application is recommended but when spray painting is not possible, brush or roller may be used. The coating should be applied with a suitable brush or short nap roller, brush and roll only in one direction

Recommended thinner - application to ambient substrate below 66°C (150°F)

- THINNER 21-06 (AMERCOAT 65)

Volume of thinner

Up to 5% THINNER can be added if desired



PPG HI-TEMP™ 1027 HD

Cleaning solvent

- THINNER 21-06 (AMERCOAT 65)

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
250 µm (10.0 mils)	2.6 m ² /l (104 ft ² /US gal)
300 µm (12.0 mils)	2.2 m ² /l (87 ft ² /US gal)

Curing time for DFT up to 250 µm (10.0 mils)		
Substrate temperature	Dry to recoat/topcoat	Dry to handle/ship
5°C (41°F)	24 hours - 36 hours	3 days
10°C (50°F)	16 hours - 24 hours	48 hours
20°C (68°F)	6 hours - 8 hours	24 hours
30°C (86°F)	5 hours - 7 hours	15 hours
40°C (104°F)	4 hours - 6 hours	12 hours

Notes:

- Minimum re-coating/top-coat time mentioned refers to compatible topcoats. PPG HI-TEMP 1027 HD can be re-coated with itself without considering a minimum over coating time
- Drying times are dependent on air and steel temperature, applied film thickness, ventilation and other environmental conditions
- Relative humidity of < 50 % will reduce curing speed and increase time to full cure
- For insulation, the drying times have to be doubled from dry to handle time to ensure sufficient solvent evaporation

Pot life (at application viscosity)	
Mixed product temperature	Pot life
20°C (68°F)	6 hours - 8 hours

SAFETY PRECAUTIONS

- The product is for use only by professional applicators in accordance with information in this product data sheet and the applicable material safety data sheet (MSDS). Refer to the appropriate MSDS before using this material. All use and application of this product should be performed in compliance with all relative federal, state and local, health, safety and environmental regulations or in compliance with all pertinent local, regional and national regulations as well as good safety practices for painting, and in conformance with recommendations in SSPC PA 1, "Shop, Field and Maintenance Painting of Steel."

PPG HI-TEMP™ 1027 HD

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

• CONVERSION TABLES	INFORMATION SHEET	1410
• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431
• CLEANING OF STEEL AND REMOVAL OF RUST	INFORMATION SHEET	1490

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

