



## MP802

### 2.1 VOC Multi-Purpose Rollable Primer

---

#### Background

OMNI<sup>®</sup> MP802 is a fast drying, two component gray multi-purpose 2.1 VOC primer which may be used as a rollable primer surfacer

---

#### Components

**Primer**

MP801 2.1 VOC Multi-Purpose Primer - White  
MP802 2.1 VOC Multi-Purpose Primer - Gray  
MP803 2.1 VOC Multi-Purpose Primer - Black

**Hardener**

MH810 Multi-Purpose Primer Hardener

**Reducer**

MR294 Compliant Reducer Fast  
MR295 Compliant Reducer Medium  
MR296 Compliant Reducer Slow  
(refer to OBTB-001 *Omni* Low VOC Reducer Guide)

**Roller/Tray**

SX1066 Light Build Roller Cover  
SX1068 Roller Handle  
SX1069 Roller Pan

---

#### Compatible Products

**Can be applied over:**

Cleaned, sanded and etch primed steel, galvanized and aluminum.  
Sanded and cleaned body filler, SMC and gel-coated fiberglass.  
Properly cleaned and sanded E-coat  
Cleaned, cured and sanded OEM and refinish coatings.  
SX1071 ECOBASE™ 5.5 Etch Primer  
SU470LV 1K Compliant Adhesion Promoter  
MP246 Polyester Primer  
MP871 2.1 VOC Epoxy Primer - Gray

**Can be topcoated with:**

MP871 2.1 VOC Epoxy Primer - Gray  
MP89x 2.1 VOC Urethane Sealers  
MBPX *Omni* Plus 3.5 VOC Acrylic Urethane Basecoat  
MBX 3.5 VOC Acrylic Basecoat  
MTX 2.8 VOC Single Stage  
MLX 2.8 VOC Acrylic Enamel

---

#### Preparation

**Surface Cleaning:**

SXA330 ACRYLI-CLEAN<sup>®</sup> Wax and Grease Remover  
SXA103 MULTI-PREP™  
SWX350 (H<sub>2</sub>O-SO-CLEAN<sup>®</sup>)  
SX1009 2.9 VOC Bug and Tar Remover

**Sanding**

For use as a primer: 180-220 Grit machine on bare steel  
For use as a sealer: 320-400 Grit machine on primer or old finishes.

---

## Mixing

---



**Ratio:**

<b>MP80x</b>	:	<b>MH810</b>	:	<b>MR29x*</b>
4	:	1	:	2

*\*To improve application, solvent may be added or reduced as needed depending on job size and shop conditions.*



**Pot Life:** 45 minutes at 70°F (21°C) at 4:1:2



**Additives:** SLV814 Universal Flexibilizer 10% to RTS quart

---

## Application

---



2 - 3 coats

**1st Coat:**

Fully cover the roller by rolling it in the MP802 primer. Start from the center of the repair and roll the primer all the way out to the featheredge using a “flicking” or lifting technique that will create a feathered edge in the primer around the entire repair. This technique will ensure a thin, smooth edge and make sanding of the featheredge much easier.

**2nd and 3rd Coats:**

When the first coat has thoroughly flashed for approximately 3 - 5 minutes, again start from the center and roll another coat just inside the edge of the first coat, using a featheredge ‘lifting’ technique. Note: Be sure to not allow the 2nd and 3rd coats to extend past the outside edge of the previous coat’s featheredge or solvent may be trapped resulting in shrinkage and may also generate a heavier edge than desired which will require excessive finish sanding.

**Sanding:**

After an appropriate air dry or force cure, MP802 can be wet sanded with P400 followed by P600 or dry sanded with P360 followed by P500. After sanding, a minimum film build of 1.5 mils is recommended for optimum performance.

---

## Dry Times

---



**Between coats:** 3 - 5 minutes at 70° (21°C)



**Air Dry:** 1-2 hours to sand and topcoat at 70°F (21°C)



**Force Dry:** 20 - 30 minutes at 140°F (60°C) metal temperature



**Infrared:** Flash 10 minutes on medium power then cure for 20 minutes



**Topcoat:**  
**Air Dry**  
1-2 hours  
**Force Dry**  
After cool down

---

## Clean Up

---

The SX1069 Roller Pans are designed to be solvent resistant and may be cleaned and re-used. Clean all equipment thoroughly with the appropriate clean up solvent such as MS151 Low VOC General Purpose Cleaner after each use. Follow EPA guidelines for proper storage and disposal of solvent-borne waste paint and materials.

---

## Properties

---

### Film Build Per Coat

Applied 4:1:2 1.5 - 2 mils.

### Square foot coverage at 1 mil

Applied 4:1:2 592 sq. ft. / gal. at 100% transfer

---

PRIMER SEALER	Standard System	Flexible System
RTS Combinations	MP80x : MH810 : MR29x	MP80x : MH810 : MR29x + 10% SLV814
Volume Ratio:	4 : 1 : 2	4 : 1 : 2 +10%
Applicable Use Category	Primer	Primer
VOC Actual (g/L)	120	113
VOC Actual (lbs/gal)	1.00	0.94
VOC Regulatory (less water less exempt) (g/L)	235	228
VOC Regulatory (less water less exempt) (lbs/gal)	1.96	1.90
Density (g/L)	1450 - 1490	1430 - 1466
Density (lbs/gal)	12.10 - 12.43	11.93 - 12.23
Volatiles wt. %	49.4 - 50.7	51.2 - 52.5
Solids wt. %	49.3 - 50.6	47.5 - 48.8
Water wt. %	0.0	0.0
Exempt wt. %	41.1 - 42.7	43.3 - 44.8
Water vol. %	0.0	0.0
Exempt vol. %	49.0	50.3

---

### Limitations

*Omni* products should not be combined with components of other product lines.

### Precautionary Information:

The contents of this package may have to be blended with other components before the product can be use. Before opening the packages be sure you understand the warning messages on the labels of all components since the mixture will have the hazards of all of its parts. Spray equipment must be handled with due care and in accordance with manufacturer's recommendations. Follow label directions for respirator use. Wear eye and skin protection. Observe all applicable precautions.

---

### Medical Response:

**EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION (412) 434-4515; IN CANADA (514)-645-1320**

---

### See Safety Data Sheet and Labels for additional safety information and handling instructions.

Data Safety Sheets for the PPG products mentioned in this publication are available through your PPG *Omni* brand distributor. To the best of our knowledge, the technical information in this bulletin is accurate; however, since PPG Industries is constantly improving its coating and paint formulas, the current technical data may vary somewhat from what was available when this bulletin was printed. Contact your *Omni* brand distributor or visit [www.ppgrefinish.com](http://www.ppgrefinish.com) for the most up-to-date information.

---



We protect and  
beautify the world™