

KL6129/KL6129B

Epoxy Primer/Sealer

DESCRIPTION

Two-component epoxy-amidoamine primer/sealer

PRINCIPAL CHARACTERISTICS

- Use as a primer/sealer for rough, etched or blasted concrete surfaces subject to radiation, decontamination, and Loss-Of-Coolant accidents in Coating Service Level I Areas of Nuclear Power Plants
- High solids, VOC compliant
- Qualified for use as a sealer on concrete surfaces in Nuclear Coating Service Level I Areas

COLOR AND GLOSS LEVEL

- Clear amber
- Gloss

Note: On concrete surfaces product will absorb into the porosity of the concrete leaving a darkened dull finish. If concrete varies in porosity the surface may range from dull to glossy

BASIC DATA AT 25°C (77°F)

Data for mixed product	
Number of components	Two
Volume solids	95 ± 3%
VOC (Supplied)	max. 0.4 lb/US gal (approx. 52 g/l) max. 1.2 lb/US gal (approx. 143 g/l)
Recommended dry film thickness	2.0 - 4.0 mils (50 - 100 µm) per coat
Theoretical spreading rate	762 ft ² /US gal for 2.0 mils (18.7 m ² /l for 50 µm) 381 ft ² /US gal for 4.0 mils (9.4 m ² /l for 100 µm)
Dry to touch	12 hours at 25 °C (77°F)
Dry to topcoat	12 hours
Shelf life	At least 12 months when stored cool and dry

Notes:

- VOC reported as Air Dried @ 0.4 lbs./gal and 1.2 lbs./gal as EPA 24 test method
- The dry film thickness and spreading rate are depending on the absorption capability coming from the roughness and porosity of the concrete
- Dry to topcoat at 12 hours as long as product is not wet. A sticky surface is acceptable as long as spiked shoes are worn to walk on surface

KL6129/KL6129B

Epoxy Primer/Sealer

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- Slabs on grade should have a maximum moisture content of 3 lbs / 1,000 ft²/24 hours when measured by calcium chloride test

Atmospheric exposure conditions

- Ambient temperature during application and curing should be between 50 °F (10 °C) and 100 °F (38 °C)
- DONOTUSE Relative humidity should not exceed 90%

Substrate temperature

- DONOTUSE Below 50°F (10°C), and at least 5°F (3°C) above dew point

Notes:

- Storage conditions should be between 50°F (10°C) and 85°F (29°C)
- If during shipment, or for some other reason, this material is stored outside the specified storage range temporarily, the material must be brought into the specified range at least 24 hours prior to application

SYSTEM SPECIFICATION

- Topcoat: KL5000

INSTRUCTIONS FOR USE

- The surface to be coated must be properly prepared, dry, clean and free of contamination
- Track blast or acid etch and rinse well to neutralize
- Use a rotary wire brush, grinder or brush blast for walls
- A surface profile equivalent to 80 grit sandpaper is required
- Mix thoroughly before application

Induction time

None

Pot life

45 minutes at 77°F (25°C)

Application

Material temperature

Material temperature during application should be between 50°F (10°C) and 85°F (29°C)

KL6129/KL6129B

Epoxy Primer/Sealer

Airless spray

- Hoses should normally be kept as short as possible
- Equipment should be capable of maintaining a minimum of 1500 psi at the tip without surge

Recommended thinner

No thinner should be added

Nozzle orifice

Approx. .009" (0.23 mm) to 0.015 (0.38 mm)

Brush/roller

- A roller suitable for epoxy application must be used
- Use a high quality natural bristle brush and/or solvent resistant, 3/8" nap roller. Ensure brush/roller is well loaded to avoid air entrainment. Multiple coats may be necessary to achieve adequate film-build

Recommended thinner

No thinner should be added

Cleaning solvent

THINNER 21-06 (PPG HI-TEMP THINNER 11/AMERCOAT 65)

SAFETY PRECAUTIONS

- Although this is a solvent-free paint, care should be taken to avoid inhalation of spray mist, as well as contact between the wet paint and exposed skin or eyes
 - **WARNING!** If you scrape, sand, or remove old paint, you may release lead dust or fumes. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. In Canada, contact a regional Health Canada office. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.
-

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

KL6129/KL6129B

Epoxy Primer/Sealer

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgmc.com. The English text of this sheet shall prevail over any translation thereof.

AVAILABILITY

Packaging

1-quart, 1-gallon and 5-gallon kits

Product codes	Description
KL6129/04	Clear base for 1 quart kit
KL6129/01	Clear Base for 1 gallon kit
KL6129/05	Clear base for 5 gallon kit
KL6129B/08	Clear Hardener for 1 quart kit
KL6129B/12	Clear Hardener for 1 gallon kit
KL6129B/02	Clear Hardener for 5 gallon kit

The PPG Logo, Bringing innovation to the surface., and all other trademarks herein are property of the PPG group of companies.



PPG Protective & Marine Coatings

Bringing innovation to the surface.™