



DPLF

DPLF Epoxy Primer is an excellent corrosion-resistant primer and provides excellent adhesion to many types of properly prepared metal, fiberglass and aluminum substrates, as well as plastic fillers.

DPLF Epoxy Primer may also be used as a sealer and topcoated with most PPG Refinish products.

DPLF Epoxy Primers come in 3 colors:
DP48LF (White), DP50LF (Gray), and DP90LF (Black).



Features & Benefits

- Direct to metal
- Strong corrosion protection
- Excellent adhesion
- Primer / Sealer

Compatible Surfaces

DPLF may be applied over

- Properly cleaned and sanded, steel, galvanized steel, sand blasted steel and aluminum
- Properly cleaned and sanded gel coated fiberglass
- Properly cleaned (unsanded) E-Coat with DP401LF catalyst only
- Various cleaned and sanded rigid plastic*: ABS, Nylon, Polycarbonate, Noryl, PBT SMC, with DP401LF Catalyst only
- Properly cleaned and sanded OEM Finishes - for OE lacquer see ++Caution statement
- Cured and sanded refinish coatings
- DF Body Fillers
- SX Metal Treatments

NOTE: DPLF is direct to metal and MUST NOT be applied over etch or wash primers. Film build of 1.2-1.5 mils of DPLF is required or the surface must be treated with metal treatment/conditioner.

*Unprimed plastics require the use of a plastic adhesion promoter prior to the application of DPLF epoxy primer.

++**Caution** when DPLF is sprayed over lacquer substrates or basecoat that is not cross linked, allow to set overnight before applying another coat of primer or topcoat as lifting may occur. This can be avoided by applying the DPLF Epoxy Primer, color and clear coating the same day or by catalyzing the basecoat.

Required Products

Catalyst

DP401LF Epoxy Primer Catalyst
DP402LF Epoxy Primer Catalyst
Acetone*

*Optional

DPLF

Surface Preparation:



- Wash the area to be painted with soap and water, then clean with appropriate PPG cleaner.
- Sand the bare metal areas completely with 80-180 grit abrasive. Sand old finishes by hand or machine with 320-400 grit dry or 600 grit wet.
- Re-clean with appropriate PPG cleaner
- Chemical treatment or the use of a conversion coating will enhance the adhesion and performance properties of the finished system.
- Prime aluminum within 8 hours.

Prime carbon steel immediately after cleaning.

Mix Ratio:



DPLF	:	DPLF Catalyst	:	(optional) Acetone*
Epoxy Primer	:	DPLF Catalyst	:	Acetone*
2	:	1	:	½



Note: Thoroughly mix primer and catalyst (5 minutes mechanical agitation recommended).

Allow 30 minutes induction period to obtain maximum performance properties prior to use of DPLF/DP401LF.

No induction period is necessary when using DPLF/DP402LF

Do not blend DP401LF and DP402LF together



Pot Life: DPLF/DP401LF is 72 hours at 70°F (21°C)
DPLF/DP402LF is 8 hours at 70°F (21°C)

Note: In non-automotive applications where higher VOC primers are allowed, one half part of DT reducer may be added. This 2:1:½ blend ratio will result in a 4.90 VOC sealer.

*The use of acetone is optional, however when used, the minimum recommended film build must be maintained.

DPLF Epoxy Primer cannot be tinted.

DPLF Epoxy colors may be blended together.

Painting Flexible Parts:

DPLF Epoxy Primer may be used as a primer sealer on flexible parts over DELTRON® or ONECHOICE® Plastic Adhesion Promoters.



DPLF	:	DP401LF	:	Acetone*
Epoxy Primer	:	DP401LF	:	Acetone*
2	:	1	:	½

Note: Do not use DP402LF Fast Catalyst on flexible parts.



Apply 1 wet coat.

Recommended Dry Film build: .5-.75 mils

Reductions other than 2:1:½ or more than 1 coat will not result in a flexible coating.

Additives:



None

DPLF

Air Pressure and Spraygun Setup:



HVLP:	8-10 psi at the air cap
Compliant:	29-40 psi at the gun
Gun Setup:	1.3-1.6 mm or equivalent

Note: For best overall results, refer to spraygun manufacturer's recommendations for inlet air pressures.

Application:



	<u>DP401LF</u>	<u>DP402LF</u>
Apply:	1-2 wet coats	1-2 wet coats
Recommended Dry Film Build		
DPLF Epoxy Primer:	0.75-1.5 mils	0.75-1.5 mils
DPLF Epoxy Primer on Flexible parts:	0.5-0.75 mils	not recommended
DPLF Epoxy Primer with Acetone:	0.75-1.5 mils	0.75-1.5 mils

Drying Times:



	<u>DP401LF</u>	<u>DP402LF</u>
Between Coats: At 70°F (21°C)	10-15 minutes	10-15 minutes



Dry to topcoat: At 70°F (21°C)		
1 coat	60 minutes	30 minutes
2 coats	90 minutes	60 minutes
Flexibilized:	30 minutes	NA



To apply body filler: At 70°F (21°C)		
1 coat	60 minutes	60 minutes
2 coats	overnight dry	overnight dry

Note: DPLF Epoxy Primer may be recoated any time up to 1 week. After 1 week, it must be cleaned, sanded and re-cleaned. Reapply 1 additional coat of DPLF Epoxy Primer only if applying basecoat directly to DPLF

Compatible Topcoats:

DPLF Epoxy Primer may be topcoated with:
 DF Body Fillers
 DELTRON® NXT Basecoat
 Deltron 2000 (DBC) Basecoat
 Deltron primers, surfacers, and sealers
 OneChoice surfacers and sealers
 ENVIROBASE® High Performance Basecoat
 Envirobase High Performance primers, surfacers, and sealers

DPLF

Equipment Cleaning: Spray guns, gun cups, storage pots, etc., should be cleaned thoroughly after each use with any appropriate PPG general purpose solvent.

Technical Data:

DPLF Epoxy Primer	DPXXLF : DP401LF/DP402LF	DPXXLF : DP401LF/DP402LF : Acetone
Volume Ratio:	2 : 1	2 : 1 : ½
Applicable Use Category:	Primer Surfacer	Primer Surfacer
VOC Actual (g/L)	537-543	460-465
VOC Actual (lbs./ gal)	4.48-4.53	3.84-3.88
VOC Regulatory (less water, less exempt (g/L)	537-543	534-542
VOC Regulatory (less water, less exempt (lbs./ US gal.)	4.48-4.53	4.46-4.52
Density (g/L)	1198-1272	1140-1203
Density (lbs./ US gal)	10.00-10.61	9.51-10.04
Solids vol. %	35.8-36.9	30.6-31.6
Solids wt. %	55.2-57.3	49.7-51.9
Sq. ft. coverage / US gal. (1 mil. At 100% transfer efficiency)	572-592	490-507
DPLF Epoxy Primer (for flexible parts) Use DP401LF only	DPXXLF : DP401LF : DT Reducer	DPXXLF : DP401LF : Acetone
Volume Ratio (RTS):	2 : 1 : ½	2 : 1 : ½
Applicable Use Category:	Sealer Specialty	Sealer Specialty
VOC Actual (g/L)	460-587	460-465
VOC Actual (lbs./ gal)	3.84-4.90	3.84-3.88
VOC Regulatory (less water, less exempt (g/L)	536-587	536-542
VOC Regulatory (less water, less exempt (lbs./ US gal.)	4.47-4.90	4.47-4.52
Density (g/L)	1140-1269	1140-1190
Density (lbs./ US gal)	9.51-10.59	9.51-9.93
Solids vol. %	30.6-31.4	30.6-31.4
Solids wt. %	46.5-51.4	49.7-51.4
Sq. ft. coverage / US gal. (1 mil. At 100% transfer efficiency)	490-504	490-504

See Safety Data Sheet and Labels for additional safety information and handling instructions.

Important: The contents of this package must be blended with other components before the product can be used. Before opening the packages, be sure you understand the warning messages on the labels of all components since the mixture will have the hazards of all its parts. Improper spray technique may result in a hazardous condition. Follow spray equipment manufacturer's instructions to prevent personal injury or fire. Follow directions for respirator use. Wear eye and skin protection. Observe all applicable precautions.

EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION (412) 434-4515; IN CANADA (514) 645-1320


Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the public. Products mentioned may be hazardous and should only be used according to direction, while observing precautions and warning statements listed on label. Statements and methods described are based upon the best information and practices known to PPG Industries. Procedures for applications mentioned are suggestions only and are not to be construed as representations or warranties as to performance, results, or fitness for any intended use, nor does PPG Industries warrant freedom from patent infringement in the use of any formula or process set forth herein.

PPG Automotive Refinish
19699 Progress Drive
Strongsville, OH 44149
800.647.6050

PPG Canada Inc.
2301 Royal Windsor Drive, Unit #6
Mississauga, Ontario L5J 1K5
888.310.4762

Follow us online:

www.ppgrefinish.com



© 2024 PPG Industries, Inc. All rights reserved

The PPG Logo, Deltron, and Envirobase, are registered trademarks and We protect and beautify the world is a trademark of PPG Industries of Ohio, Inc.

Rev. 10/24