


44Y022 Water Reducible Epoxy Primer

Product description

44Y022 is a water reducible, chemically cured, two-component epoxy polyamide primer. 44Y022 is formulated to protect the structural interior of aircraft from corrosion.

- Corrosion inhibiting
- Compatible with epoxy and urethane interior topcoats
- Excellent adhesion to aluminum and composite surfaces
- Chemical and solvent resistant
- Resistant to immersion in hydraulic fluids, lubricating oils, phosphate ester based hydraulic fluids and distilled water

Components



Mix ratio (by volume):

- | | |
|--|--|
| • 44Y022 (base component) | 2 parts |
| • 44Y022CAT (catalyst component) | 1 part |
| • Reducer (Distilled or Deionized water) | 4.5 parts water by volume (approximately 150%) |

Specifications



44Y022 primer is qualified to the following material specifications:

- BMS 10-11 Type I Class A Grade E
- EMS 93283 Composition W

Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.

Product compatibility:

44Y022 primer is compatible with the following topcoat specifications:

- BMS 10-11 Type II
- CMS-CT-203 Type I Class 4
- BMS 10-60 Type I & II

Surface preparation and pretreatments



44Y022 primer can be applied over clean, dry, intact aluminum and composite surfaces. Aluminum surfaces shall be treated with materials conforming to MIL-DTL-5541 or equivalent.

Instructions for use

44Y022 Water Reducible Epoxy Primer



Mixing instructions:

Standard can kit (mixed in separate container):

Add the entire catalyst component to the base component. Add approximately 4.5 parts distilled or deionized water to the can containing the base and catalyst components. Secure the can lid and place on paint shaker in an inverted position for 10 – 15 minutes. **DO NOT SHAKE LONGER THAN 15 MINUTES.** Primer is now ready for use. Typical application viscosity should be 20 ± 2 seconds in a # 2 EZ Zahn Cup. Constant agitation is recommended. Add small amounts of water if necessary to achieve desired viscosity. A slight variation in the amount of water is normal.

Note: It is important to condition the paint for 24 hours prior to mixing by placing all materials in the shop or hangar, with ambient temperatures between 13° and 35°C (55° to 95°F). The minimum temperature of the paint components should be 13°C (55°F) prior to mixing.



Induction time:

Not Required



Viscosity: (23°C/73°F)

- #2 EZ Zahn cup 20 ± 2 seconds

Note: Viscosities quoted are the typical ranges obtained when using specified mix ratio.



Pot life:

4 hours @ 21 - 25°C (70 - 77°F)

Application guidelines

Recommended application conditions:

Temperature	15 - 30°C (59 - 86°F)
Relative Humidity	20 - 90%

Application:

Ground the aircraft and the application equipment before priming. Stir the primer slowly during the application. The suggested film thickness is 12.5 to 22.5 microns (0.5 to 0.9 mils). This can be accomplished with one medium coat with a 50% overlap.

These application guidelines represent PPG's best advice in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.




Theoretical coverage:

9.65 square meters/liter at 25 microns dry film (394 square feet/gallon at 1 mil dry film)

Recommended dry film thickness; 12.5 to 22.5 microns (0.5 to 0.9 mils)

44Y022 Water Reducible Epoxy Primer



Dry film density:

1.72 grams/cubic centimeter (14.35 pounds/gallon)

Dry film weight:

43.6 grams/square meter at 25 microns dry film (0.00892 pounds/square feet at 1 mil dry film)



Equipment:

44Y022 primer is compatible with all current forms of spray equipment.

Equipment type	Tip size	Pot pressure	Atomization pressure at the cap
*Electrostatic Air Spray Gun	1.2 mm or 1.5 mm	10 to 20 psi (0.69 to 1.4 bar)	45 to 60 psi (3.1 to 4.1 bar)
*Electrostatic Air Assisted Airless Spray Gun	#611 or #613 (Graco Nomenclature)	700 to 1200 psi (48 to 82 bar)	40 to 60 psi (2.8 to 4.1 bar)
High Volume Low Pressure Spray Gun (HVLP)	1.0 mm to 1.4 mm	10 to 20 psi (0.69 to 1.4 bar)	10 psi maximum (0.69 bar)
Conventional Air Spray Gun	1.2 mm to 1.8 mm	10 to 20 psi (0.69 to 1.4 bar)	45 to 60 psi (3.1 to 4.1 bar)

**Note: When spraying with electrostatic spray equipment, ensure that this is rated for use with water-borne coatings. Spraying water-borne coatings with regular electrostatic spray equipment can result in safety hazards.*

Equipment Cleaning:

Water will clean approximately 95% of liquid primer remaining on equipment. Follow with IS-248 Cleaning Solvent for Water Reducible Primer to remove any residual primer from equipment. Once material has cured, use an approved chemical paint removal system to strip primer from parts and equipment. Is with water.

Physical Properties (product)



Color: BAC 3661 yellow



Gloss: 10 G.U. maximum at 60°

44Y022 Water Reducible Epoxy Primer



Dry Times	21 - 27°C (70 - 80°F)
Dust Free	15 minutes maximum
Tack Free	2 hours maximum
Dry Through	4 hours maximum
Dry to Tape	4 hours minimum
Full Cure	7 days

Note: Dry times above were established at room (ambient) temperatures, 75° ± 5°F and 50% ± 10% relative humidity.

Forced Dry Schedule: For dry to stack conditions only. Allow a minimum of 15 minutes flash off time at ambient temperatures* prior to exposing painted parts to high temperatures. Complete testing should be done prior to use. Below are suggested starting points. Other variables may affect these cure schedules.

Temperature	Time
49°C (120°F)	90 minutes
60°C (140°F)	60 minutes
71°C (160°F)	40 minutes
82°C (180°F)	30 minutes

Note: Ambient temperatures are defined as 70° ± 10°F and 50% ± 10% Relative Humidity. For more information please refer to BAC 5736.



VOC:

Mixed, ready to use VOC (EPA method 24)	338 grams/liter
Base Component	335 grams/liter
Catalyst Component	344 grams/liter



Flash point closed cup:

Base Component	22°C (72°F)
Catalyst Component	31°C (87°F)

Shelf Life:

9 months from date of manufacture to most OEM specifications. Consult the specification you are procuring to verify shelf life requirements.

Note: Shelf life is provided for original, unopened containers.

44Y022 Water Reducible Epoxy Primer

Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

Note: When procuring to a qualified material specification, follow those storage instructions.

Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

Additional information can be found at: www.ppgaerospace.com

For sales and ordering information call the local PPG office at the numbers listed below:

Asia Pacific

ASC – Australia
Tel 61 (3) 9335 1557
Fax 61 (3) 9335 3490

ASC – Japan
Tel 81 561 35 5200
Fax 81 561 35 5201

ASC – South East Asia
Tel 65 6861 1119
Fax 65 6861 6162

ASC – Suzhou
Tel (86-512) 6661 5858
Fax (86-512) 6661 6868

ASC – Tianjin
Tel (86-022) 2482 8625
Fax (86-022) 2482 8600

Americas

1 (818) 362-6711 or 1-800-AEROMIX

Europe and Middle East

ASC – Central Europe
Tel 49 (40) 742 193 10
Fax 49 (40) 742 139 69

ASC – Middle East & India
Tel (971) 4 883 9666
Fax (971) 4 883 9665

ASC – North Europe
Tel 44 (0) 1388 770222
Fax 44 (0) 1388 770288

ASC – South Europe
Tel 33 (0) 235 53 43 71
Fax 33 (0) 235 53 54 44

44Y022 Water Reducible Epoxy Primer

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PRC-DeSoto International, Inc.
12780 San Fernando Road
Sylmar, CA 91342
www.ppgaerospace.com

Issue Date: 9/24
Lit: