

# SIGMASHIELD™ 880 GF / AMERLOCK™ 880 GF

## DESCRIPTION

Two-component, surface tolerant, high-solids, glass flake epoxy coating

## PRINCIPAL CHARACTERISTICS

- Primarily designed for use in offshore splash zone maintenance
- Designed for use in heavy-duty and corrosive environments
- Outstanding sea water resistance
- Excellent corrosion resistance
- Enhanced impact and abrasion resistance
- Continues to cure when immersed in water
- Long-term protection in a single-coat application
- Resistant to well designed cathodic protection
- Suitable for application on exterior of buried pipes
- Suitable on wet blast or ultra high pressure water (UHPWW) cleaned substrates (damp or dry)

## COLOR AND GLOSS LEVEL

- Yellow, black (other colors available on request)
- Gloss

Note:

- Epoxy coatings will characteristically chalk and fade upon exposure to sunlight. Light colors are prone to ambering to some extent in interior or exterior exposures.

## BASIC DATA AT 20°C (68°F)

| Data for mixed product         |   |
|--------------------------------|---|
| Number of components           | Two   |
| Mass density                   | 1.5 kg/l (12.1 lb/US gal)   |
| Volume solids                  | 85 ± 2%   |
| VOC (Supplied)                 | Directive 2010/75/EC, SED: max. 122.0 g/kg<br>UK PG 6/23(92) Appendix 3: max. 207.0 g/l (approx. 1.7 lb/US gal)<br>EPA Method 24: 200.0 g/ltr (1.7 lb/US gal) |
| Recommended dry film thickness | 150 - 1000 µm (6.0 - 40.0 mils) depending on system   |
| Theoretical spreading rate     | 4.3 m <sup>2</sup> /l for 200 µm (170 ft <sup>2</sup> /US gal for 8.0 mils)   |
| Dry to touch                   | 3 hours   |
| Overcoating Interval           | Minimum: 3.5 hours<br>Maximum: 14 days  |
| Shelf life                     | Base: at least 24 months when stored cool and dry<br>Hardener: at least 24 months when stored cool and dry  |

Notes:

# SIGMASHIELD™ 880 GF / AMERLOCK™ 880 GF

- See ADDITIONAL DATA – Spreading rate and film thickness
  - See ADDITIONAL DATA – Overcoating intervals
  - See ADDITIONAL DATA – Curing time
- 

## RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

### Substrate conditions

- Coating performance will depend upon the surface preparation degree
- For atmospheric service, abrasive blast to ISO Sa2½ or minimum SSPC SP6, power tool cleaned to ISO St3 (SSPC SP3) or hand tool cleaned to ISO St2 (SSPC SP2) or ultra high pressure water jet to SSPC SP WJ-2(L) / NACE WJ-2(L)
- For immersion service: steel; blast cleaned to ISO Sa2½ (SSPC SP10), blasting profile 40 – 75 µm (1.6 – 3.0 mils)
- Higher profiles (>75 µm, 3.0 mils) is allowable with appropriate coating thickness
- Compatible previous coat must be dry and free from any contamination

Note:

- Coating performance is, in general, proportional to the degree of surface preparation
- 

### Substrate temperature and application conditions

- Substrate temperature during application should be at least 3°C (5°F) above dew point
- 

## INSTRUCTIONS FOR USE

### Mixing ratio by volume: base to hardener 3:1

- Thinner should be added after mixing the components
  - Do not thin more than is required by appropriate application property
  - Adding too much thinner results in reduced sag resistance and slower cure
- 

### Induction time

0 minute

Note:

- No induction time required
- 

### Pot life

2 hours at 20°C (68°F)

Note:

- See ADDITIONAL DATA – Pot life
-

# SIGMASHIELD™ 880 GF / AMERLOCK™ 880 GF

## **Air spray**

### **Recommended thinner**

THINNER 91-92

### **Volume of thinner**

4 - 8%, depending on required thickness and application conditions

### **Nozzle orifice**

1.5 - 3.0 mm (approx. 0.060 - 0.110 in)

### **Nozzle pressure**

0.2 - 0.4 MPa (approx. 2 - 4 bar; 29 - 58 p.s.i.)

---

## **Airless spray**

### **Recommended thinner**

THINNER 91-92

### **Volume of thinner**

0 - 8%, depending on required thickness and application conditions

### **Nozzle orifice**

Approx. 0.53 - 0.69 mm (0.021 - 0.027 in)

### **Nozzle pressure**

15.0 MPa (approx. 150 bar; 2176 p.s.i.)

---

## **Brush/roller**

### **Recommended thinner**

THINNER 91-92

### **Volume of thinner**

0 - 5%

---

## **Cleaning solvent**

- THINNER 90-53
-

# SIGMASHIELD™ 880 GF / AMERLOCK™ 880 GF

## ADDITIONAL DATA

| Spreading rate and film thickness |   |
|-----------------------------------|---|
| DFT                               | Theoretical spreading rate                          |
| 200 µm (8.0 mils)                 | 4.3 m <sup>2</sup> /l (170 ft <sup>2</sup> /US gal) |
| 500 µm (20.0 mils)                | 1.7 m <sup>2</sup> /l (68 ft <sup>2</sup> /US gal)  |

| Overcoating interval for DFT up to 500 µm (20.0 mils) |          |                |               |                |                |                |                 |
|---|----------|----------------|---------------|----------------|----------------|----------------|-----------------|
| Overcoating with...                                   | Interval | -5°C<br>(23°F) | 5°C<br>(41°F) | 10°C<br>(50°F) | 20°C<br>(68°F) | 30°C<br>(86°F) | 40°C<br>(104°F) |
| itself  | Minimum  | 36 hours       | 14 hours      | 7 hours        | 3.5 hours      | 2 hours        | 1.5 hours       |
|   | Maximum  | 2 months       | 1.5 months    | 1 month        | 28 days        | 21 days        | 14 days         |
| epoxy coatings  | Minimum  | 36 hours       | 14 hours      | 7 hours        | 3.5 hours      | 2 hours        | 1.5 hours       |
|   | Maximum  | 1 month        | 28 days       | 21 days        | 14 days        | 7 days         | 4 days          |
| polyurethanes   | Minimum  | 48 hours       | 22 hours      | 14 hours       | 10 hours       | 6 hours        | 4 hours         |
|   | Maximum  | 1 month        | 28 days       | 21 days        | 14 days        | 7 days         | 4 days          |

Note:

- Surface should be dry and free from any contamination

# SIGMASHIELD™ 880 GF / AMERLOCK™ 880 GF

| Curing time for DFT up to 500 µm (20.0 mils) |              |               |           |
|--|--------------|---------------|-----------|
| Substrate temperature                        | Dry to touch | Dry to handle | Full cure |
| -5°C (23°F)                                  | 24 hours     | 48 hours      | 30 days   |
| 5°C (41°F)                                   | 10 hours     | 24 hours      | 18 days   |
| 10°C (50°F)                                  | 5 hours      | 16 hours      | 14 days   |
| 20°C (68°F)                                  | 3 hours      | 8 hours       | 7 days    |
| 30°C (86°F)                                  | 2 hours      | 5 hours       | 5 days    |
| 40°C (104°F)                                 | 1 hour       | 3 hours       | 3 days    |

Notes:

- The curing time is related to the DFT of the paint and ventilation of the drying condition. High DFT and poor ventilation will slow curing
- When total DFT is higher than 1500 µm (60.0 mils), curing times have to be 2 - 2.5 times in order to obtain sufficient mechanical strength
- Premature exposure to water will lead to whitening of dark colours when applied between tides on jetties, piling etc. This will not affect anticorrosive properties of the coating.
- Adequate ventilation must be maintained during application and curing

| Pot life (at application viscosity) |          |
|-------------------------------------|----------|
| Mixed product temperature           | Pot life |
| 10°C (50°F)                         | 3 hours  |
| 20°C (68°F)                         | 2 hours  |
| 30°C (86°F)                         | 1 hour   |

**Product Qualifications**

- Qualified for NORSOK M501 Rev.6 System 7A with 2 coating system

**SAFETY PRECAUTIONS**

- See Safety Data Sheet and product label for complete safety and precaution requirements
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

**WORLDWIDE AVAILABILITY**

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.



# SIGMASHIELD™ 880 GF / AMERLOCK™ 880 GF

## REFERENCES

- Information sheet | Explanation of product data sheets

## WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

## LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at [www.ppgpmc.com](http://www.ppgpmc.com). The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

