

# PPG SL60 Joint Sealant

## DESCRIPTION

Two-component, 100% solids, self-leveling, flexible modified polyurea control joint sealant

## PRINCIPAL CHARACTERISTICS

- 100% solids
- Rapid cure and return-to-service
- Remains flexible at lower temperatures
- Cures at temperatures from -20°F (-29°C) to 130°F (54°C)
- Resists jet fuel
- Designed for 25% movement of an installed joint width
- TYPICAL USES:
- Suitable for interior and exterior control joints and cracks in horizontal concrete surfaces
- Not recommended for use in non-breathing, resilient or polymer flooring systems
- Not suitable for slopes greater than 15%

Note: Information Sheet available with test and certification data

## COLOR AND GLOSS LEVEL

- Light Gray, Concrete Gray, Ryno Gray, Dark Gray, Signal Grey, Black, Tile Red
- Semi-gloss

Note: Color changes can occur under UV-exposure without negative impact on the product performance

## BASIC DATA AT 70°F (21°C)

Data for mixed product	
Number of components	Two
Volume solids	100%
VOC (Supplied)	EPA Method 24: 0.0 lb/US gal (0.0 g/l)
Dry to touch	4.5 minutes
Curing time	30 minutes

### Notes:

- Curing time reflects ready for service time
- Cure times will be longer at lower temperatures
- Product will cure at sub-freezing temperatures; however, frozen concrete substrates with high moisture content will affect material adhesion and long term performance.
- See ADDITIONAL DRYING/CURING DETAILS for gel time and tack-free time
- The shelf life for the unmixed components (Part A and Part B) for this product is 12 months at 70°F (21°C).
- Store cartridges in an upright position.
- Refer to Application Guide for additional information



# PPG SL60 Joint Sealant

## RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- All surfaces must be sound, dry, clean, free of oil, grease, dirt, mildew, curing compounds, loose and flaking paint, and other foreign substances
- Prepare joint in a manner that takes both joint walls back to bare concrete, removing all saw laitance, cure compounds, sealers, debris, etc.
- Prepare joint using a vacuum-equipped saw that will reach the base of the saw-cut joint or to a depth of 2 inch (5.1 cm) in the case of through-slab construction joints
- Joints should be ground to remove dirt and surface laitance using a grinder with a diamond or carbide blade
- Joints may be cleaned using either two cleaning passes (one along each side of the joint) or a single cleaning pass using a blade that is slightly wider than the joint to be cleaned
- Where joints have minor edge chips or spalls, areas may be squared off or filled along with the joint itself or repaired using PPG Quick Mender® Concrete Repair
- Compressible backer rod is prohibited in saw-cut joints unless 2 inch (5.1 cm) depth is exceeded. Saw cut joints should be filled full-depth

---

## Substrate temperature and application conditions

- The substrate temperature must be at least 5°F (3°C) above dew point
- Moisture content should not exceed 5%

### Notes:

- Joints must be completely dry. Moisture can cause bubbles to form in the products and adhesion may be reduced
- Refrigerated and freezer areas should be held at operating temperatures for 7-14 days, if possible, prior to installation

---

## INSTRUCTIONS FOR USE

### Mixing ratio by volume: Part A to Part B 1:1

- Prior to use, the temperature of Part A and Part B should be at least (70°F) 21°C
- For products provided in pails: Pre-mix Part B components thoroughly to redistribute any settlement that may have occurred
- For products provided in cartridges: Shake cartridge sets vigorously for several minutes to ensure homogenous distribution of base components
- For recommended application instructions, see working procedure

---

### Application

- Defer installation for as long as possible after slab placement. For best adhesion, the product should be installed no earlier than 28 days after slab placement
- For products provided in pails: Apply using plural component pump and static mixing wand
- For products provided in cartridges: Use Cartridge Dispensing Guns

### Recommended thinner

No thinner should be added

---

# PPG SL60 Joint Sealant

## Cleaning procedures

- Use disposable plastic tools and buckets wherever possible. Cured material may be stripped or peeled from plastic tools and containers
- Steel mixers or other metal tools are more difficult to clean. They may need to be soaked in a solvent such as MEK to soften and peel cured material

## ADDITIONAL DATA

Physical data of cured material	
Characteristic	Value
Tensile Strength (ASTM D638)	1,164 psi (8.0 MPa)
Tensile Elongation (ASTM D638)	748%
Tear Strength (Die C, ASTM D624)	219 pli
100% Modulus (ASTM D412/D638)	329 psi (2.3 MPa)
200% Modulus (ASTM D412/D638)	486 psi (3.35 MPa)
300% Modulus (ASTM D412/D638)	602 psi (4.15 MPa)
Hardness, Shore A (ASTM D2240)	65

Additional drying/curing details	
Characteristic	Value
Gel time at 70°F (21°C)	1 minute
Tack free time at 70°F (21°C)	4.5 minutes
Open to Foot Traffic at 70°F (21°C)	30 minutes

## Product Qualifications

- Compliant with USDA Incidental Food Contact Requirements
- CFIA approved

## DISCLAIMER

- This product is specifically suitable for use on the substrates mentioned in this document. For application on any other substrates, please always contact your distributor for specific instructions and in order to make sure that the product performance can be safeguarded.
- For industrial or professional use only

## SAFETY PRECAUTIONS

- Read all label and Safety Data Sheet (SDS) information prior to use



# PPG SL60 Joint Sealant

## WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

## WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

## LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at [www.ppgmc.com](http://www.ppgmc.com). The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

