

PPG AQUATAFLEX® 506 Hybrid Coating

DESCRIPTION

100% solids epoxy/polyurethane/polyurea hybrid coating designed for fast curing and high chemical resistance

PRINCIPAL CHARACTERISTICS

- USDA BioPreferred® certified bio-based product
- Meets NSF/ANSI Standard 61 for potable water tanks and pipes
- Excellent chemical resistance
- USDA/FSIS acceptable
- Surface tolerant and hydrophobic
- TYPICAL USES:
- Wastewater structures, buried pipelines, tanks and other corrosive environments
- Potable water tanks, reservoirs, basins and pipes
- Primary or secondary containment applications

Notes:

- Information Sheet available with test and certification data
- In regions outside of the US and Canada, this product may be sold as PPG NOVGUARD® 1506 hybrid coating

COLOR AND GLOSS LEVEL

- Blue, Tan
- Semi-gloss

Notes:

- Color changes can occur under UV-exposure without negative impact on the product performance
- Listed colors are standard available colors for finished product.

BASIC DATA AT 72°F (22°C)

Data for mixed product	
Number of components	Two
Mass density	8.9 lb/US gal (1.1 kg/l)
Volume solids	100 ± 2%
VOC (Supplied)	EPA Method 24: 0.0 lb/US gal (2.9 g/l)
Recommended dry film thickness	20.0 - 300.0 mils (500 - 7620 µm) per coat
Theoretical spreading rate	81 ft ² /US gal for 20.0 mils (2.0 m ² /l for 508 µm) 5 ft ² /US gal for 300.0 mils (0.1 m ² /l for 7620 µm)
Dry to touch	20 seconds
Overcoating Interval	Maximum: Not applicable Maximum: 8 hours
Curing time	24 hours



PPG AQUATAFLEX® 506 Hybrid Coating

Data for mixed product

Full cure after	14 days
-----------------	---------

Notes:

- Curing time reflects ready for service time
- The shelf life for the unmixed components (Part A and Part B) for this product is 6 months at 70°F (21°C).
- Material should be stored in dry conditions, out of direct sunlight, and in unopened original factory containers, at temperatures above 60°F (16°C) and below 95°F (35°C).
- If overcoat time is exceeded, abrade and clean surface before recoating
- See ADDITIONAL DATA – Spreading rate and film thickness

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Steel (Immersion Service)

- Remove all surface contaminants, oil and grease in accordance with SSPC SP-1
- Abrasive blast with an angular abrasive to an SSPC SP-10 cleanliness or higher. Achieve a surface profile of 3.0 – 5.0 mils (75 – 125 µm)
- Ensure surface is dust free after blasting

Steel (Non-Immersion Service)

- Remove all surface contaminants, oil and grease in accordance with SSPC SP-1
- Abrasive blast with an angular abrasive to an SSPC SP-6 or higher. Achieve a surface profile of 2.5 – 4.0 mils (65 – 100 µm)
- Ensure surface is dust free after blasting

Concrete / Masonry

- All surfaces must be sound, dry, clean, free of oil, grease, dirt, mildew, curing compounds, loose and flaking paint, and other foreign substances
- Abrade surface to achieve a surface profile equivalent to CSP 3 to CSP 5 in accordance with ICRI 310.2R-2013
- New concrete must cure a minimum of 28 days prior to application of this product
- Prepare in accordance with SSPC SP-13 guidelines
- Concrete pH must be 7.0 or higher

Ductile Iron

- All oils, small deposits of asphalt, paint, and grease shall be removed by solvent cleaning per NAPF 500-03-01
- Abrasive blast in accordance with NAPF 500-03-04

Substrate temperature and application conditions

- Substrate temperature during application should be between 40°F (4°C) and 140°F (60°C)
- Relative humidity should not exceed 90%



PPG AQUATAFLEX® 506 Hybrid Coating

SYSTEM SPECIFICATION

- Primer for concrete: PPG RAVEN® 175 Primer, PPG RAVEN® 171FS Primer, PPG VF20 Primer
- Primer for Carbon Steel: PPG AQUATAPOXY® 190 Primer*
- Primer for non-ferrous metals: PPG AQUATAPOXY® 190 Primer*
- Tie-Coat: PPG RAVEN® 161 Primer

Note: *Do not use this primer if immersion temperatures will exceed 140°F (60°C)

INSTRUCTIONS FOR USE

Mixing ratio by volume: Part A to Part B 50:50 (1:1)

- Material requires heated plural component airless spray set-up
- Part A does not require pre-mixing.
- Part B component must be thoroughly mixed prior to use.
- Mix Part B using three-tier, collapsible blade power mixer through the center bung hole
- Mixer diameter should be 1/3 of the diameter of the container
- Mix for at least 30 minutes prior to processing
- Properly mixed material will be a uniform color without light or dark spots

Airless spray: Plural component

- Material and equipment temperatures must be kept at 70°F (21°C) or above
- A drum mixer is required for Part B component
- Equipment capable of maintaining a minimum of 2500 psi at the tip without surge and 160°F (71°C)
- Heated hoses are required
- Recirculation is required for both components

Recommended thinner

No thinner should be added

Nozzle orifice

Approx. 0.031 – 0.035 in (0.78 – 0.89 mm)

Note: Prior to spraying, drums need to be pre-heated to a minimum of: Part A 70°F (21°C); Part B 120°F (49°C)

Cleaning solvent

MEK, acetone or xylene

PPG AQUATAFLEX® 506 Hybrid Coating

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
20.0 mils (508 µm)	81 ft ² /US gal (2.0 m ² /l)
40.0 mils (1016 µm)	40 ft ² /US gal (1.0 m ² /l)
60.0 mils (1524 µm)	27 ft ² /US gal (0.7 m ² /l)
80.0 mils (2032 µm)	20 ft ² /US gal (0.5 m ² /l)
100.0 mils (2540 µm)	16 ft ² /US gal (0.4 m ² /l)
125.0 mils (3175 µm)	13 ft ² /US gal (0.3 m ² /l)
300.0 mils (7620 µm)	5 ft ² /US gal (0.1 m ² /l)

Physical data of cured material	
Characteristic	Value
Tensile Strength (ASTM D638)	2,110 psi (14.5 MPa)
Tensile Elongation (ASTM D638)	>70%
Hardness, Shore A (ASTM D2240)	95
Hardness, Shore D (ASTM D2240)	50
Moisture Vapor Transmission (ASTM D1653)	25 g/m ²
Adhesion to Steel (ASTM D4541)	>1,500 psi (>10.3 MPa)
Taber Abrasion (ASTM D4060, CS-17 Wheel, 1 kg load, 1,000 cycles)	44 mg loss
Tear Strength (Die C, ASTM D624)	158 pli
Pickle Jar (Greenbook 211-2)	Pass
SWAT - Severe Wastewater Analysis Test (ASTM G210)	Pass
Water Absorption (ASTM D570)	0.17%
Shrinkage	0.4%

Note: The value ranges stated in this Technical Data Sheet are based on system processing under laboratory conditions. Equipment configurations and/or field application conditions may produce variances in final system values.

DISCLAIMER

- PPG Protective & Marine Coatings does not accept any responsibility or liability for any odor, taste or contamination imparted to the drinking water from the coatings or products retained in the coating
- For industrial or professional use only
- This product is specifically suitable for use on the substrates mentioned in this document. For application on any other substrates, please always contact your distributor for specific instructions and in order to make sure that the product performance can be safeguarded.



PPG AQUATAFLEX® 506 Hybrid Coating

SAFETY PRECAUTIONS

- Although this is a solvent-free paint, care should be taken to avoid inhalation of spray mist, as well as contact between the wet paint and exposed skin or eyes
- Read all label and Safety Data Sheet (SDS) information prior to use

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

• SAFETY INDICATIONS	INFORMATION SHEET	1430
• PRODUCT PERFORMANCE TEST RESULT SUMMARY SHEET		
• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• CONVERSION TABLES	INFORMATION SHEET	1410

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

