

PPG NOVAGUARD® 5090 Epoxy Filler

formerly known as Milamar ICO GEL Epoxy Filler

DESCRIPTION

Three-component, 100% solids, epoxy patching material primarily designed for horizontal, vertical and overhead applications

PRINCIPAL CHARACTERISTICS

- 100% solids
- Can fill holes up to 1" (2.5 cm) thick on vertical or overhead surfaces without shrinkage or sagging
- Bonds to dry and damp concrete
- Self priming on concrete and steel
- TYPICAL USES:
 - Filler for bug holes and surface cracks in concrete
 - To fill bug holes, crevices and cracks on vertical walls and floors, vertical stair repairs and concrete columns
 - Pit filler / seam sealer for steel
 - Repair of badly eroded manholes, sumps and sewers
 - Particularly suited for vertical and overhead repairs where constant dampness is present

COLOR AND GLOSS LEVEL

- Neutral
- White
- Concrete gray

BASIC DATA AT 77°F (25°C)

Data for mixed product	
Number of components	Three
Mass density	9.3 lb/US gal (1.1 kg/l)
Volume solids	100 ± 2%
VOC (Supplied)	EPA Method 24: 0.0 lb/US gal (3.5 g/l)
Theoretical spreading rate	40 ft ² /US gal for 125.0 mils (1.0 m ² /l for 3125 µm)
Dry to touch	50 minutes
Overcoating Interval	Minimum: 6 hours Maximum: 18 hours
Curing time	18 hours
Full cure after	7 days
Shelf life	Part A: at least 12 months when stored cool and dry Part B: at least 12 months when stored cool and dry Part C: at least 12 months when stored cool and dry

Notes:

PPG NOVAGUARD® 5090 Epoxy Filler

formerly known as Milamar ICO GEL Epoxy Filler

- Curing time reflects ready for service time
- If overcoat time is exceeded, abrade and clean surface before recoating
- Listed data for mixed product using standard hardener.

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Concrete

- All surfaces must be sound, clean, free of oil, grease, dirt, mildew, curing compounds, loose and flaking paint, and other foreign substances
- New concrete must cure a minimum of 28 days prior to application
- Prepare in accordance with SSPC SP-13 guidelines

Steel

- Abrasive blast with an angular abrasive to an SSPC SP-10 cleanliness or higher. Achieve a surface profile of 4.0 mils (100 µm)

INSTRUCTIONS FOR USE

Mix as packaged

- Mix Part A and Part B together using a paint paddle or low speed drill mixer for 1 minute
- Add the Part C aggregate slowly and mix for another minute
- Properly mixed material will be a uniform color without light or dark spots
- For recommended application instructions, see working procedure

Notes:

- Use of Part C is optional, add as required to achieve consistency for desired applications
- Part C not required when used as a pit filler/seam sealer on steel
- When adding Part C to mixed Part A and Part B, ratio is 0.6:1 by volume (1.5:1 by weight)

Application

- Can be applied on vertical surfaces up to 1" (2.5 cm) thick
- Use a clean margin trowel or spatula
- Press the product firmly into place in a wiping motion. Use enough material to overfill the opening
- Can be applied up to 1" (2.5 cm) depths without sagging

Note:

- For application thickness between 1 in. (2.5 cm) and 3 in. (7.6 cm) per coat, standard Part C fill material can be replaced with the XT Part C fill material.

PPG NOVAGUARD® 5090 Epoxy Filler

formerly known as Milamar ICO GEL Epoxy Filler

Pot life

40 minutes at 77°F (25°C)

Note:

- Listed data is for product with standard hardener.

ADDITIONAL DATA

Working time for product with standard hardener

- 65 minutes at 50°F (10°C)
- 50 minutes at 77°F (25°C)
- 40 minutes at 90°F (32°C)

Working time for product with medium cure (MC) hardener

- 50 minutes at 50°F (10°C)
- 40 minutes at 77°F (25°C)
- 35 minutes at 90°F (32°C)

Working time for product with fast cure (FC) hardener

- 40 minutes at 50°F (10°C)
- 35 minutes at 77°F (25°C)
- 25 minutes at 90°F (32°C)

Maximum Recoat Time (without sanding) at 77°F (25°C)

- Standard hardener: 18 hours
- Medium cure (MC) hardener: 10 hours
- Fast cure (FC) hardener: 6 hours

Physical data of cured material	
Characteristic	Value
Tensile Strength (ASTM C307)	1,810 psi (12.5 MPa)
Tensile Elongation (ASTM D638)	10%
Compressive Strength (ASTM D695)	6,170 psi (45 MPa)
Bond Strength (ASTM C482)	>1000 psi (>6.9 MPa)
Hardness, Shore D (ASTM D2240)	80
Water Absorption (ASTM C413)	0.3%

Note:

- The value ranges stated in this Product Data Sheet are based on system processing under laboratory conditions. Equipment configurations and/or field application conditions may produce variances in final system values.

PPG NOVAGUARD® 5090 Epoxy Filler

formerly known as Milamar ICO GEL Epoxy Filler

Drying time with standard hardener

Substrate temperature	Dry to service
50°F (10°C)	72 hours
77°F (25°C)	18 hours
90°F (32°C)	10 hours

Drying time with medium cure (MC) hardener

Substrate temperature	Dry to service
50°F (10°C)	48 hours
77°F (25°C)	10 hours
90°F (32°C)	7 hours

Drying time with fast cure (FC) hardener

Substrate temperature	Dry to service
50°F (10°C)	20 hours
77°F (25°C)	8 hours
90°F (32°C)	4 hours

Pot life for product with standard hardener

Mixed product temperature	Pot life
50°F (10°C)	45 minutes
77°F (25°C)	40 minutes
90°F (32°C)	15 minutes

Pot life for product with medium cure (MC) hardener

Mixed product temperature	Pot life
50°F (10°C)	45 minutes
77°F (25°C)	30 minutes
90°F (32°C)	10 minutes

PPG NOVAGUARD® 5090 Epoxy Filler

formerly known as Milamar ICO GEL Epoxy Filler

Pot life for product with fast cure (FC) hardener	
Mixed product temperature	Pot life
50°F (10°C)	10 minutes
77°F (25°C)	8 minutes
90°F (32°C)	5 minutes

DISCLAIMER

- PPG Protective & Marine Coatings does not accept any responsibility or liability for any odor, taste or contamination imparted to the drinking water from the coatings or products retained in the coating

SAFETY PRECAUTIONS

- Read all label and Safety Data Sheet (SDS) information prior to use

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

- Information sheet | Explanation of product data sheets
- Guide | PPG NOVAGUARD 5090 | Application guidelines

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.