

VB-14

## STARFIRE™

VM4206 Red VM4207 Blue

# VM4210 Green II VM4212 Yellow II

STARFIRE<sup>™</sup> toners are special colored aluminum pigments that are part of the VIBRANCE COLLECTION<sup>®</sup> which may be used with DELTRON<sup>®</sup> DBC 2000 and DELTRON<sup>®</sup> NXT Basecoats to enhance the basecoat color capability.

These pigments may also be used in DBC500 color blender and VWM500 Custom Midcoat, or sprayed alone to produce custom special effect colored groundcoats and midcoats.

For procedures relating to custom and/or restoration work refer to PPG's Custom Restoration Guide available at ppgrefinish.com under Training.



### **Compatible Products and Systems**

Starfire toners are used in conjunction with the systems shown below:

- DELTRON<sup>®</sup> DBC 2000 Refinish System Follow P-175 *Deltron* DBC recommendation for proper preparation and compatible primers.
- DELTRON<sup>®</sup> NXT Refinish System Follow P-251 *Deltron* NXT recommendation for proper preparation and compatible primers.
- DBC500 Color Blender Follow P-176 *Deltron* DBC500 recommendations for proper preparation and compatible primers.
- VWM500 Vibrance Collection Custom Midcoat Follow VB-22 recommendations for proper preparation and use.

Note: Custom or exotic finishes are excluded from coverage under the PPG Paint Performance Guarantee.

### **Surface Preparation**

•	When working on custom finishes close attention to details outlined for standard
	because proparation canding and cleaning is preded to achieve the optimum results

- basecoat preparation, sanding, and cleaning is needed to achieve the optimum results.
  Starfire colors are designed to be applied over properly cleaned, sanded, and primed surfaces.
- T
- For use over ENVIROBASE<sup>®</sup> High Performance EHP, use VWM500 Custom Midcoat (VB-22)

# **VB-14**

## VM42xx

### **Reducing:**

VIVI 12/00				
<b>Mixing Ratio:</b> (adding VM42xx to a basecoat color or blender)		For a custom formulation you may add a maximum of 10% <i>Starfire</i> pigment to un-reduced color or 5% to ready-to-spray mix of DBC, BC, DBC500 and D895 or up to 14% to unreduced of VWM500.		
Reducing:			color or blender already containing VM42xx	
(basecoat color or		For detailed <i>Deltron</i> DBC 2000 reduction specifics see data sheet P-175**		
blender already	: +	For detailed Global Refinish System BC reduction specifics see data sheet EU02**		
containing VM42xx)		For detailed DBC500 re	duction specifics see data sheet P176**	
		For detailed D895 redu	ction specifics see data sheet EU113**	
		For detailed VWM500 r	eduction specifics see data sheet VB-22	
		**DX57 or D888 activator <b>must</b> be used in DBC or BC colors containing VM42xx or DBC, DBC500, BC or D895 colors containing <i>Starfire</i> color. When using <i>Starfire</i> basecoat colors, DX57 or D888 activator <b>must</b> be used in both the ground coat and mid-coat colors.		
		Pot Life:	See specific product data sheet listed above	
	S.M.	Using activated materia (especially on multiple o	l beyond 1 hour may result in wrinkling or other product failures colors).	
Additives:	A B	See specific product data sheet listed above		
Air Pressure		HVLP:	8 - 10 psi at the air cap	
And Gun Setup:		Compliant:	29 - 40 psi at the gun	
	<b>&gt;</b> 1	Gun Setup:	1.1 - 1.5 mm or equivalent	
		Refer to spraygun manufacturer's recommendations for inlet air pressures.		
Application:		Apply:	Sufficient number of coats to achieve desired effect.	
			Spraying a test panel is recommended to determine desired effect.	
Drying Times	<u>}</u>	Between Coats:	See specific product data sheet listed above	
		Air Dry: Tape Time:	See specific product data sheet listed above	
		Dry to Clearcoat:	See specific product data sheet listed above 24 hour maximum to clear coat	
		approval difficult to see	are designed to dry low in gloss. This makes color match and its e until the clearcoat is applied. <b>A good technique is to spray the</b> <b>on a small test panel before spraying the job.</b>	
		basecoat color applied.		
Tri-Coat Mixing			oat applications, 5% DX57 Basecoat Activator (DBC) or D888 Basecoat e added to the reduced basecoat prior to spraying in <b>BOTH</b> the ground	
		<i>Starfire</i> toner can be bl	ended as a mid-coat color with DBC500 Color Blender (DBC), VWM500	

*starfire* toner can be blended as a mid-coat color with DBC500 Color Blender (DBC), VWM500 Custom Midcoat, or D895 Color Blender (BC). In doing so you can achieve more transparency, when combined with varying ground coat colors and create different degrees of custom effects. DBC500. VWM500, or D895 can be used in any quantity necessary to achieve the desired effect.

Striping or Two Toning	Tape Times:			
	Tape time of DBC and NXT is 30 - 60 minutes at 70°F (21°C) and 50% relative humidity.			
	Tape time of VWM500 is 45 - 60 minutes (additional coats may require longer dry time).			
	All striping, two toning must be completed within 24 hours. If allowed to dry for more than			
	24 hours, it must be sanded and reapplied.			
	When applying DBC or NXT basecoats, 5% DX57 Basecoat Activator ${\sf must}$ be added to the			
	reduced basecoat prior to spraying in <b>BOTH</b> the ground coat and mid coat.			
Clearcoating:	Clearcoat Starfire colors with any Vibrance Collection clearcoat or any clear recommended			
	for <i>Deltron</i> DBC 2000 (P-175), <i>Deltron</i> NXT (P-251), or <i>Envirobase</i> High Performance EHP (see			
	EB-143 for complete listing)			
Equipment Cleaning:	Spray guns, gun cups, storage pots, etc., should be cleaned thoroughly after each use with			
	any appropriate PPG general purpose solvent.			

Technical Data	DBC	<u>NXT</u>	<u>DBC500</u>
Package VOC Actual	4.86 - 6.16 lbs./gal	5.91 - 6.42 lbs./gal	5.20 - 5.62 lbs./gal
	(582 - 738 g/L)	(708 - 769 g/L)	(623 - 673 g/L)
Package VOC Regulatory	4.86 - 6.16 lbs./gal	5.91 - 6.42 lbs./gal	5.20 - 5.62 lbs./gal
(Less water, less exempts)	(582 - 738 g/L)	(708 - 769 g/L)	(623 - 673 g/L)
RTS Volume Ratio	1:1 + 5%	1:1 + 5%	1:1 + 5%
RTS VOC Regulatory	5.49 - 6.20 lbs./gal	5.54 - 6.20 lbs./gal	5.87 - 6.49 lbs./gal
(Less water, less exempts)	(658 - 743 g/L)	(664 - 743 g/L)	(704 - 778 g/L)

	<u>VWM500</u>	
Package VOC Actual	1.52 -1.55 lbs./gal (182 - 189 g/L)	
Package VOC Regulatory (Less water, less exempts)	3.33 - 3.66 lbs./gal (400 - 439 g/L)	
RTS Volume Ratio	1:1 + 5%	
RTS VOC Regulatory (Less water, less exempts)	5.50 - 5.88 lbs./gal (659 - 705 g/L)	
For detailed DBC recommendations and V For detailed NXT recommendations and V	•	For detailed DBC500 recommendations and VOC specifics see data sheet P176 For detailed VWM500 recommendations and VOC specifics see data sheet VB-22

### See Safety Data Sheet and Labels for additional safety information and handling instructions.

Important: The contents of this package must be blended with other components before the product can be used. Before opening the packages, be sure you understand the warning messages on the labels of all components since the mixture will have the hazards of all its parts. Improper spray technique may result in a hazardous condition. Follow spray equipment manufacturer's instructions to prevent personal injury or fire. Follow directions for respirator use. Wear eye and skin protection. Observe all applicable precautions.

#### EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION (412) 434-4515; IN CANADA (514) 645-1320

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the public. Products mentioned may be hazardous and should only be used according to direction, while observing precautions and warning statements listed on label. Statements and methods described are based upon the best information and practices known to PPG Industries. Procedures for applications mentioned are suggestions only and are not to be construed as representations or warranties as to performance, results, or fitness for any intended use, nor does PPG Industries warrant freedom from patent infringement in the use of any formula or process set forth herein.

PPG Automotive Refinish 19699 Progress Drive Strongsville, OH 44149

800.647.6050



pgrennisn.com



© 2024 PPG Industries, Inc. All rights reserved. The PPG Logo, We protect and beautify the world, Starfire, Deltron, Envirobase, , and Vibrance Collection are trademarks of PPG Industries Ohio, Inc. PPG Canada Inc. 2301 Royal Windsor Drive, Unit #6 Mississauga, Ontario L5J 1K5 888.310.4762