

# DIMETCOTE® 9 H

## DESCRIPTION

Inorganic Zinc Silicate Primer

## PRINCIPAL CHARACTERISTICS

- >85% zinc in dry film
- VOC Compliant <2.8 lb/ gal
- Provides outstanding corrosion resistance
- Good abrasion resistance
- Resistant to dry temperature up to 750°F(399°C)
- Recommended for ISO 12944 C5I and C5M conditions

## BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Three
Volume solids	80 ± 4%
VOC (Supplied)	max. 2.7 lb/US gal (approx. 324 g/l)
Temperature resistance (Continuous)	To 750°F (399°C)
Recommended dry film thickness	2.0 - 5.0 mils (50 - 125 µm) depending on system
Theoretical spreading rate	642 ft <sup>2</sup> /US gal for 2.0 mils (16.0 m <sup>2</sup> /l for 50 µm)
Shelf life	Liquid: at least 9 months when stored cool and dry Activator: at least 24 months when stored cool and dry Powder: at least 24 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time
- Color will drift at elevated temperatures
- Applications up to 6.0 mils (150 µm) are acceptable with random spot readings up to 8.0 mils (200 µm). For high temperature applications, a maximum of 3.0 mils (75 µm) is allowed
- volume solids is based on applied properties and accounts for film porosity

## RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

### Steel

- Abrasive Blast to SSPC SP-6 or higher with a 1.0-3.0 mil surface profile
- Higher surface profiles up to 5 mils (125 µm) are acceptable, but the product must be applied in a thickness great enough to achieve a minimum of 2.5 mils (65 µm) dry film thickness
- Apply this product as soon as possible to avoid rusting of blasted surfaces
- Keep moisture, oil, grease and other organic matter off surface before coating
- For touch up and repair, power tool cleaning in accordance with SSPC-SP 11 is acceptable



# DIMETCOTE® 9 H

## **Substrate temperature and application conditions**

- Surface temperature during application should be between 20°F (-7°C) and 130°F (54°C)
- Surface temperature during application should be at least 5°F (3°C) above dew point
- Ambient temperature during application and curing should be between 20°F (-7°C) and 120°F (49°C)
- Relative humidity during application and curing should be above 50% to obtain optimal curing properties

### Note:

- Work area can be artificially humidified by atomized water spray and/or ponding water under the coated structures. After the film is dry-to-touch, a fine mist may be applied over the coating to expedite curing in low humidity environments

---

## **SYSTEM SPECIFICATION**

- Primers: Direct to metal
- Topcoats: PSX 700, AMERLOCK 2/400, AMERCOAT Epoxies and PITTGUARD Epoxies

---

## **INSTRUCTIONS FOR USE**

### **Mix as packaged**

- Only mix full kits. Liquid, powder and activator are packaged in the correct proportions which, when mixed together, yield 0.68 gallons or 3.4 gallons of DIMETCOTE 9 H
- Pre-mix base component with a pneumatic air mixer at moderate speeds to homogenize the container. Add powder component slowly under agitation until fully mixed. Strain the mixture from one container to another through a 30 mesh filter/strainer to remove any undispersed lumps.

---

### **Application**

- Area should be sheltered from airborne particulates and pollutants
- Ensure good ventilation during application and curing
- Provide shelter to prevent wind from affecting spray patterns
- Repair: When dry though, measure the dry film thickness. If film thickness is lower than specified, additional material can be applied up 24 hours from the previous application. Thin the second coat with AMERCOAT 101 thinner or AMERCOAT 930 thinner. Ensure any dry spray is removed
- Repair: For aged inorganic zinc coatings, spot blast rusted areas in accordance with the surface preparation instructions before touching up with this product. When blasting is not practical, AMERCOAT 68 HS or DIMETCOTE 302 H may be used for repair
- Mist spray: A mist coat / full coat application technique is required when topcoating to prevent application bubbling. Ensure dry spray is removed from the surface
- Product can be un-topcoated in certain applications

# DIMETCOTE® 9 H

## **Pot life**

8 hours at 70°F (21°C)

Note:

- See ADDITIONAL DATA – Pot life
- 

## **Air spray**

- Separate air and fluid pressure regulators and a moisture and oil trap in the main air supply line are recommended.
- Maintain continuous agitation to keep zinc in suspension
- Limit fluid hose length to 50 feet

## **Recommended thinner**

THINNER 21-06 (AMERCOAT 65) (xylene), THINNER 21-25 (AMERCOAT 101) (recommended for > 60°F (16°C)), AMERCOAT 930 (recommended for applications > 80°F (27°C) or when dry spray is a problem)

## **Volume of thinner**

0 - 8%

## **Nozzle orifice**

Approx. 0.070 in (1.8 mm)

---

## **Airless spray**

- 30:1 pump or larger
- Use standard airless spray equipment
- A reversible fluid tip recommended

## **Recommended thinner**

THINNER 21-06 (AMERCOAT 65) (xylene), THINNER 21-25 (AMERCOAT 101) (recommended for > 60°F (16°C)), AMERCOAT 930 (recommended for applications > 80°F (27°C) or when dry spray is a problem)

## **Nozzle orifice**

0.019 – 0.023 in (approx. 0.48 – 0.58 mm)

---

## **Brush/roller**

- Use a high-quality natural-bristle brush. Brush application is only recommended for small touch-up and/or repair areas. Roller application is not recommended

## **Recommended thinner**

AMERCOAT 65 (Xylene)| AMERCOAT 101 (recommended for >60°F (16°C)), AMERCOAT 930 (recommended for applications >80°F (27°C) or when dry spray is a problem)

---

# DIMETCOTE® 9 H

## ADDITIONAL DATA

Overcoating interval for DFT up to 3.0 mils (75 µm) and 50% relative humidity					
Overcoating with...	Interval	40°F (4°C)	50°F (10°C)	70°F (21°C)	90°F (32°C)
itself	Minimum	48 hours	36 hours	24 hours	16 hours
	Maximum	Unlimited	Unlimited	Unlimited	Unlimited

Curing time for DFT up to 3.0 mils (75 µm) and 50% relative humidity		
Substrate temperature	Dry to touch	Dry to handle
40°F (4°C)	40 minutes	70 minutes
50°F (10°C)	30 minutes	40 minutes
70°F (21°C)	15 minutes	20 minutes
90°F (32°C)	5 minutes	10 minutes

Pot life (at application viscosity)	
Mixed product temperature	Pot life
50°F (10°C)	12 hours
70°F (21°C)	8 hours
90°F (32°C)	4 hours

Note:

- Maintain agitation throughout application to prevent settling of the zinc. Protect product from moisture contamination

## Product Qualifications

- SSPC Paint 20, Type IC, Level 1
- RCSC Class B slip coefficient for high strength bolted connections
- Zinc dust meets ASTM D520 type 2 standards
- AASHTO M300

## SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes



# DIMETCOTE® 9 H

## WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

## REFERENCES

- Information sheet | Explanation of product data sheets

## WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

## LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at [www.ppgpmc.com](http://www.ppgpmc.com). The English text of this sheet shall prevail over any translation thereof.

## AVAILABILITY OF PACKAGING

Depending on specific country of application the following versions are available:

Product	Color
DI9-P	Zinc Powder
DI9H-A	Liquid
DI9H-B	Activator

