

VB-05

FLAMBOYANCE®

VM4141 White *Flamboyance*VM4142 Gold *Flamboyance*VM4143 Red *Flamboyance*VM4145 Blue *Flamboyance*VM4146 Green *Flamboyance*

FLAMBOYANCE® special effect pigments are a part of the VIBRANCE COLLECTION® custom paint finishes line and are offered in 6 colors to create a wide range of basecoat and tricoat custom color formulations.

Flamboyance pigments can be added directly to basecoats or to a ground coat for use with RADIANCE® II mid-coats. Flamboyance colors can also be added to color blenders, Radiance II dyes or mid-coats to create custom formulated tricoat effects.

For procedures relating to custom and/or restoration work refer to PPG's Custom Restoration Guide available at ppgrefinish.com under Training.



Compatible Products and Systems

Flamboyance custom colors are used in conjunction with the systems shown below:

- DELTRON® DBC 2000 Refinish System Follow P-175 *Deltron* DBC recommendation for proper preparation and compatible primers.
- GLOBAL REFINISH SYSTEM® BC Refinish System Follow EU02 *Global Refinish System* BC recommendation for proper preparation and compatible primers.
- ENVIROBASE® High Performance Refinish System Follow EB-143 *Envirobase* High Performance recommendations for proper preparation and compatible primers.
- AQUABASE® Plus Refinish System Follow PDS N5.3.2 recommendations for proper preparation and compatible primers.
- DBC500 Color Blender Follow P-176 Deltron DBC500 recommendations for proper preparation and compatible primers.
- D895 Color Blender Follow EU113 Global Refinish System BC recommendations for proper preparation and compatible primers.
- VWM5556 VIBRANCE COLLECTION® Waterborne Midcoat Follow VB-15 recommendations for proper preparation and use.
- VWM500 Vibrance Collection Custom Midcoat Follow VB-22 recommendations for proper preparation and use.

Note: Custom or exotic finishes are excluded from coverage under the PPG Paint Performance Guarantee.

Directions for Use

Surface Preparation



- When working on custom finishes close attention to the details outlined for standard basecoat preparation, sanding, and cleaning is needed to achieve the optimum results.
- *Flamboyance* special effects pigments are designed to be applied over properly cleaned, sanded, and primed surfaces.

VM414x

Mixing Ratio:

(adding VM414x to a basecoat color or blender) For a custom formulation you may add a maximum of 10% (by weight) *Flamboyance* pigments to unreduced color or 5% (by weight) to ready-to-spray DBC, BC, EHP, ABP, DBC500, D895, VWM5556, or VWM500.

Reducing:

(basecoat color or blender already containing VM414x)



Reduction of basecoat color or blender containing VM414x

For detailed *Deltron DBC* 2000 reduction specifics see data sheet P-175**

For detailed Global Refinish System BC reduction specifics see data sheet EU02**

For detailed Envirobase High Performance EHP reduction specifics see data sheet EB-143

For detailed Aquabase Plus ABP reduction specifics see data sheet PDS N5.3.2

For detailed DBC500 reduction specifics see data sheet P176**

For detailed D895 reduction specifics see data sheet EU113**

For detailed VWM5556 reduction specifics see data sheet VB-15

For detailed VWM500 reduction specifics see data sheet VB-22

DX57 or D888 activator **must be used in DBC or BC colors containing *Flamboyance* special effects pigment. When using *Flamboyance* tri-coat custom colors, DX57 or D888 activator **must** be used in both the ground coat and midcoat colors.



Pot Life: See specific product data sheet listed above

Using activated material beyond 1 hour may result in wrinkling or other product failures (especially on multiple colors).

Additives:



See specific product data sheet listed above

Air Pressure
And Gun Setup:



HVLP: 8 - 10 psi at the air cap
Compliant: 29 - 40 psi at the gun
Gun Setup: 1.1 - 1.5 mm or equivalent

Refer to spraygun manufacturer's recommendations for inlet air pressures.

Application:



Apply: Sufficient number of coats to achieve desired effect.

Spraying a test panel is recommended to determine desired

effect.

Drying Times



Between Coats:

See specific product data sheet listed above



Air Dry:

Tape Time: See specific product data sheet listed above



Dry to Clearcoat:

See specific product data sheet listed above

24 hour maximum to clear coat

Note: Basecoat colors are designed to dry low in gloss. This makes color match and its approval difficult to see until the clearcoat is applied. A good technique is to spray the basecoat and clearcoat on a small test panel before spraying the job.

If the basecoat color is allowed to dry more than 24 hours, it must be scuffed and new basecoat color applied.

VM414x

Tri-Coat Mixing:

When applying *Deltron* basecoat or *Global Refinish System* basecoat, 5% DX57 or D888 Basecoat Activator must be added to the reduced basecoat prior to spraying in **BOTH** the ground coat and mid-coat.

Flamboyance pigments can be blended as a mid-coat color with DBC500, VWM5556 Waterborne Midcoat, VWM500 Custom Midcoat or D895 Color Blender. In doing so you achieve more transparency, when combined with varying ground coat colors and create different degrees of custom effects.

Striping or Two Toning

Tape Times:

Tape time of DBC and BC is 30 - 60 minutes at $70^{\circ}F$ ($21^{\circ}C$) and 50% relative humidity. Tape time of EHP, ABP and VWM5556 is 30 - 35 minutes at $70^{\circ}F$ ($21^{\circ}C$) and 50% relative humidity.

Tape time of VWM500 is 45 - 60 minutes (additional coats may require longer dry time).

All striping, two toning must be completed within 24 hours. If allowed to dry for more than 24 hours, it must be sanded and reapplied.

When applying DBC or BC basecoats, 5% DX57 or D888 Basecoat Activator **must** be added to the reduced basecoat prior to spraying in **BOTH** the ground coat and mid coat.

Clearcoating:

Due to the large particle size of the *Flamboyance* pigment, you **must** apply 2.5-3.0 mils of clear (usually 2-4 coats) to cover the basecoat.

Clear with any *Vibrance Collection* clearcoat or any clearcoat recommended for *Deltron* DBC, *Global Refinish System* BC, *Envirobase* High Performance or *Aquabase* Plus.

Equipment Cleaning:

Spray guns, gun cups, storage pots, etc., should be cleaned thoroughly after each use with any appropriate PPG general purpose solvent.

Technical Data	<u>DBC</u>	<u>BC</u>	<u>EHP</u>	<u>ABP</u>
Package VOC Actual	4.72 - 6.16 lbs./gal	4.89 - 6.08 lbs./gal	0.35 - 1.00 lbs./gal	0.35 - 1.00 lbs./gal
	(567 - 738 g/L)	(586 - 729 g/L)	(43 - 120 g/L)	(43 - 120 g/L)
Package VOC Regulatory	4.72 - 6.16 lbs./gal	4.89 - 6.08 lbs./gal	1.57 - 3.30 lbs./gal	1.57 - 3.30 lbs./gal
(Less water, less exempts)	(567 - 738 g/L)	(586 - 729 g/L)	(188 - 395 g/L)	(188 - 395 g/L)
RTS Volume Ratio	1:1 + 5%	1:1 + 5%	1:10 - 30%	1:10 - 30%
RTS VOC Regulatory	5.43 - 6.20 lbs./gal	5.47 - 6.20 lbs./gal	1.70 - 3.50 lbs./gal	1.70 - 3.50 lbs./gal
(Less water, less exempts)	(651 - 743 g/L)	(655 - 743 g/L)	(203 - 419 g/L)	(203 - 419 g/L)

	<u>DBC500</u>	<u>D895</u>	<u>VWM5556</u>	<u>VWM500</u>
Package VOC Actual	5.06 - 5.62 lbs./gal	5.06 - 5.62 lbs./gal	0.34 - 0.39 lbs./gal	1.38 - 1.55 lbs./gal
	(607 - 673 g/L)	(607 - 673 g/L)	(40 - 46 g/L)	(166 - 189 g/L)
Package VOC Regulatory	5.06 - 5.62 lbs./gal	5.06 - 5.62 lbs./gal	1.47 - 1.69 lbs./gal	3.20 - 3.66 lbs./gal
(Less water, less exempts)	(607 - 673 g/L)	(607 - 673 g/L)	(176 - 203 g/L)	(383 - 439 g/L)
RTS Volume Ratio	1:1 + 5%	1:1 + 5%	4:1	1:1 + 5%
RTS VOC Regulatory	5.80 - 6.49 lbs./gal	5.77 - 6.26 lbs./gal	2.03 - 2.30 lbs./gal	5.42 - 5.88 lbs./gal
(Less water, less exempts)	(695 - 778 g/L)	(692 - 750 g/L)	(243 - 276 g/L)	(651 - 705 g/L)

For detailed DBC recommendations and VOC specifics see data sheet P-175
For detailed BC recommendations and VOC specifics see data sheet EU02
For detailed EHP recommendations and VOC specifics see data sheet EB-143
For detailed ABP recommendation and VOC specifics see data sheet PDS N5.3.2

For detailed DBC500 recommendations and VOC specifics see data sheet P176 For detailed D895 recommendations and VOC specifics see data sheet EU113 For detailed VWM5556 recommendations and VOC specifics see data sheet VB-15 For detailed VWM500 recommendations and VOC specifics see data sheet VB-22

VM414x

See Safety Data Sheet and Labels for additional safety information and handling instructions.

Important: The contents of this package must be blended with other components before the product can be used. Before opening the packages, be sure you understand the warning messages on the labels of all components since the mixture will have the hazards of all its parts. Improper spray technique may result in a hazardous condition. Follow spray equipment manufacturer's instructions to prevent personal injury or fire. Follow directions for respirator use. Wear eye and skin protection. Observe all applicable precautions.

EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION (412) 434-4515; IN CANADA (514) 645-1320

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the public. Products mentioned may be hazardous and should only be used according to direction, while observing precautions and warning statements listed on label. Statements and methods described are based upon the best information and practices known to PPG Industries. Procedures for applications mentioned are suggestions only and are not to be construed as representations or warranties as to performance, results, or fitness for any intended use, nor does PPG Industries warrant freedom from patent infringement in the use of any formula or process set forth herein.

PPG Automotive Refinish 19699 Progress Drive Strongsville, OH 44149 800.647.6050 PPG Canada Inc. 2301 Royal Windsor Drive, Unit #6 Mississauga, Ontario L5J 1K5 888.310.4762

Follow us online: www.ppgrefinish.com



The PPG Logo, We protect and beautify the world, Flamboyance, Deltron, Radiance, Aquabase, Global Refinish System, Envirobase, and Vibrance Collection are trademarks of PPG Industries Ohio, Inc.

© 2017 PPG Industries, Inc. All rights reserved.