



# SIGMACOVER® 809



Renewable  
Energy

## Corrosion-resistant epoxy primer

Long-lasting protection in highly corrosive onshore and offshore environments



Corrosion  
Resistance



Cost  
Effective



Easy and  
Efficient



Low VOC  
Emissions

### Product Overview



PPG *Sigmacover 809* is a high-performance modified epoxy passivation primer and buildcoat that delivers long-lasting protection to steel structures requiring corrosion protection in extreme environmental conditions. Developed for use within the renewable energy industry, PPG *Sigmacover 809* epoxy primer is suitable for both onshore and offshore structures and is certified to ISO 12944 C5 very high and CX extreme corrosion protection standards.

PPG *Sigmacover 809* epoxy primer (or 'buildcoat') is more cost effective and formulated with higher volume solids in comparison with traditional zinc-rich primers. In addition to excellent corrosion protection, this primer also helps to reduce the environmental impact of application thanks to lower VOC emissions\*.

### End Use



PPG *Sigmacover 809* epoxy primer is suitable for both new construction and maintenance applications. Its surface tolerance properties make it ideal for touch-ups during installation and regular long-term maintenance.

- Offshore Substation Topsides
- Offshore OEM Equipment
- Onshore and Offshore Structural Steel

### Features and Benefits



#### Excellent Corrosion Resistance

- Meets ISO 12944 C5VH and CX standards
- Extends service life of steel structures
- Reduces frequency of repairs and maintenance
- ISO 12944 performance even at lower DFT systems (360 µm and 280 µm)

#### Cost-Effective Protection

- More economical than zinc-rich primers

#### Easy and Efficient Application

- High volume solids and fast curing time
- Lower density (compared with zinc-rich primers) for easier mixing and handling
- Ease of application with airless spray and brush

#### Reduced Environmental Impact\*

- Low VOC emissions < 280 g/l

### Certifications and Regulations



- Meets ISO 12944 C5VH and CX extreme corrosion protection standards

\*Compared to zinc-rich primers.





# Certified Systems C5 Very High and CX

System C5.04/1*			
Layer	Generic Type	Product	DFT (µm)
Primer	EP	PPG SIGMACOVER 809	150
Buildcoat	EP	PPG SIGMACOVER 809	150
Topcoat	PUR	PPG SIGMADUR 550	60
<b>Total system DFT</b>			<b>360</b>

System CX/1**			
Layer	Generic Type	Product	DFT (µm)
Primer	EP	PPG SIGMACOVER 809	100
Buildcoat	EP	PPG SIGMACOVER 410	200
Topcoat	PUR	PPG SIGMADUR 550	50
<b>Total system DFT</b>			<b>350</b>

System C5.04/2*			
Layer	Generic Type	Product	DFT (µm)
Primer	EP	PPG SIGMACOVER 809	100
Buildcoat	EP	PPG SIGMACOVER 410	200
Topcoat	PUR	PPG SIGMADUR 550	60
<b>Total system DFT</b>			<b>360</b>

System CX/2			
Layer	Generic Type	Product	DFT (µm)
Primer	EP	PPG SIGMACOVER 809	75
Buildcoat	EP	PPG SIGMACOVER 410	145
Topcoat	PUR	PPG SIGMADUR 550	60
<b>Total system DFT</b>			<b>280</b>

System C5.04/3			
Layer	Generic Type	Product	DFT (µm)
Primer	EP	PPG SIGMACOVER 809	75
Buildcoat	EP	PPG SIGMACOVER 410	145
Topcoat	PUR	PPG SIGMADUR 550	60
<b>Total system DFT</b>			<b>280</b>


System CX/3**			
Layer	Generic Type	Product	DFT (µm)
Primer	EP	PPG SIGMACOVER 809	100
Buildcoat	EP	PPG SIGMAFAST 278	200
Topcoat	PUR	PPG SIGMADUR 550	50
<b>Total system DFT</b>			<b>350</b>

\*\*Also complies with ISO 12944-9:2018 min. Nominal Dry Film Thickness and Minimum Number of Coats requirements.

System C5.04/4*			
Layer	Generic Type	Product	DFT (µm)
Primer	EP	PPG SIGMACOVER 809	100
Buildcoat	EP	PPG SIGMAFAST 278	200
Topcoat	PUR	PPG SIGMADUR 550	60
<b>Total system DFT</b>			<b>360</b>

System C5.04/5			
Layer	Generic Type	Product	DFT (µm)
Primer	EP	PPG SIGMACOVER 809	75
Buildcoat	EP	PPG SIGMAFAST 278	145
Topcoat	PUR	PPG SIGMADUR 550	60
<b>Total system DFT</b>			<b>280</b>

\*Also complies with ISO 12944-5:2019 min. Nominal Dry Film Thickness and Minimum Number of Coats requirements



The PPG Logo and We protect and beautify the world are registered trademarks of PPG Industries Ohio, Inc. Sigmacover, Sigmadur and Sigmafast are registered trademarks of PPG Coatings Nederland B.V. ©2024 PPG Industries, Inc. All rights reserved. PM 68713

For more information, visit [ppgpmc.com](http://ppgpmc.com) or contact [PMCMARKETING@ppg.com](mailto:PMCMARKETING@ppg.com)