


## 5014 PU Surfacer

### Product Description

5014 is a two pack polyurethane sanding surfacer that provides an improved appearance to aluminium when used over P99 and PAC33. 5014 is also suitable for use over epoxy, polyester and polyamide composite surfaces.

- Highly flexible
- Water resistant
- Good fluid resistance including phosphate ester hydraulic fluids
- Transparent to ultrasound & radar

### Components



#### Mix Ratio (by volume)

- |                         |         |
|-------------------------|---------|
| • 5425/0000 (Base)      | 2 parts |
| • 0707/9000 (Activator) | 1 part  |
| • 0491/9000 (Thinner)   | 1 part  |

### Specifications



5014 is qualified to:

- ASNA 4251
- BLGG 900101
- HMDC0003
- MDL 5045
- RRJ0000-RE-314-528

5014 meets the requirement of :

- AIMS 04-04-002
- AIMS 04-04-011

#### Product Compatibility

5014 is compatible with the following primer specifications:

- AIMS 04-04-004
- AIMS 04-04-012
- AIMS 04-04-054
- AIMS 04-04-055

*Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.*

## Surface Preparation and Pretreatment



Ensure the surface is clean, dry and intact using a high performance solvent cleaner - DeSoto® CN20, Desoclean™ 45 or DeSoto® CN13 solvent cleaners are recommended.

Aged P99/PAC33 primers requires mechanical sanding prior to application of 5014 sanding surfacer.

Composites Surfaces require cleaning with DeSoto® CN20, Desoclean™ 45 or DeSoto® CN13 solvent cleaners to remove release agents and contaminates.

## Instructions for Use



Hand stir or mechanically shake base material until all components are uniformly dispersed. Add activator to base component and mix thoroughly. Add thinner while stirring.

*Note: All products and components should be placed in ambient conditions of 15-30°C (59-86°F) for at least 24 hours prior to mixing and application.*



### **Induction Time:**


Not required



### **Viscosity:** ( 23°C/73°F)

• AFNOR2.5	45 - 80 seconds
• AFNOR4	15 - 20 seconds
• BSB3	26 - 40 seconds
• FORD4	12 - 19 seconds
• ISO3	37 - 85 seconds
• ISO4	18 - 38 seconds
• ZAHN2	16 - 25 seconds

*Note: Viscosities quoted are typical ranges obtained when using specified mix ratio.*



### **Pot Life:**

3 hours @ 21 - 25°C (70 - 77°F)

## Application Guidelines

### Recommended Application Conditions:

Temperature	15 - 35°C (59 - 95°F)
Relative Humidity	30 - 85%

### Application:

Apply several single passes to achieve the required dry film thickness.




### Theoretical Coverage: (ready for use)

4 m<sup>2</sup> /Lt @ 90 µm dry film thickness  
160 ft/US gal @ 3.6 mil dry film thickness

### Recommended Dry Film Thickness:

40 - 150 µm  
1.6 - 6 mil



### Dry Film Density:

1.60 - 1.78 g/cm<sup>3</sup>  
13.4 - 14.8 lbs./US gal

### Dry Film Weight:

145 - 161 g/m<sup>2</sup> @ 90 µm dry film thickness  
0.029 - 0.032 lbs/ft<sup>2</sup> @ 3.6 mil dry film thickness

*Note: These application guidelines represent PPG's best advice for usage in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.*



### Equipment:

Equipment Type	Tip Size	Pressure
HVLP Air Spray	1.2 mm	21 to 29 psi (1.5 to 2 bar)
Pressure Pot	1.5 mm	41 to 72 psi (3 to 5 bar)
Airless	0.3mm Angle 67° or 80°	1450 to 1885 psi (100 to 130 bar)

### Equipment Cleaning:

Clean as soon as possible after use. DeSoto® CN20 or Desoclean™ 45 solvent cleaners are recommended.

## Physical Properties



**Colour:**

White (5425/0000)  
Blue (5425/6407)




**Gloss:**

N/A



DRYING TIMES @ 50% R.H	23°C (73°F)	60-70°C (140-158°F)
Dust Free	90 minutes	
Dry to Touch	4 hours	30 minutes
Dry to Tape	6-8 hours	
Dry to Sand	10 hours	1 hour
Dry to Overcoat	2 hours (min.) 72 hours (max.)	1 hour
Full Cure	7 days	5 hours

*Note: Drying times listed above are dependent upon film thickness applied, air flow conditions and application technique.*



**Flash Off Time:**

30 minutes prior to force dry



**VOC: (ASTM)**

Mixed ready for use	540 g/Lt
5425/0000 Base Component	430 g/Lt
0707/9000 Activator	455 g/Lt
0491/9000 Thinner	840 g/Lt



**Flash Point:**

5425/0000 Base Component	30°C (86°F)
0707/9000 Activator	50°C (122°F)
0491/9000 Thinner	-3°C (27°F)

**Shelf Life:**

5425/0000 Base Component	24 months in original unopened container
0707/9000 Activator	24 months in original unopened container
0491/9000 Thinner	10 years in original unopened container

*Note: Shelf life may vary due to OEM specification requirements. Refer to container label for specific shelf life information.*

*Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.*

## Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

*Note: When procuring to a qualified material specification, follow those storage instructions.*

## Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

**For industrial use only. Keep away from children.**

**Additional information can be found at: [www.ppgaerospace.com](http://www.ppgaerospace.com)**

**For sales and ordering information call the local PPG office at the numbers listed below:**

### **Asia Pacific**

#### **ASC – Australia**

Tel 61 (3) 9335 1557  
Fax 61 (3) 9335 3490

#### **ASC – Japan**

Tel 81 561 35 5200  
Fax 81 561 35 5201

#### **ASC – South East Asia**

Tel 65 6861 1119  
Fax 65 6861 6162

#### **ASC – Suzhou**

Tel (86-512) 6661 5858  
Fax (86-512) 6661 6868

#### **ASC – Tianjin**

Tel (86-022) 2482 8625  
Fax (86-022) 2482 8600

### **Americas**

1 (818) 362-6711 or 1-800-AEROMIX

### **Europe and Middle East**

#### **ASC – Central Europe**

Tel 49 (40) 742 193 10  
Fax 49 (40) 742 139 69

#### **ASC – Middle East & India**

Tel (971) 4 883 9666  
Fax (971) 4 883 9665

#### **ASC – North Europe**

Tel 44 (0) 1388 770222  
Fax 44 (0) 1388 770288

#### **ASC – South Europe**

Tel 33 (0) 235 53 43 71  
Fax 33 (0) 235 53 54 44

**Desoclean, and DeSoto are trademarks of PRC-DeSoto International, Inc.**

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

*This document has been reviewed by the PPG Aerospace Export Control Department and has been determined to contain only EAR99 controlled data*

PPG Aerospace  
Sealants and Coatings  
Darlington Road  
Shildon, Co Durham UK  
DL4 2QP

[www.ppgaerospace.com](http://www.ppgaerospace.com)

Issue Date: 11/23

Lit: 4226