

JP390 2.1 VOC Epoxy Primer - Gray

Background

SHOP-LINE® JP390 is a gray 2.1 VOC two component epoxy primer which may be used as a primer or as a sealer.

Components

Primer	Hardener	Reducers
JP390 2.1 VOC Epoxy Primer - Gray	JH397 2.1 VOC Epoxy Hardener	JR554 Fast 55-65°F (13-18°C) JR555 Medium 65-75°F (18-24°C) JR556 Slow 75-85°F (24-29°C) JR557 Retarder 85-95°F (29-35°C)

Compatible Products

Can be applied over:

Sanded and cleaned bare or treated steel, galvanized or aluminum.
Sanded and cleaned body filler, SMC and gel-coated fiberglass.
Properly cleaned and sanded E-Coat
Cleaned, cured and sanded OEM and refinish coatings.
SU470LV 1K Compliant Adhesion Promoter
JP35x 2.1 VOC Multi-Purpose Primers

Can be topcoated with:

JP211 Gray Polyester Primer / Filler
JP35x 2.1 VOC Multi-Purpose Primers
JP36x 2.1 VOC Urethane Sealers
JBPX Shop-Line Plus 3.5 VOC Acrylic Urethane Basecoat
JBX 3.5 VOC Acrylic Basecoat
JTX 2.8 VOC Acrylic Urethane Direct Gloss
JLX 2.8 VOC Acrylic Enamel

Note: JP390 should not be applied over etch primer.

Compatible Products

Surface Cleaning:

SXA330 Wax and Grease Remover
SWX350 (H₂O-SO-CLEAN™)
SX1009 2.9 VOC Bug and Tar Remover

Sanding

180 - 220 Grit machine on bare steel
320 - 400 Grit machine on primer and old finishes

Mixing



Primer Ratio: $\frac{\text{JP390} : \text{JH397} : \text{JR55x}}{2 : 1 : 1}$



Sealer Ratio: $\frac{\text{JP390} : \text{JH397} : \text{JR55x}}{2 : 1 : 2}$



Pot Life: 3 - 4 hours at 70°F (21°C)



Additives: None

Air Pressure and Gun Setup



HVLP: 8 - 10 psi at the air cap
Compliant: 29 - 40 psi at the gun
Gun Setup: 1.3 - 1.6 mm or equivalent

Note: For best overall results, refer to spraygun manufacturer's recommendations for inlet air pressures.

Application



Coats: 2 : 1 : 1 1 - 2 coats used as a primer
2 : 1 : 2 2 - 3 coats used as a sealer

Note: When additional reducer is added and JP390 is sprayed as a sealer, be sure that the minimum recommended film build is maintained. (see chart)

Dry Times



Between Coats: 5 - 10 minutes at 70°F (21°C)



Air Dry at 70°F (21°C): 2 : 1 : 1 **Primer**
60 minutes
2 : 1 : 2 **Sealer**
30 - 40 minutes



Force Dry 2 : 1 : 1 **Primer**
30 minutes at 140°F (60°C) metal temperature and cool down to topcoat



IR 2 : 1 : 1 **Primer**
10 - 15 minutes and cool down to topcoat



Topcoat: **Air Dry**
2 : 1 : 1
60 minutes
2 : 1 : 2
30 - 40 minutes
Force Dry
After cool down



Note: JP390 2.1 VOC Series Epoxy Primers must be scuffed and reapplied if allowed to sit more than 3 days (72 hours)

Clean Up


Clean spray guns, gun cups, storage post, etc., thoroughly with the appropriate clean up solvent such as JT571 0.21 VOC General Purpose Solvent after each use.

Follow EPA guidelines for proper storage and disposal of solvent-borne waste paint.

Properties

Dry Film Build Per Coat	Applied 2 : 1 : 1	1.0 mils
	Applied 2 : 1 : 2	0.7 mils
Square foot coverage at 1 mil	Applied 2 : 1 : 1	650 sq. ft. / gal. 100% transfer
	Applied 2 : 1 : 2	520 sq. ft. / gal. 100% transfer

PRIMER-SEALER	Primer	Sealer
RTS Combinations:	JP390 : JH397 : JR55x	JP390 : JH397 : JR55x
Volume Ratio:	2 : 1 : 1	2 : 1 : 2
Applicable Use Category	Primer	Primer-Sealer
VOC Actual (g/L)	144	115
VOC Actual (lbs/gal)	1.21	0.96
VOC Regulatory (less water less exempt) (g/L)	248	248
VOC Regulatory (less water less exempt) (lbs/gal)	2.07	2.07
Density (g/L)	1313 - 1349	1291 - 1346
Density (lbs/gal)	10.96 - 11.25	10.77 - 11.23
Volatiles wt. %	49.1 - 50.4	58.6 - 60.3
Water wt. %	0.1	0.1
Exempt wt. %	38.1 - 39.7	49.6 - 51.7
Water vol. %	0.2	0.1 - 0.2
Exempt vol. %	42.0 - 42.1	53.6 - 53.7



Limitations

Shop-Line products should not be combined with components of other product lines.

Precautionary Information:

The contents of this package may have to be blended with other components before the product can be use. Before opening the packages be sure you understand the warning messages on the labels of all components since the mixture will have the hazards of all of its parts. Spray equipment must be handled with due care and in accordance with manufacturer's recommendations. Follow label directions for respirator use. Wear eye and skin protection. Observe all applicable precautions.

Medical Response:

EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION (412) 434-4515; IN CANADA (514)-645-1320

See Safety Data Sheet and Labels for additional safety information and handling instructions.

Safety Data Sheets for the PPG products mentioned in this publication are available through your PPG *Shop-Line* brand distributor. To the best of our knowledge, the technical information in this bulletin is accurate; however, since PPG Industries is constantly improving its coating and paint formulas, the current technical data may vary somewhat from what was available when this bulletin was printed. Contact your *Shop-Line* brand distributor or visit www.ppgrefinish.com for the most up-to-date information.

© Copyright 2025 PPG Industries All Rights Reserved - www.ppgrefinish.com
The PPG Logo, H₂O-So-Clean, and Shop-Line, are registered trademarks and *We protect and beautify the world* is a trademark of PPG Industries Ohio, Inc.