

# VB Basecoat

## Product Data Sheet



PPG VELOCITY® VB Basecoat is a high-solids, high-hiding basecoat that is easy to use, delivers excellent coverage and dries quickly. This product offers high quality and productivity as well as durability. VB Basecoat is available with mixing scheme toners, multi-stage colors and pearls.

### Compatible Products



#### Apply over:

- VP2X0 2K Urethane Primer Surfacer
- VS3X0 2K Urethane Primer Sealer
- DPLF Epoxy Primer (DP48LF, DP50LF, DP90LF)

#### Topcoat with:

- VC200 HS Clear
- VC300 HS Extra Clear
- VC400 Rapid Clear
- VC850/VC800 Matte/Semi-Gloss Clear System

### Substrate Preparation



- Wash all surfaces to be painted with car wash soap and water to remove water soluble contaminants, then apply the appropriate PPG ONECHOICE® cleaner. Ensure that the substrate is thoroughly cleaned and dried both before and after application work.
- Abrade (wet) with U.S. 500–600 / European P800–P1200-grade paper or abrade (dry) with U.S. 400–500 / European P600–P800-grade paper.
- Wash off residue and dry thoroughly before re-cleaning with appropriate *OneChoice* cleaner. The use of a *OneChoice* tack rag is recommended.
- For plastic substrates, refer to product bulletin for *OneChoice* Plastic Adhesion Promoter.

### Application Guide



#### Mix Ratio

VB Basecoat	1 part
VR Universal Thinner	1 part
VN300 Activator (Optional)	0.1 part

#### Thinners

VR151 Universal Fast Thinner	60-70° F (16-21° C)
VR152 Universal Normal Thinner	70-80° F (21-27° C)
VR153 Universal Slow Thinner	80-90° F (27-32° C)
VR154 Universal Extra Slow Thinner	Above 90° F (32° C)

#### Additives

VN300 Activator	Increases durability when added to RTS (ready to spray) basecoat. VN300 must be used in VB to qualify for PPG warranty.
-----------------	---



#### Pot Life

- Unlimited if mixed 1:1 ratio
- 2 hours if activated with VN300 at 70° F (21° C)

# Velocity® VB Basecoat

## Product Data Sheet

### Application Guide (cont.)



#### Spray Gun Setup and Pressure

Fluid tip	1.3 – 1.4 mm
Viscosity at 70° F (21° C)	15-19 seconds with a DIN4
HVLP at the air cap	8 – 10 psi
Compliant at the spray gun	26 – 29 psi

For best overall results, refer to the spray gun manufacturer's recommendations for optimum inlet air pressures.



#### Application

- 2-3 medium wet coats or until proper color is achieved
- 0.4 mils suggested dry film build



#### Drying Times

Dust-free, air dry	20 minutes at 70° F (21° C)
Tape time, air dry	40 minutes at 70° F (21° C)
Dry to clear, air dry	20-30 minutes at 70° F (21° C)

See technical bulletin IRTBI for information about infrared usage and drying times.

#### Flash Off

Between coats, 5-10 minutes or until fully flashed off at 70° F (21° C)



#### Recoating

- After 24 hours, basecoat must be cleaned, abraded and recleaned before reapplying the basecoat.
- After 12 hours, basecoat with VN300 must be cleaned, abraded with a fine scuff pad and then recleaned before reapplying the basecoat.

#### Striping / Two-Toning

- If using VN300 all striping, two toning, and clear coating must be completed within 12 hours.
- If not using VN300, after 24 hours the VB basecoat must be abraded, and cleaned before reapplying basecoat color or clearcoat.
- Clearcoat only with VC200, VC300, VC400 or VC8X0 clears.

#### As a Wet Bed: VX656 Transparent Base mixed 1:1 with VRI51/VRI52/VRI53 Thinner

- 1-2 light to medium coats applied from edge to edge over entire repair area allowing a 5-10 minute flash.
- VB basecoat may then be applied directly over the wet bed and blended as necessary.

#### As a Color Blender: Reduced VX656 mixed 1:1 with Reduced VB Basecoat

- 1-2 light to medium coats. Extend each coat a little further than the previous coat.
- If desired, more of the reduced VX656 may be added to the color mixture to further reduce the hiding for each blend step.

# Velocity® VB Basecoat

## Product Data Sheet

### Performance Guidelines

- The use of HVLP spray equipment can give an increase in transfer efficiency of around 25% depending upon the make and model of the equipment used.
- Store in a cool dry place away from heat.

### Technical Data

RTS Information	VB : VR151/152/153 1 : 1	VB : VR151/152/153 : VN300 1 : 1 : 0.10
Coating category	Color Coating	Color Coating
VOC actual (g/L)	740 – 820 g/L	742 – 805 g/L
VOC actual (lbs./U.S. gal.)	6.18 – 6.85 lbs./gal.	6.19 – 6.72 lbs./gal.
VOC regulatory (g/L) (less water less exempt)	740 – 820 g/L	742 – 805 g/L
VOC regulatory (lbs./U.S. gal.) (less water less exempt)	6.18 – 6.92 lbs./gal.	6.19 – 6.72 lbs./gal.
Density (g/L)	915 – 1077 g/L	901 – 1077 g/L
Density (lbs./U.S. gal.)	7.64 – 8.99 lbs./gal.	7.59 – 8.93 lbs./gal.
Solids volume %	8.40 – 15.75%	10.43 – 16.90%
Solids weight %	11.86 – 30.09%	13.61 – 30.64%
Coverage at 1 mil at 100% transfer efficiency (sq. ft.)	128 – 253 sq. ft.	167 – 276 sq. ft.

### Health and Safety

**See Safety Data Sheet and Labels for additional safety information and handling instructions.**

- The contents of this package may have to be blended with other components before the product can be used. Before opening the packages, be sure you understand the warning messages on the labels and SDS of all the components, since the mixture will have the hazards of all its parts.
- Improper handling and use, for example, poor spray technique, inadequate engineering controls and/or lack of proper Personal Protective Equipment (PPE), may result in hazardous conditions or injury.
- Follow spray equipment manufacturer's instructions to prevent personal injury or fire.
- Provide adequate ventilation for health and fire hazard control.
- Follow company policy, product SDS and respirator manufacturer's recommendations for selection and proper use of respiratory protection. Be sure employees are adequately trained on the safe use of respirators per company and regulatory requirements.
- Store waterborne and solvent borne waste separately. A competent agent with appropriate certification must handle all hazardous waste. Waste must be disposed of in accordance with all federal, state, provincial and local laws and regulations.
- Wear appropriate PPE such as eye and skin protection. In the event of injury, see first aid procedures on SDS.
- Always observe all applicable precautions and follow good safety and hygiene practices.

# Velocity® VB Basecoat

## Product Data Sheet

### Health and Safety (cont.)

#### Emergency Medical or Spill Control Information: (412) 434-4515

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public. Products mentioned may be hazardous and should only be used according to directions, while observing precautions and warning statements listed on label. Statements and methods described are based upon the best information and practices known to PPG Industries. Procedures for applications mentioned are suggestions only and are not to be construed as representations or warranties as to performance, result, or fitness for any intended use, nor does PPG Industries warrant freedom from patent infringement in the use of any formula or process set forth herein.



WARNING: Certain products listed may contain chemicals known to the State of California to cause cancer and/or reproductive harm. For more information go to [P65Warnings.ca.gov](http://P65Warnings.ca.gov).

The PPG Logo, We protect and beautify the world, Velocity and OneChoice are registered trademarks of PPG Industries Ohio, Inc. The Facebook "f" Logo is a registered trademark of Facebook, Inc. The IN Logo is a registered trademark of LinkedIn Corporation. The Instagram Glyph is a registered trademark of Instagram, LLC. ©2025 PPG Industries, Inc. 08/25 VL-VB

PPG Automotive Refinish • 19699 Progress Drive, Strongsville, OH 44149 • 1.800.647.6050 • [ppg.com/refinish](http://ppg.com/refinish)



We protect and beautify the world®