

PPG RAVEN® 760

DESCRIPTION

Three-component high performance epoxy-modified cement mortar resurfacing material

PRINCIPAL CHARACTERISTICS

- Proprietary epoxy-modified portland cement mortar.
- Can be spray or trowel applied
- May be polymer top-coated from 3 hours of cure time to up to 14 days without additional surface preparation
- Near zero VOCs (< 3 g/l)
- TYPICAL USES:
- Resurfacing concrete and masonry structures prior to polymer topcoat

COLOR AND GLOSS LEVEL

- Concrete gray
- Matte

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Three
Mass density	2.3 kg/l (19.2 lb/US gal)
Volume solids	100%
VOC (Supplied)	EPA Method 24: 0.0 lb/US gal (0.0 g/l)
Overcoating Interval	Minimum: 3 hours

Notes:

- Material should be stored in dry conditions, out of direct sunlight and at temperatures above 4°C (40°F) and below 43°C (110°F)
- The shelf life for the unmixed components (Part A, Part B and Part C) for this product is 12 months at 70°F (21°C)
- Curing time reflects ready for service time
- Refer to Application Guide for additional information

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- Surfaces must be damp but free of excess or flowing water before application
- A Saturated Surface Dry (SSD) condition is required
- Surface must be clean, uniform, sound, and free from contamination (such as oil, grease, rust, scale, or deposits)
- Loose or protruding brick, mortar and concrete must be removed using a Mason's hammer, chisel or scraper

PPG RAVEN® 760

Concrete / Masonry

- Abrade surface to achieve a surface profile equivalent to CSP 3 to CSP 5 in accordance with ICRI 310.2R-2013
- Abrasive blasting, shot blasting, high-pressure water cleaning, water jetting or a combination of methods may be used

Substrate temperature and application conditions

- Substrate temperature during application should be between 10°C (50°F) and 32°C (90°F)
- Ambient temperature during application should be between 10°C (50°F) and 32°C (90°F)

Note:

- For best results in limiting outgassing, apply to prepared concrete when the substrate temperature is stable or falling

SYSTEM SPECIFICATION

- Minimum application thickness is 1/16 in. (1.6 mm) per lift.
- Maximum application thickness is 1/4 in (6.4 mm) per lift.
- Additional thickness may be achieved by applying successive applications
- Theoretical coverage is 83.4 ft² (7.7 m²) per 55 lb (25 kg) bag at 1/16 in (1.6 mm) thickness.
- Theoretical coverage is 20.8 ft² (1.9 m²) per 55 lb (25 kg) bag at 1/4 in (6.4 mm) thickness.

INSTRUCTIONS FOR USE

- If time between applications of additional product is to be longer than 15 minutes, place a cover over structure to restrict air movement
- At no time should the finished product be exposed to sunlight or air movement for longer than 15 minutes
- In extremely hot and arid climates, surfaces shall be shaded while application is in process
- In environments where the humidity level is below 70%, the applied product shall be kept damp for 72 hours

Preparation

- Pour the contents of the one pint jars of Part A and Part B epoxy into the 6-gallon mixing bucket and power mix for one minute.
- Add five pints of clean water to the mixed epoxy, and mix again for one minute.
- Slowly add the 55 lb (25 kg) bag of Dry Mortar and mix using a large drill with a large spiral mixer.
- Mix until the material is uniform in texture with no dry lumps.
- For spray application, you may add an additional 8 fluid ounces (1/2 pint) of water to achieve a mix that flows well through a mortar pump.
- Follow mixing procedure on product label

PPG RAVEN® 760

Application

- Optimal spray application is achieved with the use of a PPG approved low velocity cementitious spray system, such as the Graco M680 Mortar Pump.
- Can be applied by trowel
- Only potable water may be added

Note:

- Contact Technical Services to discuss application options.

Pot life

30 minutes at 22°C (72°F)

Cleaning procedure

- Clean tools and equipment with water
- To clean skin, wash immediately and thoroughly with soap and water
- Cured product may be disposed of without restriction

ADDITIONAL DATA

Physical data of cured material	
Characteristic	Value
Tensile Strength (ASTM C307)	472 psi (3.2 MPa)
Flexural Strength (ASTM C580)	1,080 psi (7.4 MPa)
Compressive Strength (ASTM C109, 28 days)	9,120 psi (62.9 MPa)
Linear Shrinkage (ASTM C531)	0.022%
Coefficient of Thermal Expansion (ASTM C531)	$5.4 \times 10^{-6}/^{\circ}\text{F}$
Modulus of Elasticity (ASTM C580)	1,640,000 psi (11,300 MPa)
Adhesion to Concrete (ASTM D7234)	>200 psi (>1.4 MPa)

Note:

- The value ranges stated in this Product Data Sheet are based on system processing under laboratory conditions. Equipment configurations and/or field application conditions may produce variances in final system values.

DISCLAIMER

- PPG Protective & Marine Coatings does not accept any responsibility or liability for any odor, taste or contamination imparted to the drinking water from the coatings or products retained in the coating

PPG RAVEN® 760

SAFETY PRECAUTIONS

- Read all label and Safety Data Sheet (SDS) information prior to use

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

- Information sheet | Explanation of product data sheets

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.