

# PPG SIGMAGUARD™ 720

## DESCRIPTION

Two-component, reinforced high solids tank coating, based upon polyamine adduct cured pure epoxy technology

## PRINCIPAL CHARACTERISTICS

- Tank coating with good chemical resistance against a wide range of chemicals
- Meets the requirements of EI 1541 2.2 (coating systems for aviation fuel storage tanks and pipes)
- Short curing periods
- Good low-temperature curing
- Easy to clean

## COLOR AND GLOSS LEVEL

- Green, gray
- Gloss

## BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.4 kg/l (11.7 lb/US gal)
Volume solids	78 ± 2%
VOC (Supplied)	Directive 2010/75/EU, SED: max. 163.0 g/kg max. 233.0 g/l (approx. 1.9 lb/US gal)
Recommended dry film thickness	125 - 160 µm (5.0 - 6.3 mils) depending on system
Theoretical spreading rate	6.2 m <sup>2</sup> /l for 125 µm (250 ft <sup>2</sup> /US gal for 5.0 mils)
Dry to touch	3 hours
Overcoating Interval	Minimum: 8 hours Maximum: 28 days
Shelf life	Base: at least 12 months when stored cool and dry Hardener: at least 24 months when stored cool and dry

### Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time

# PPG SIGMAGUARD™ 720

## RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

### Substrate conditions

- Steel; blast cleaned to a minimum of ISO Sa2½, blasting profile 40 – 70 µm (1.6 – 2.8 mils)
  - Previous coat must be dry and free from any contamination
  - Surface of previous coat should be sufficiently roughened if necessary
- 

### IMO-MSC.288(87) requirements for cargo tanks of crude oil tankers

- Steel; ISO 8501-3:2006 grade P2, with all edges treated to a rounded radius of minimum 2 mm (0.079 in) or subject to three pass grinding or at least equivalent process before painting
  - Steel; blast cleaned to ISO-Sa2½, blasting profile 30 – 75 µm (1.2 – 3.0 mils)
  - Dust quantity on the surface to be coated must not exceed rating "1" for dust size class "3", "4" or "5" (ISO 8502-3-2017). Lower dust size classes ("1" and/or "2") to be removed if visible without magnification.
- 

### Substrate temperature and application conditions

- Substrate temperature during application and curing should be above 5°C (41°F)
  - Substrate temperature during application and curing should be at least 3°C (37°F) above dew point
- 

## SYSTEM SPECIFICATION

### System for chemical resistance according to the latest issue of the chemical resistance list

- SIGMAGUARD 720: 125 µm (5.0 mils)
  - SIGMAGUARD 720: 125 µm (5.0 mils)
- 

### System for cargo tanks of Crude Oil Tankers according to IMO resolution MSC.288(87)

- SIGMAGUARD 720: 160 µm (6.3 mils)
  - SIGMAGUARD 720: 160 µm (6.3 mils)
- 

## INSTRUCTIONS FOR USE

### Mixing ratio by volume: base to hardener 3:1

- The temperature of the mixed base and hardener should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
  - Adding too much thinner results in reduced sag resistance and slower cure
  - Thinner should be added after mixing the components
-

# PPG SIGMAGUARD™ 720

## **Table of Induction time**

<b>Mixed product induction time</b>	
<b>Mixed product temperature</b>	<b>Induction time</b>
15°C (59°F)	15 minutes
20°C (68°F)	10 minutes
25°C (77°F)	5 minutes

---

## **Pot life**

1.5 hours at 20°C (68°F)

---

## **Air spray**

### **Recommended thinner**

THINNER 91-92

### **Volume of thinner**

5 - 15% for a one coat application of 125 µm (5.0 mils) DFT

### **Nozzle orifice**

1.8 – 2.0 mm (approx. 0.070 – 0.079 in)

### **Nozzle pressure**

0.3 - 0.4 MPa (approx. 3 - 4 bar; 44 - 58 p.s.i.)

---

## **Airless spray**

### **Recommended thinner**

THINNER 91-92

### **Volume of thinner**

0 - 10% for a one coat application of 125 µm (5.0 mils) DFT

### **Nozzle orifice**

Approx. 0.53 – 0.69 mm (0.021 – 0.027 in)

### **Nozzle pressure**

15.0 MPa (approx. 150 bar; 2176 p.s.i.)

---

# PPG SIGMAGUARD™ 720

## Brush/roller

- For stripe coating and spot repair only

## Cleaning solvent

- THINNER 90-53

## ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
100 µm (4.0 mils)	7.8 m <sup>2</sup> /l (313 ft <sup>2</sup> /US gal)
125 µm (5.0 mils)	6.2 m <sup>2</sup> /l (250 ft <sup>2</sup> /US gal)
160 µm (6.3 mils)	4.9 m <sup>2</sup> /l (199 ft <sup>2</sup> /US gal)

Note:

- Maximum DFT when brushing: 100 µm (4.0 mils)

Overcoating interval for DFT up to 160 µm (6.3 mils)						
Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself	Minimum	32 hours	24 hours	8 hours	4 hours	3 hours
	Maximum	28 days	28 days	28 days	14 days	7 days

Note:

- Surface should be dry and free from any contamination



# PPG SIGMAGUARD™ 720

Curing time for full system - DFT up to 320 µm (12.6 mils)		
Substrate temperature	Minimum curing time before transport of aliphatic petroleum products and ballast water and tanktest with seawater	Minimum curing time before transport of cargoes without note 4, 7 or 11
5°C (41°F)	10 days	17 days
10°C (50°F)	7 days	14 days
15°C (59°F)	5 days	8 days
20°C (68°F)	3 days	5 days
30°C (86°F)	60 hours	4 days
40°C (104°F)	36 hours	3 days

Notes:

- For detailed information on resistance and resistance notes, please refer to the latest issue of the Tank coating Resistance List (TRIS)
- Adequate ventilation must be maintained during application and curing

Curing time for DFT up to 160 µm (6.3 mils)	
Substrate temperature	Dry to touch
5°C (41°F)	7-8 hours
10°C (50°F)	5-6 hours
20°C (68°F)	2-3 hours

Pot life (at application viscosity)	
Mixed product temperature	Pot life
15°C (59°F)	3 hours
20°C (68°F)	2.25 hours
25°C (77°F)	1.75 hour
30°C (86°F)	1.0 hour

## SAFETY PRECAUTIONS

- See Safety Data Sheet and product label for complete safety and precaution requirements
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes



# PPG SIGMAGUARD™ 720

## WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

---

## REFERENCES

- Information sheet | Explanation of product data sheets

---

## WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

---

## LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at [www.ppgpmc.com](http://www.ppgpmc.com). The English text of this sheet shall prevail over any translation thereof.

