

C-BOND™ 255

Flexible, two-component silicone adhesive

Description

C-BOND™ 255 is a general purpose silicone adhesive. It is a two component material requiring a heat cure, but does not need exposure to air or to moisture for curing. Adhesion to metals, plastics, glass and ceramics is excellent.

C-BOND™ 255 adheres well to silicone rubber, and is the recommended adhesive for bonding silicone-based C-RAM™ sheets, such as the FLX, GDSS, and RGD-S grades.

Availability

C-BOND™ 255 is available as a two-part kit comprising Part A and Part B, in the following sizes:

- 1 lb PINT (0.46 kg)
- 2 lb QUART (0.91 kg)
- 8 lb GALLON (3.60 kg)

Consult Cuming Microwave for bulk orders.

Unopened containers, if stored at room temperature, should have a shelf life of at least 6 months.

Typical properties

Color:	Clear
Usage temperature:	-55 to +230 °C (-70 to +450 °F)
Hardness, shore A:	50-60
Dielectric strength:	25 kV/mm (650 V/mil)
Volume resistivity:	10 ¹⁴ Ohm-cm
Dielectric constant (10 ² to 10 ¹⁰ Hz):	4
Dissipation factor (10 ² to 10 ¹⁰ Hz):	0.02

Instructions for use

Clean the surfaces to be bonded prior to application of the adhesive. Alcohol or acetone work well to remove grease, dirt, and fingerprints. Scuffing surfaces with sandpaper will enhance the bond strength. While its use is not necessary, a coat of C-PRIME 215 silicone primer on the metal surface will further enhance the durability of the bond in demanding applications. See Technical Bulletin 215 for information on C-PRIME 215.

Weigh out the desired amount of C-BOND™ 255 in the ratio of 10 parts A : 1 part B into a suitable container. Mix thoroughly--hand mixing is acceptable for small batches, but be sure to scrape the side of the container so no unmixed material is present.

It is recommended to draw a vacuum on the mixture to remove trapped air--trapped air may expand during the cure and affect the bond.

Apply a thin layer of adhesive to both surfaces using a brush or dust-free cloth. Mate the surfaces and apply pressure to squeeze out the excess. Ideally, the pieces being bonded should be held together under pressure during cure.

Cure at 120°C (250 °F) for 4 hours or at 175°C (350°F) for 2 hours. Pot life of the mix is at least 8 hrs at room temperature.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

This document has been reviewed by the PPG Aerospace Export Control Department and has been determined to contain only EAR99 controlled data.

Cuming Microwave Corporation

Engineered Materials
264 Bodwell Street
Avon, MA 02322
Telephone +1 (508) 521-6700
Fax +1 (508) 584-2309
www.cumingmicrowave.com
Made in the USA
Issue Date: 10/24
Supersedes: New
Lit: #4904