

AMERLOCK® 400 AL / SIGMACOVER™ 400 AL

DESCRIPTION

Two-component, high solids epoxy coating

PRINCIPAL CHARACTERISTICS

- Aluminum containing surface tolerant maintenance coating
- Compatibility with a wide range of substrates and surface preparations
- High solids, low VOC
- Can be overcoated with a wide range of topcoats
- Good adhesion on most existing coatings
- Good resistance to splash and spillage of chemicals

COLOR AND GLOSS LEVEL

- Aluminum
- Semi-gloss

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.3 kg/l (10.8 lb/US gal)
Volume solids	85 ± 2%
VOC (Supplied)	Directive 2010/75/EC, SED: max. 157.0 g/kg max. 150.0 g/l (approx. 1.3 lb/US gal)
Recommended dry film thickness	125 µm (5.0 mils) per coat
Theoretical spreading rate	6.8 m ² /l for 125 µm (273 ft ² /US gal for 5.0 mils)
Dry to touch	6 hours
Overcoating Interval	Minimum: 16 hours
Full cure after	7 days
Shelf life	Base: at least 36 months when stored cool and dry Hardener: at least 36 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time

AMERLOCK® 400 AL / SIGMACOVER™ 400 AL

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Steel; blast cleaned to ISO-Sa2½, for excellent corrosion protection
 - Steel; blast cleaned to ISO-Sa2, blasting profile 40 – 70 µm (1.6 – 2.8 mils) or power tool cleaned to ISO-St2 for good corrosion protection
 - Shop primed steel; pretreated to SPSS-Pt3 / SSPC-SP3
 - Coated steel; hydrojetted to VIS WJ2/3L
 - Existing sound coating systems; sufficiently roughened, dry and cleaned
 - For immersion exposure: steel; blast cleaned to ISO-Sa2½
-

Substrate temperature and application conditions

- Surface temperature during application should be between 5°C (41°F) and 60°C (140°F)
 - Surface temperature during application should be at least 3°C (5°F) above dew point
 - Ambient temperature during application and curing should be between 5°C (41°F) and 50°C (122°F)
 - Relative humidity during application and curing should not exceed 90%
-

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 1:1

- The paint should be stirred well before use, preferably by means of a mechanical mixer, to ensure homogeneity
 - Add hardener to base and continue stirring until homogeneous
 - The thinner should be added after mixing the two components
 - Adding too much thinner results in reduced sag resistance and slower cure
-

Pot life

4 hours at 20°C (68°F)

Note:

- See ADDITIONAL DATA – Pot life
-

AMERLOCK® 400 AL / SIGMACOVER™ 400 AL

Air spray

Recommended thinner

THINNER 91-92

Volume of thinner

0 - 10%, depending on required thickness and application conditions

Nozzle orifice

1.8 – 2.0 mm (approx. 0.070 – 0.079 in)

Nozzle pressure

0.3 - 0.4 MPa (approx. 3 - 4 bar; 44 - 58 p.s.i.)

Airless spray

Recommended thinner

No extra thinner needed

Nozzle orifice

Approx. 0.48 – 0.53 mm (0.019 – 0.021 in)

Nozzle pressure

15.0 - 18.0 MPa (approx. 150 - 180 bar; 2176 - 2611 p.s.i.)

Brush/roller

- Brush: apply evenly using a clean, well-loaded brush
- Application by brush or roller will provide approximately 80 µm (3.1 mils) DFT in a single-coat application

Cleaning solvent

- THINNER 90-53 or THINNER 90-58 (AMERCOAT 12)

ADDITIONAL DATA

Spreading rate and film thickness

DFT	Theoretical spreading rate
125 µm (5.0 mils)	6.8 m ² /l (273 ft ² /US gal)

AMERLOCK® 400 AL / SIGMACOVER™ 400 AL

Overcoating interval for DFT up to 125 µm (5.0 mils)					
Overcoating with...	Interval	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself	Minimum	24 hours	16 hours	8 hours	4 hours
	Maximum	3 months	3 months	2 months	1 month
polyurethanes	Minimum	36 hours	16 hours	8 hours	4 hours
	Maximum	1 month	1 month	14 days	7 days

Note:

- An extended recoatable window may be allowable in some circumstances. Please contact your PPG representative for more details.

Curing time for DFT up to 125 µm (5.0 mils)			
Substrate temperature	Dry to touch	Dry to handle	Full cure
10°C (50°F)	16 hours	3 days	21 days
20°C (68°F)	6 hours	24 hours	7 days
30°C (86°F)	4 hours	10 hours	4 days
40°C (104°F)	2 hours	8 hours	3 days

Notes:

- Drying times are dependent on air and steel temperature, applied film thickness, ventilation and other environmental conditions
- Adequate ventilation must be maintained during application and curing

Pot life (at application viscosity)	
Mixed product temperature	Pot life
10°C (50°F)	6 hours
20°C (68°F)	4 hours
30°C (86°F)	2 hours
40°C (104°F)	1 hour

SAFETY PRECAUTIONS

- See Safety Data Sheet and product label for complete safety and precaution requirements
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes



AMERLOCK® 400 AL / SIGMACOVER™ 400 AL

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

- Information sheet | Explanation of product data sheets

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.