

PPG SIGMACOVER® 809

DESCRIPTION

Two-component, high solids, polyamine adduct cured zinc phosphate epoxy primer/coating

PRINCIPAL CHARACTERISTICS

- High-performance modified passivation primer and buildcoat for protective coatings systems
- Long-lasting protection to steel structures requiring corrosion protection in extreme environmental conditions
- Suitable for use in offshore and onshore environments with ISO 12944-2 corrosivity categories of C5 and CX (offshore)
- Surface tolerant coating for lower grade of surface preparation for atmospheric exposure
- Easy application by brush/roller and (airless) spray

COLOR AND GLOSS LEVEL

- Gray, redbrown
- Flat

Notes:

- Epoxy coatings will chalk and fade upon exposure to sunlight, elevated temperatures, or chemical exposure. Discoloration and normal chalking do not impact performance. Light colors will darken over time. Some batch-to-batch variation in color is to be expected. Color matches are approximate.
- The addition of a UV stable topcoat should be considered when using epoxy coatings in cosmetic areas

BASIC DATA AT 20°C (68°F)

| Data for mixed product | |
|--------------------------------|---|
| Number of components | Two |
| Mass density | 1.7 kg/l (14.2 lb/US gal) |
| Volume solids | 80 ± 2% |
| VOC (Supplied) | Directive 2010/75/EU, SED: max. 159.0 g/kg UK PG 6/23(92) Appendix 3: max. 270.0 g/l (approx. 2.3 lb/US gal) |
| Recommended dry film thickness | 75 - 250 µm (3.0 - 10.0 mils) |
| Theoretical spreading rate | 10.7 m ² /l for 75 µm (428 ft ² /US gal for 3.0 mils) |
| Dry to touch | 2 hours |
| Overcoating Interval | Minimum: 3 hours Maximum: 28 days |
| Full cure after | 5 days |
| Shelf life | Base: at least 12 months when stored cool and dry Hardener: at least 24 months when stored cool and dry |

Notes:



PPG SIGMACOVER® 809

- See ADDITIONAL DATA – Spreading rate and film thickness
 - See ADDITIONAL DATA – Overcoating intervals
 - See ADDITIONAL DATA – Curing time
-

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- Apply this product to the specified thickness as soon as possible after the surface is prepared
-

Substrate conditions

- Steel; blast cleaned to ISO Sa2 or ISO-Sa2½, blasting profile 40 – 70 µm (1.6 – 2.8 mils)
 - Alternative methods to abrasive blast cleaning include: ISO-St2 (SSPC-SP2), ISO-St3 (SSPC-SP3), SSPC-SP15 or SSPC-SP WJ-2 or WJ-3 with dry surface
-

Primed steel or previous coat

- Previous suitable coat must be dry and free from any contamination
 - Surface of previous coat should be sufficiently roughened if necessary
 - When applied to zinc silicate, a mist coat and full coat technique is required
-

Substrate temperature and application conditions

- Substrate temperature during application and curing should be at least 3°C (5°F) above dew point
 - Relative humidity during application and curing should not exceed 85%
-

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 5:1

- The temperature of the paint should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
 - Adding too much thinner results in reduced sag resistance and slower cure
 - Thinner should be added after mixing the components
-

Pot life

2 hours at 20°C (68°F)

PPG SIGMACOVER® 809

Air spray

Recommended thinner

THINNER 91-92

Volume of thinner

5 - 15%, depending on required thickness and application conditions

Nozzle orifice

1.5 - 2.2 mm (approx. 0.060 - 0.087 in)

Nozzle pressure

0.3 - 0.6 MPa (approx. 3 - 6 bar; 44 - 87 p.s.i.)

Airless spray

Recommended thinner

THINNER 91-92

Volume of thinner

5 - 10%

Nozzle orifice

Approx. 0.43 - 0.48 mm (0.017 - 0.019 in)

Nozzle pressure

15.0 - 20.0 MPa (approx. 150 - 200 bar; 2176 - 2901 p.s.i.)

Brush/roller

Recommended thinner

THINNER 91-92

Volume of thinner

0 - 5%

Note:

- Application by brush may show brush marking, due to the thixotropic nature of the paint and is most suitable to small areas, tight angle areas or for stripe coating or touch-up
-

Cleaning solvent

- THINNER 90-53
-

PPG SIGMACOVER® 809

ADDITIONAL DATA

| Spreading rate and film thickness | |
|-----------------------------------|--|
| DFT | Theoretical spreading rate |
| 75 µm (3.0 mils) | 10.7 m ² /l (428 ft ² /US gal) |
| 100 µm (4.0 mils) | 8.0 m ² /l (321 ft ² /US gal) |
| 150 µm (6.0 mils) | 5.3 m ² /l (214 ft ² /US gal) |
| 250 µm (10.0 mils) | 3.2 m ² /l (128 ft ² /US gal) |

| Overcoating interval for DFT up to 150 µm (6.0 mils) | | | | | | |
|--|----------|------------|-------------|-------------|-------------|--------------|
| Overcoating with... | Interval | 0°C (32°F) | 10°C (50°F) | 20°C (68°F) | 30°C (86°F) | 40°C (104°F) |
| itself and various two-pack epoxy coatings | Minimum | 21 hours | 7 hours | 3 hours | 2 hours | 1.5 hours |
| | Maximum | 2 months | 1 month | 28 days | 21 days | 14 days |
| polyurethanes | Minimum | 30 hours | 14 hours | 10 hours | 6 hours | 4 hours |
| | Maximum | 1 month | 21 days | 14 days | 7 days | 4 days |

Note:

- The surface must be dry and free from all contaminations (oil, grease, chalking, etc...) which would require cleaning and/or abrading

| Curing time for DFT up to 150 µm (6.0 mils) | | | |
|---|--------------|---------------|-----------|
| Substrate temperature | Dry to touch | Dry to handle | Full cure |
| 0°C (32°F) | 18 hours | 24 hours | 20 days |
| 5°C (41°F) | 12 hours | 16 hours | 14 days |
| 10°C (50°F) | 5 hours | 8 hours | 10 days |
| 20°C (68°F) | 3 hours | 5 hours | 5 days |
| 30°C (86°F) | 1 hour | 4 hours | 4 days |
| 40°C (104°F) | 45 minutes | 3 hours | 48 hours |

Note:

- Adequate ventilation must be maintained during application and curing

PPG SIGMACOVER® 809

| Pot life (at application viscosity) | |
|-------------------------------------|------------|
| Mixed product temperature | Pot life |
| 10°C (50°F) | 3 hours |
| 20°C (68°F) | 2 hours |
| 30°C (86°F) | 1 hour |
| 40°C (104°F) | 40 minutes |

SAFETY PRECAUTIONS

- See Safety Data Sheet and product label for complete safety and precaution requirements
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

- Information sheet | Explanation of product data sheets

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

