

# PHENGUARD™ SUBSEA 780

## DESCRIPTION

Two-component, amine adduct-cured phenolic epoxy finish

## PRINCIPAL CHARACTERISTICS

- Finish coat for coating system, used for the protection of subsea equipment
- Bright color to assist location by ROV
- Excellent resistance to seawater immersion
- Very good corrosion control
- Excellent high-temperature resistance in immersed conditions
- Good application properties, resulting in a smooth surface
- Meets the requirements of Norsok M-501 Rev. 6, System 7C

## COLOR AND GLOSS LEVEL

- Yellow (RAL 1004, RAL 1018), Orange (RAL 2004), Offwhite (RAL 9002), other colors available on a limited basis
- Eggshell

Note:

- Color is approximate and will be subject to some degree of drift over time

## BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.7 kg/l (14.2 lb/US gal)
Volume solids	66 ± 2%
VOC (Supplied)	EPA Method 24: 300.0 g/ltr (2.5 lb/USgal)
Recommended dry film thickness	100 - 175 µm (4.0 - 7.0 mils) depending on system
Theoretical spreading rate	6.6 m <sup>2</sup> /l for 100 µm (265 ft <sup>2</sup> /US gal for 4.0 mils) 3.8 m <sup>2</sup> /l for 175 µm (151 ft <sup>2</sup> /US gal for 7.0 mils)
Dry to touch	2 hours
Overcoating Interval	Minimum: 3 hours Maximum: 21 days
Shelf life	Base: at least 24 months when stored cool and dry Hardener: at least 12 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time
- Please contact a PPG representative when shelf life extension is needed

# PHENGUARD™ SUBSEA 780

## RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

### Substrate conditions

- Previous coat of approved coating must be dry and free from any contamination
- Substrate must be dry, free from oil, grease and any contamination

### Substrate temperature and application conditions

- Substrate temperature during application and curing should be above 10°C (50°F)
- Substrate temperature during application should be at least 3°C (5°F) above dew point

## INSTRUCTIONS FOR USE

### Mixing ratio by volume: base to hardener 7.33:1

- The temperature of the paint should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
- Adding too much thinner results in reduced sag resistance and slower cure
- Thinner should be added after mixing the components

### Table of Induction time

Mixed product induction time	
Mixed product temperature	Induction time
15°C (59°F)	20 minutes
20°C (68°F)	15 minutes
30°C (86°F)	10 minutes

### Pot life

4 hours at 20°C (68°F)

Note:

- See ADDITIONAL DATA – Pot life



# PHENGUARD™ SUBSEA 780

## **Air spray**

### **Recommended thinner**

THINNER 91-92

### **Volume of thinner**

2 - 10%, depending on required thickness and application conditions

### **Nozzle orifice**

2.0 mm (approx. 0.079 in)

### **Nozzle pressure**

0.3 MPa (approx. 3 Bar; 44 p.s.i.)

## **Airless spray**

### **Recommended thinner**

THINNER 91-92

### **Volume of thinner**

2 - 10%, depending on required thickness and application conditions

### **Nozzle orifice**

Approx. 0.46 – 0.53 mm (0.018 – 0.021 in)

### **Nozzle pressure**

15.0 MPa (approx. 150 bar; 2176 p.s.i.)

## **Cleaning solvent**

- THINNER 90-53

## **ADDITIONAL DATA**

<b>Spreading rate and film thickness</b>	
<b>DFT</b>	<b>Theoretical spreading rate</b>
100 µm (4.0 mils)	6.6 m <sup>2</sup> /l (265 ft <sup>2</sup> /US gal)
125 µm (5.0 mils)	5.3 m <sup>2</sup> /l (212 ft <sup>2</sup> /US gal)
175 µm (7.0 mils)	3.8 m <sup>2</sup> /l (151 ft <sup>2</sup> /US gal)



# PHENGUARD™ SUBSEA 780

Overcoating interval for DFT up to 175 µm (7.0 mils)						
Overcoating with...	Interval	10°C (50°F)	15°C (59°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself	Minimum	16 hours	6 hours	3 hours	3 hours	2 hours
	Maximum	28 days	25 days	21 days	14 days	7 days

Notes:

- Surface should be dry and free from any contamination
- When needs to walk on for topcoat, min. recoat time should be same as dry to handle time to avoid damage on coated system

Curing time for DFT up to 175 µm (7.0 mils)		
Substrate temperature	Dry to handle	Full cure
10°C (50°F)	16 hours	5 days
15°C (59°F)	12 hours	4 days
20°C (68°F)	8 hours	3 days
30°C (86°F)	6 hours	48 hours

Note:

- Adequate ventilation must be maintained during application and curing

Pot life (at application viscosity)	
Mixed product temperature	Pot life
10°C (50°F)	6 hours
20°C (68°F)	4 hours
30°C (86°F)	1.5 hours
40°C (104°F)	30 minutes

**Product Qualifications**

- Qualified for NORSOK M501 Rev.7 System 7C up to 150°C(302°F) with 3 coating system (Phenguard 985 / 985 / Phenguard Subsea 780 system)
- Qualified for NORSOK M501 Rev.7 System 7C up to 180°C(356°F) with 2 coating system (Phenguard Subsea 610 / 780 system)
- Qualified for NORSOK M501 Rev.7 System 7C up to 180°C(356°F) with 3 coating system (Phenguard Subsea 610 / 780 / 780 system)



# PHENGUARD™ SUBSEA 780

## SAFETY PRECAUTIONS

- See Safety Data Sheet and product label for complete safety and precaution requirements
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

---

## WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

---

## REFERENCES

- Guide | PPG PHENGUARD | Subsea application and repair guidelines (3-layer system)
- Guide | PPG PHENGUARD | Subsea application and repair guidelines (2-layer system)
- Information sheet | Explanation of product data sheets

---

## WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

---

## LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at [www.ppgpmc.com](http://www.ppgpmc.com). The English text of this sheet shall prevail over any translation thereof.

