

## MBC Acrylic Basecoat

### Background

OMNI® MBC is a fast drying acrylic basecoat designed for today's automotive collision centers. MBC must be clearcoated with one of the *Omni* clears.

### Components

#### Color

MBC Acrylic Basecoat

#### Reducer

MR185 Fast 55-65°F (13-18°C)  
MR186 Medium 65-75°F (18-24°C)  
MR187 Slow 75-85°F (24-29°C)  
MR188 Very Slow 85-95°F (29-35°C)

### Compatible Products

#### Can be applied over:

Cured, cleaned and sanded OEM and refinish coatings  
MP17x Epoxy Primers  
MP178 Plastic Primer  
MP281 1K Light Gray Primer Surfacer  
MP182 2K Urethane Surfacer  
MP282 High Build 2K Primer Surfacer  
MP213 GP Sealer  
MP23x 2K Urethane Sealers

#### Can be topcoated with:

MC161 High Solids Urethane Clear  
MC250 Urethane Clearcoat  
MC260 Quick Clear  
MC270 4.2 VOC Production Clear  
MC2800 EUROPLUS® Speed Clear

### Preparation

#### Surface Cleaning:

MX190 Cleaner  
MX192 Plastic Cleaner  
SXA330 Wax and Grease Remover  
SWX350 (H<sub>2</sub>O-SO-CLEAN®) Waterborne Pre-Cleaner

#### Sanding

400 grit (machine or dry hand) or 500 grit (wet) on old finishes and primer surfacers.

### Mixing



#### Ratios

MBC	:	MR Reducer
1	:	1



#### Pot Life:

Indefinite



#### Tinting:

MBC may be tinted up to 10% with *Omni* AU mixing bases and equal parts of M150 basemaker.



#### Additives:

Optional  
The hardener that will be used in the clearcoat selected for the repair may also be added to catalyze the basecoat as follows:  
10% to unreduced RTS or  
5% to reduced RTS

---

## Air Pressure and Gun Setup

---



<b>HVLP:</b>	8 - 10 psi at the air cap
<b>Compliant:</b>	29 - 40 psi at the gun
<b>Gun Setup:</b>	1.3 - 1.6 mm or equivalent

Note: For best overall results, refer to spraygun manufacturer's recommendations for inlet air pressures.

---

## Application

---



<b>Coats:</b>	2 - 3 coats or until proper color is achieved
---------------	---

---

## Dry Times

---



<b>Between Coats:</b>	5 - 10 minutes at 70°F (21°C)
-----------------------	-------------------------------



<b>Air Dry:</b>	
Tape:	45 minutes



<b>Clear Coat:</b>	20 minutes minimum, 24 hours maximum at 70°F (21°C)
--------------------	---

---

## Clean Up

---

Clean spray guns, gun cups, storage pots, etc., thoroughly with MR Reducer, MS251 Multi Purpose Solvent or another appropriate clean up solvent after each use.

Follow EPA guidelines for proper storage and disposal of solvent-borne waste paint.

---

## Properties

---

### VOC

Package VOC Actual	4.39 - 5.78 lbs./ gal (526 - 693 g/L)
Package VOC Regulatory	4.39 - 5.78 lbs./ gal (526 - 693 g/L)
Applied RTS VOC Regulatory (1:1)	5.61 - 6.29 lbs./ gal (644 - 755 g/L)
RTS Solids by weight	12.5-23.5%
Film build per coat	
Applied (1:1)	0.5 - 0.6 mils
Square Foot coverage at 1 mil	
Applied (1:1)	159 - 198 sq. ft. gal at 100% transfer

### Limitations

*Omni* products should not be combined with components of other product lines.

### Precautionary Information:

The contents of this package may have to be blended with other components before the product can be used. Before opening the packages be sure you understand the warning messages on the labels of all components since the mixture will have the hazards of all of its parts. Spray equipment must be handled with due care and in accordance with manufacturer's recommendations. Follow label directions for respirator use. Wear eye and skin protection. Observe all applicable precautions.

### Medical Response:

**EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION (412) 434-4515; IN CANADA (514)-645-1320**

**See Safety Data Sheet and Labels for additional safety information and handling instructions.**

Data Safety Sheets for the PPG products mentioned in this publication are available through your PPG *Omni* brand distributor. To the best of our knowledge, the technical information in this bulletin is accurate; however, since PPG Industries is constantly improving its coating and paint formulas, the current technical data may vary somewhat from what was available when this bulletin was printed. Contact your *Omni* brand distributor or visit [www.ppgrefinish.com](http://www.ppgrefinish.com) for the most up-to-date information.

