

SIGMA SAILADVANCE™ DX II

DESCRIPTION

High-performance self-polishing and self-smoothing antifouling based on hydrolyzing, pure silyl acrylate technology

PRINCIPAL CHARACTERISTICS

- Designed as the antifouling system suitable for a range of vessel activities
- Self-polishing antifouling with good weathering properties for atmospheric resistance during vessel construction and in- service
- Controlled polishing rate to give effective protection in accordance with the specified dry film thickness
- Enhances self-smoothing capabilities to give optimal hull roughness reduction
- Controls settlement of shell and weed fouling for prolonged periods, depending on sailing pattern and routes
- Complies with IMO Antifouling Systems Convention
- Developed based upon advanced PPG technology

COLOR AND GLOSS LEVEL

- Redbrown, brown
- Flat

BASIC DATA AT 20°C (68°F)

Data for product	
Number of components	One
Mass density	1.8 kg/l (15.2 lb/US gal)
Volume solids	63 ± 2%
VOC (Supplied)	Directive 2010/75/EU, SED: max. 205.5 g/kg max. 378.0 g/l (approx. 3.2 lb/US gal) China GB 38469-2019 (tested) 416.0 g/l (approx. 3.5 lb/gal)
Recommended dry film thickness	75 - 165 µm (3.0 - 6.5 mils) depending on system
Theoretical spreading rate	4.2 m ² /l for 150 µm (168 ft ² /US gal for 6.0 mils)
Dry to touch	2 hours
Overcoating Interval	Minimum: 6 hours
Shelf life	At least 12 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals



SIGMA SAILADVANCE™ DX II

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Previous coat must be sound, dry and free from any contamination
 - Suitable high performance anticorrosive tiecoats
-

Substrate temperature and application conditions

- Substrate temperature during application should be at least 3°C (5°F) above dew point
 - Substrate temperature during application and curing should be above -5°C (23°F)
 - Relative humidity during application and curing should not exceed 85%
-

INSTRUCTIONS FOR USE

- Stir well before use
 - The temperature of the paint should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
 - Adding too much thinner results in reduced sag resistance
-

Airless spray

Recommended thinner

THINNER 21-06

Volume of thinner

0 - 3%, depending on required thickness and application conditions

Nozzle orifice

Approx. 0.53 – 0.69 mm (0.021 – 0.027 in)

Nozzle pressure

12.0 - 15.0 MPa (approx. 120 - 150 bar; 1741 - 2176 p.s.i.)

Brush/roller

- Only for touch-up and spot repair

Recommended thinner

THINNER 21-06

Volume of thinner

0 - 3%

SIGMA SAILADVANCE™ DX II

Cleaning solvent

- THINNER 21-06

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
75 µm (3.0 mils)	8.4 m ² /l (337 ft ² /US gal)
100 µm (4.0 mils)	6.3 m ² /l (253 ft ² /US gal)
150 µm (6.0 mils)	4.2 m ² /l (168 ft ² /US gal)
165 µm (6.5 mils)	3.8 m ² /l (155 ft ² /US gal)

Overcoating interval for DFT up to 165 µm (6.5 mils)							
Overcoating with...	Interval	-5°C (23°F)	0°C (32°F)	5°C (41°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)
itself	Minimum	30 hours	24 hours	18 hours	12 hours	6 hours	4 hours
	Refloating - Minimum	48 hours	30 hours	24 hours	18 hours	12 hours	9 hours

Notes:

- Longer drying times may be necessary at higher DFT and under unfavorable atmospheric conditions
- Above table is a fair indication for normal application conditions. Please contact your PPG representative for data at much lower and higher DFT conditions.

SAFETY PRECAUTIONS

- See Safety Data Sheet and product label for complete safety and precaution requirements
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

- Information sheet | Explanation of product data sheets



SIGMA SAILADVANCE™ DX II

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

AVAILABILITY OF PACKAGING

Depending on specific country of application the following versions are available:

Article code	Color	Reference
430173	Redbrown	200800KR2150
445903	Brown	200000KR2150

