

# SIGMAZINC™ 109 ME

## DESCRIPTION

Two-component, zinc-rich, polyamide-cured epoxy primer

## PRINCIPAL CHARACTERISTICS

- Designed as a system primer for various paint systems
- Good corrosion prevention properties
- Quick-drying, can be overcoated after a short interval
- Topcoats must be unsaponifiable
- Complies with the compositional requirements of SSPC-Paint 20, Level 1 and BS5493, which means zinc content is higher than 90% in dried film

## COLOR AND GLOSS LEVEL

- Gray, reddish gray
- Flat

## BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	2.9 kg/l (24.5 lb/US gal)
Volume solids	62 ± 2%
VOC (Supplied)	Directive 2010/75/EU, SED: max. 129.0 g/kg max. 378.0 g/l (approx. 3.2 lb/US gal)
Recommended dry film thickness	40 - 75 µm (1.6 - 3.0 mils) depending on surface preparation
Theoretical spreading rate	15.5 m <sup>2</sup> /l for 40 µm (622 ft <sup>2</sup> /US gal for 1.6 mils) 8.3 m <sup>2</sup> /l for 75 µm (331 ft <sup>2</sup> /US gal for 3.0 mils)
Dry to touch	20 minutes
Overcoating Interval	Minimum: 8 hours Maximum: 3 months
Full cure after	7 days
Shelf life	Base: at least 24 months when stored cool and dry Hardener: at least 24 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time

# SIGMAZINC™ 109 ME

## RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

### Substrate conditions

- Steel; blast cleaned to ISO-Sa2½, blasting profile 40 – 70 µm (1.6 – 2.8 mils)
  - For maintenance and repair in atmospheric service, the product can be applied over surfaces prepared in accordance with SSPC SP-2 or SSPC SP-3 (hand and power tool cleaning).
- 

### Substrate temperature and application conditions

- Substrate temperature during application and curing should be above 5°C (41°F)
  - Substrate temperature during application and curing should be at least 3°C (5°F) above dew point
- 

## INSTRUCTIONS FOR USE

### Mixing ratio by volume: base to hardener 4:1

- The temperature of the mixed base and hardener should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
  - Adding too much thinner results in reduced sag resistance and slower cure
  - Thinner should be added after mixing the components
- 

### Pot life

24 hours at 20°C (68°F)

Note:

- See ADDITIONAL DATA – Pot life
- 

### Air spray

#### **Recommended thinner**

THINNER 91-92

#### **Volume of thinner**

5 - 10%, depending on required thickness and application conditions

#### **Nozzle orifice**

1.8 – 2.2 mm (approx. 0.070 – 0.087 in)

#### **Nozzle pressure**

0.3 - 0.6 MPa (approx. 3 - 6 bar; 44 - 87 p.s.i.)

---

# SIGMAZINC™ 109 ME

## **Airless spray**

### **Recommended thinner**

THINNER 91-92

### **Volume of thinner**

5 - 10%, depending on required thickness and application conditions

### **Nozzle orifice**

Approx. 0.43 – 0.48 mm (0.017 – 0.019 in)

### **Nozzle pressure**

15.0 MPa (approx. 150 bar; 2176 p.s.i.)

---

## **Brush/roller**

### **Recommended thinner**

THINNER 91-92

### **Volume of thinner**

0 – 5%

---

## **Cleaning solvent**

- THINNER 90-53
- 

## **ADDITIONAL DATA**

### **Spreading rate and film thickness**

<b>DFT</b>	<b>Theoretical spreading rate</b>
40 µm (1.6 mils)	15.5 m <sup>2</sup> /l (622 ft <sup>2</sup> /US gal)
75 µm (3.0 mils)	8.3 m <sup>2</sup> /l (331 ft <sup>2</sup> /US gal)

---

# SIGMAZINC™ 109 ME

Overcoating interval for DFT up to 75 µm (3.0 mils)				
Overcoating with...	Interval	10°C (50°F)	20°C (68°F)	30°C (86°F)
various two-pack epoxy coatings	Minimum	10 hours	8 hours	6 hours
	Maximum	3 months	3 months	3 months

Notes:

- When a longer overcoating interval is required, it is recommended to overcoat SIGMAZINC 109 ME as soon as possible with SIGMACOVER 522
- Before overcoating any visible surface contamination must be removed by sandwashing, sweep blasting or mechanical cleaning
- An interval of several months can be allowed under clean interior exposure conditions
- Zinc rich primers can form zinc salts on the surface; preferably they should not be weathered for long periods before overcoating
- In clean exterior conditions, a maximum interval of 14 days can be tolerated, but in industrial or marine conditions this interval should be reduced to the practical minimum

Curing time for DFT up to 75 µm (3.0 mils)		
Substrate temperature	Full cure	Dry to touch
10°C (50°F)	20 days	45 minutes
15°C (59°F)	10 days	30 minutes
20°C (68°F)	7 days	20 minutes
30°C (86°F)	5 days	10 minutes

Notes:

- For such applications alternative zinc rich primers are recommended: SIGMAZINC 158 for systems exposed to atmospheric conditions, DIMETCOTE 9 for systems exposed to immersed conditions
- SIGMAZINC 109 ME can be applied at temperatures down to 5°C (41°F), but the curing rate will be very slow
- Adequate ventilation must be maintained during application and curing

Pot life (at application viscosity)	
Mixed product temperature	Pot life
20°C (68°F)	24 hours
35°C (95°F)	6 hours



# SIGMAZINC™ 109 ME

## SAFETY PRECAUTIONS

- See Safety Data Sheet and product label for complete safety and precaution requirements
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

---

## WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

---

## REFERENCES

- Information sheet | Explanation of product data sheets

---

## WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

---

## LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at [www.ppgmc.com](http://www.ppgmc.com). The English text of this sheet shall prevail over any translation thereof.

