

SIGMALINE™ 403 HS

DESCRIPTION

Two-component, high-solids polyamine cured epoxy flow coating

PRINCIPAL CHARACTERISTICS

- Reduces the frictional resistance of the inside of steel pipes for the transportation of purified natural gas
- High volume solids
- Good anticorrosive properties
- Meets API RP 5L2 fourth edition
- Meets the requirements of EN10301

COLOR AND GLOSS LEVEL

- Redbrown
- Gloss

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.5 kg/l (12.1 lb/US gal)
Volume solids	78 ± 2%
VOC (Supplied)	Directive 1999/13/EC, SED: max. 165.0 g/kg max. 239.0 g/l (approx. 2.0 lb/US gal)
Recommended dry film thickness	50 - 100 µm (2.0 - 4.0 mils) depending on surface preparation
Theoretical spreading rate	15.6 m ² /l for 50 µm (626 ft ² /US gal for 2.0 mils)
Dry to touch	3.5 hours
Overcoating Interval	Minimum: 8 hours Maximum: 2 months
Full cure after	7 days
Shelf life	Base: at least 12 months when stored cool and dry Hardener: at least 12 months when stored cool and dry

Notes:

- See ADDITIONAL DATA - Spreading rate and film thickness
- See ADDITIONAL DATA - Curing time
- See ADDITIONAL DATA - Spreading rate and film thickness

SIGMALINE™ 403 HS

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Steel; blast cleaned to ISO Sa 2½ or SSPC-SP-10, blasting profile (Rz) 30 – 80 µm (1.2 – 3.2 mils) (*)
- During the curing time coated pipes should be protected against adverse weather conditions such as condensation, rain, fog and snow

Note: (*) It must be noted that the main purpose of a flowcoat is not the anticorrosive protection, but the reduction of friction during the transport of gas. As such it is important to have a smooth finish. The applied DFT needs to be adjusted to the obtained blasting profile. We recommend to apply a nominal DFT which is always at least 20µm higher than the blasting profile (Rz). ISO 19840:2012 shall be used for the determination of DFT.

Substrate temperature and application conditions

- Ambient temperature during application should be between 5°C (41°F) and 40°C (104°F)
- Substrate temperature during application and curing should be above 5°C (41°F)
- Substrate temperature during application and curing should be at least 3°C (5°F) above dew point
- Relative humidity during application and curing should not exceed 80%

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 80:20 (4:1)

- The temperature of the paint should preferably be above 5°C (41°F), otherwise extra thinner may be required to obtain application viscosity
- Adding too much thinner results in reduced sag resistance and slower cure
- Thinner should be added after mixing the components

Induction time

None

Pot life

3 hours at 20°C (68°F)

Note: See ADDITIONAL DATA – Pot life

Application

- Visco base: 5 - 10 Poise
- Visco hardener: 3 - 5 Poise
- Visco set: 4 - 7 Poise
- Weight solids: 79 ± 2%
- Ash content: 37 ± 2%
- Bucholz hardness: 104 ± 10



SIGMALINE™ 403 HS

Airless spray

Recommended thinner

THINNER 21-06

Volume of thinner

0 - 3%, depending on required thickness and application conditions

Nozzle orifice

Approx. 0.48 - 0.64 mm (0.019 - 0.025 in)

Nozzle pressure

16.0 - 22.0 MPa (approx. 160 - 220 bar; 2321 - 3191 p.s.i.)

Brush/roller

- Only for touch-up and spot repair
- Multicoat roller or brush application is not recommended. Maximum DFT achievable by brush or roller is 50 µm (2.0 mils)

Recommended thinner

THINNER 21-06

Volume of thinner

0 - 3%

Cleaning solvent

THINNER 90-53

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
50 µm (2.0 mils)	15.6 m ² /l (626 ft ² /US gal)
75 µm (3.0 mils)	10.4 m ² /l (417 ft ² /US gal)
100 µm (4.0 mils)	7.8 m ² /l (313 ft ² /US gal)

SIGMALINE™ 403 HS

Curing time for DFT up to 75 µm (3.0 mils)

Substrate temperature	Dry to touch	Dry to handle	Full cure
5°C (41°F)	9 hours	16 hours	21 days
10°C (50°F)	7 hours	14 hours	14 days
20°C (68°F)	3.5 hours	8 hours	7 days
25°C (77°F)	2.5 hours	6 hours	6 days
30°C (86°F)	2 hours	5 hours	5 days

Notes:

- Adequate ventilation must be maintained during application and curing (please refer to INFORMATION SHEETS 1433 and 1434)
- During the curing period precautions must be taken to avoid contact of the coating with moisture, otherwise blushing may occur

Pot life (at application viscosity)

Mixed product temperature	Pot life
5°C (41°F)	6 hours
10°C (50°F)	4 hours
20°C (68°F)	3 hours
30°C (86°F)	2 hours
40°C (104°F)	1 hour

Product Qualifications

- SigmaLine 403 HS meets both requirements of API RP 5L2 fourth edition as well as BS EN 10301:2003
- The glass transition temperature (T_g) of SigmaLine 403 HS is determined as 16°C (DSC according to ISO 11357-2:2013)
- SigmaLine 403 HS is suitable for dry sweet gas cargoes with a maximum service temperature range up to 120°C
- SigmaLine 403 HS is suitable for wet sour gas however at different temperature ranges. In the event of the cargo being wet sour gas, the composition, concentration etc. of the cargo will have to be provided in order for PPG to make a recommendation on the maximum temperature range

SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.



SIGMALINE™ 403 HS

REFERENCES

• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431
• SAFE WORKING IN CONFINED SPACES	INFORMATION SHEET	1433
• DIRECTIVES FOR VENTILATION PRACTICE	INFORMATION SHEET	1434
• SURFACE PREPARATION OF STEEL PIPES AND FITTINGS SHOP APPLICATION	INFORMATION SHEET	1492

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

