

PPG SIGMATHERM™ 230

DESCRIPTION

Two-component, high-build, heat-resistant epoxy phenol novolac coating

PRINCIPAL CHARACTERISTICS

- Provides a corrosion resistant barrier on carbon steel and stainless steel under thermal insulation
- Suitable as heat resistant system under insulation up to 230°C (450°F)
- Suitable for use in cryogenic conditions
- Passes cryogenic cyclic test down to -196°C (-321°F)
- Excellent protection and resistance against corrosion and severe chemicals
- Excellent resistance to thermal shock during rapid wet & dry cycling
- Meets CS-1, 3 and 4 for carbon steels under thermal insulation according to NACE SP0198-10
- Meets SS-1, 2 and 3 for stainless steels under thermal insulation according to NACE SP0198-10
- No post-curing is required to obtain mechanical strength
- Can be applied on hot substrate up to 150°C (302°F), please contact your PPG representative for detail

COLOR AND GLOSS LEVEL

- Pink, gray
- Low sheen

Note:

- Epoxy coatings will chalk and fade upon exposure to sunlight, elevated temperatures, or chemical exposure. Discoloration and normal chalking do not impact performance. Light colors will darken over time. Some batch-to-batch variation in color is to be expected. Color matches are approximate.

BASIC DATA AT 20°C (68°F)

| Data for mixed product | |
|--------------------------------|---|
| Number of components | Two |
| Mass density | 1.7 kg/l (14.2 lb/US gal) |
| Volume solids | 68 ± 2% |
| VOC (Supplied) | Directive 2010/75/EU, SED: max. 195.0 g/kg max. 329.0 g/l (approx. 2.7 lb/US gal) EPA Method 24: 310.0 g/ltr (2.6 lb/USgal) |
| Recommended dry film thickness | 100 - 150 µm (4.0 - 6.0 mils) |
| Theoretical spreading rate | 4.5 m ² /l for 150 µm (182 ft ² /US gal for 6.0 mils) |
| Dry to touch | 3 hours |
| Overcoating Interval | Minimum: 8 hours Maximum: 14 days |
| Full cure after | 3 days |
| Shelf life | Base: at least 24 months when stored cool and dry |



PPG SIGMATHERM™ 230

| Data for mixed product | |
|------------------------|---|
| | Hardener: at least 24 months when stored cool and dry |

Notes:

- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time
- To avoid crack at elevated temperature, it is recommended that the total average dry film thickness not exceed 350 µm (14 mils) and locally 400 µm (16 mils)

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Steel; blast cleaned to ISO-Sa2½, blasting profile 40 – 70 µm (1.6 – 2.8 mils)
- The substrate must be perfectly dry before and during application of SIGMATHERM 230
- Stainless steel ; degrease with solvent and sweep blast, SSPC SP-16 with blasting profile 40 – 100 µm (1.5 – 4.0 mils)

Substrate temperature and application conditions

- Substrate temperature during application and curing should be above 5°C (41°F)
- Substrate temperature during application and curing should be at least 3°C (5°F) above dew point

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 6.69:1

- The temperature of the mixed base and hardener should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
- Adding too much thinner results in reduced sag resistance
- Thinner should be added after mixing the components

Table of Induction time

| Mixed product induction time | |
|------------------------------|----------------|
| Mixed product temperature | Induction time |
| 5°C (41°F) | 20 minutes |
| 10°C (50°F) | 15 minutes |
| 15°C (59°F) | 10 minutes |



PPG SIGMATHERM™ 230

Pot life

2 hours at 20°C (68°F)

Note:

- See ADDITIONAL DATA – Pot life
-

Air spray**Recommended thinner**

THINNER 91-92 for ambient temperature ; THINNER 21-25 for application to hot surfaces

Volume of thinner

5 - 10%, depending on required thickness and application conditions

Nozzle orifice

2.0 mm (approx. 0.079 in)

Nozzle pressure

0.3 MPa (approx. 3 Bar; 44 p.s.i.)

Airless spray**Recommended thinner**

THINNER 91-92 for ambient temperature ; THINNER 21-25 for application to hot surfaces

Volume of thinner

5 - 10%, depending on required thickness and application conditions

Nozzle orifice

Approx. 0.46 – 0.53 mm (0.018 – 0.021 in)

Nozzle pressure

15.0 MPa (approx. 150 bar; 2176 p.s.i.)

Brush/roller**Recommended thinner**

THINNER 91-92

Volume of thinner

0 – 5%

PPG SIGMATHERM™ 230

Cleaning solvent

- THINNER 90-53

ADDITIONAL DATA

| Overcoating interval for DFT up to 150 µm (6.0 mils) | | | | | | |
|--|----------|------------|-------------|-------------|-------------|-------------|
| Overcoating with... | Interval | 5°C (41°F) | 10°C (50°F) | 15°C (59°F) | 20°C (68°F) | 30°C (86°F) |
| itself | Minimum | 24 hours | 20 hours | 14 hours | 8 hours | 6 hours |
| | Maximum | 28 days | 25 days | 21 days | 14 days | 7 days |

Note:

- Surface should be dry and free from any contamination

| Curing time for DFT up to 150 µm (6.0 mils) | | | |
|---|--------------|---------------|-----------|
| Substrate temperature | Dry to touch | Dry to handle | Full cure |
| 5°C (41°F) | 28 hours | 60 hours | 7 days |
| 10°C (50°F) | 12 hours | 30 hours | 5 days |
| 15°C (59°F) | 6 hours | 15 hours | 4 days |
| 20°C (68°F) | 3 hours | 5 hours | 3 days |
| 30°C (86°F) | 2 hours | 4 hours | 48 hours |

Note:

- Adequate ventilation must be maintained during application and curing

| Pot life (at application viscosity) | |
|-------------------------------------|----------|
| Mixed product temperature | Pot life |
| 5°C (41°F) | 8 hours |
| 10°C (50°F) | 6 hours |
| 15°C (59°F) | 4 hours |
| 20°C (68°F) | 2 hours |
| 30°C (86°F) | 1 hour |



PPG SIGMATHERM™ 230

SAFETY PRECAUTIONS

- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes
- See Safety Data Sheet and product label for complete safety and precaution requirements

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

- Information sheet | Explanation of product data sheets

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgmc.com. The English text of this sheet shall prevail over any translation thereof.

