

# SIGMATHERM™ 230

## DESCRIPTION

Two-component, high-build, heat-resistant epoxy phenol novolac coating

## PRINCIPAL CHARACTERISTICS

- Provides a corrosion resistant barrier on carbon steel and stainless steel under thermal insulation
- Suitable as heat resistant system under insulation up to 230°C (450°F)
- Suitable for use in cryogenic conditions
- Passes cryogenic cyclic test down to -196°C (-321°F)
- Excellent protection and resistance against corrosion and severe chemicals
- Excellent resistance to thermal shock during rapid wet & dry cycling
- Meets CS-1, 3 and 4 for carbon steels under thermal insulation according to NACE SP0198-10
- Meets SS-1, 2 and 3 for stainless steels under thermal insulation according to NACE SP0198-10
- No post-curing is required to obtain mechanical strength
- Can be applied on hot substrate up to 150°C (302°F), please contact your PPG representative for detail

## COLOR AND GLOSS LEVEL

- Pink, gray
- Eggshell

Note: Epoxy coatings will chalk and fade upon exposure to sunlight, elevated temperatures, or chemical exposure. Discoloration and normal chalking does not impact performance. Light colors will darken over time. Some batch-to-batch variation in color is to be expected. Color matches are approximate.

## BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.7 kg/l (14.2 lb/US gal)
Volume solids	68 ± 2%
VOC (Supplied)	Directive 2010/75/EU, SED: max. 195.0 g/kg max. 329.0 g/l (approx. 2.7 lb/US gal) EPA Method 24: 310.0 g/ltr (2.6 lb/USgal)
Recommended dry film thickness	100 - 150 µm (4.0 - 6.0 mils)
Theoretical spreading rate	4.5 m <sup>2</sup> /l for 150 µm (182 ft <sup>2</sup> /US gal for 6.0 mils)
Dry to touch	3 hours
Overcoating Interval	Minimum: 8 hours Maximum: 14 days
Full cure after	3 days



# SIGMATHERM™ 230

## Data for mixed product

<b>Shelf life</b>	Base: at least 12 months when stored cool and dry Hardener: at least 12 months when stored cool and dry
-------------------	--

### Notes:

- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time
- To avoid crack in elevated temperature, it is recommended that the total average dry film thickness not exceed 350 µm (14 mils) and locally 400 µm (16 mils)

## RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

### Substrate conditions

- Steel; blast cleaned to ISO-Sa2½, blasting profile 40 – 70 µm (1.6 – 2.8 mils)
- The substrate must be perfectly dry before and during application of SIGMATHERM 230
- Stainless steel ; degrease with solvent and sweep blast, SSPC SP-16 with blasting profile 40 – 100 µm (1.5 – 4.0 mils)

### Substrate temperature and application conditions

- Substrate temperature during application and curing should be above 5°C (41°F)
- Substrate temperature during application and curing should be at least 3°C (5°F) above dew point

## INSTRUCTIONS FOR USE

### Mixing ratio by volume: base to hardener 87:13

- The temperature of the mixed base and hardener should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
- Adding too much thinner results in reduced sag resistance
- Thinner should be added after mixing the components

### Induction time

Allow induction time before use

Mixed product induction time	
Mixed product temperature	Induction time
5°C (41°F)	20 minutes
10°C (50°F)	15 minutes
15°C (59°F)	10 minutes

### Pot life

2 hours at 20°C (68°F)

Note: See ADDITIONAL DATA – Pot life



# SIGMATHERM™ 230

## Air spray

### **Recommended thinner**

THINNER 91-92 for ambient temperature ; THINNER 21-25 for application to hot surfaces

### **Volume of thinner**

5 - 10%, depending on required thickness and application conditions

### **Nozzle orifice**

2.0 mm (approx. 0.079 in)

### **Nozzle pressure**

0.3 MPa (approx. 3 Bar; 44 p.s.i.)

---

## Airless spray

### **Recommended thinner**

THINNER 91-92 for ambient temperature ; THINNER 21-25 for application to hot surfaces

### **Volume of thinner**

5 - 10%, depending on required thickness and application conditions

### **Nozzle orifice**

Approx. 0.46 – 0.53 mm (0.018 – 0.021 in)

### **Nozzle pressure**

15.0 MPa (approx. 150 bar; 2176 p.s.i.)

---

## Brush/roller

### **Recommended thinner**

THINNER 91-92

### **Volume of thinner**

0 - 5%

---

## Cleaning solvent

THINNER 90-53

---

# SIGMATHERM™ 230

## ADDITIONAL DATA

Overcoating interval for DFT up to 150 µm (6.0 mils)						
Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	15°C (59°F)	20°C (68°F)	30°C (86°F)
itself	Minimum	24 hours	20 hours	14 hours	8 hours	6 hours
	Maximum	28 days	25 days	21 days	14 days	7 days

Note: Surface should be dry and free from any contamination

Curing time for DFT up to 150 µm (6.0 mils)			
Substrate temperature	Dry to touch	Dry to handle	Full cure
5°C (41°F)	28 hours	60 hours	7 days
10°C (50°F)	12 hours	30 hours	5 days
15°C (59°F)	6 hours	15 hours	4 days
20°C (68°F)	3 hours	5 hours	3 days
30°C (86°F)	2 hours	4 hours	48 hours

Note: Adequate ventilation must be maintained during application and curing (please refer to INFORMATION SHEETS 1433 and 1434)

Pot life (at application viscosity)	
Mixed product temperature	Pot life
5°C (41°F)	8 hours
10°C (50°F)	6 hours
15°C (59°F)	4 hours
20°C (68°F)	2 hours
30°C (86°F)	1 hour

## SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

## WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.



# SIGMATHERM™ 230

## REFERENCES

• CONVERSION TABLES	INFORMATION SHEET	1410
• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431
• SAFE WORKING IN CONFINED SPACES	INFORMATION SHEET	1433
• DIRECTIVES FOR VENTILATION PRACTICE	INFORMATION SHEET	1434
• CLEANING OF STEEL AND REMOVAL OF RUST	INFORMATION SHEET	1490
• SPECIFICATION FOR MINERAL ABRASIVES	INFORMATION SHEET	1491
• RELATIVE HUMIDITY – SUBSTRATE TEMPERATURE – AIR TEMPERATURE	INFORMATION SHEET	1650

## WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

## LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at [www.ppgpmc.com](http://www.ppgpmc.com). The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

