

# NOVAGUARD™ 810 ER

## DESCRIPTION

Two-component, solvent-free, amine rapid-cured novolac phenolic epoxy coating

## PRINCIPAL CHARACTERISTICS

- Rapid cure and return-to-service
- Cures at temperatures down to -7°C (20°F)
- Good chemical resistance against a wide range of chemicals and solvents
- Smooth finish and light color for easy cleaning and inspection
- Hydrocarbon immersion after only 1 day at 20°C (68°F)
- Qualification for MIL-PRF-23236D Type VII: Class 5/18, 7/18, 17/18, 19/18
- Meets NSF/ANSI Standard 61 for potable water when applied and used as described on <http://info.nsf.org/>

## COLOR AND GLOSS LEVEL

- Cream OAP (Off-white base + Yellow cure), Green OAP (Green base + Neutral cure), Red Oxide OAP (Red oxide base + Neutral cure), Off-white OAP (Off-white base + Neutral cure)
- Semi-gloss

## BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Volume solids	100%
VOC (Supplied)	EPA Method 24: 61.0 g/ltr (0.5 lb/USgal)
Recommended dry film thickness	20.0 - 40.0 mils (500 - 1000 µm) depending on system
Theoretical spreading rate	80 ft <sup>2</sup> /US gal for 20.0 mils (2.0 m <sup>2</sup> /l for 500 µm)
Dry to touch	2 hours
Overcoating Interval	Minimum: 6 hours Maximum: 28 days
Full cure after	48 hours
Shelf life	Base: at least 24 months when stored cool and dry Hardener: at least 24 months when stored cool and dry

### Notes:

- Volume solids based on oven solids testing is 93%
- See ADDITIONAL DATA - Spreading rate and film thickness
- See ADDITIONAL DATA - Overcoating intervals
- See ADDITIONAL DATA - Curing time

# NOVAGUARD™ 810 ER

## RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

### Substrate conditions

- Steel; blast cleaned to a minimum of SSPC-SP10 or ISO-SA2½ , blasting profile 50 – 125 µm (5.0 mils) (2.0 – 5.0 mils)
- 

### Substrate temperature and application conditions

- Substrate temperature during application and curing down to -7°C (20°F) is acceptable; provided the substrate is free from ice and dry
  - Substrate temperature during application and curing should be at least 3°C (5°F) above dew point
- 

## INSTRUCTIONS FOR USE

### Mixing ratio by volume: base to hardener 4:1

- The temperature of the mixed base and hardener should preferably be above 75°F (24°C)
  - At lower temperature, the viscosity will be too high for spray application
  - No thinner should be added
  - For recommended application instructions, see working procedure
- 

### Airless spray

- Use heated, airless spray, plural-component equipment
- In-line heating or insulated hoses may be necessary to avoid cooling down of paint in hoses at low air temperature
- Length of hoses should be as short as possible

### Recommended thinner

No thinner should be added

### Nozzle orifice

Approx. 0.48 – 0.53 mm (0.019 – 0.021 in)

### Nozzle pressure

3500 - 4250 p.s.i. (approx. 242 - 293 bar; 24.1 - 29.3 MPa)

### Notes:

- For optimal flow and sag resistance on vertical areas having a substrate temperature above 20°C (68°F), the paint temperature (spray fan) should be kept typically above 30°C (86°F)
  - For optimal flow and leveling on horizontal areas having a substrate temperature below 20°C (68°F), the paint temperature (spray fan) should be kept typically below 30°C (86°F). The distance between the spray gun and the substrate should be low, for example less than 50 cm (20 inch)
-

# NOVAGUARD™ 810 ER

## Cleaning solvent

- THINNER 90-53 or THINNER 90-83

## CLEANING PROCEDURE

- All application equipment must be cleaned immediately after use
- Paint inside the spraying equipment must be removed before the pot life has been expired

## ADDITIONAL DATA

### Measuring wet film thickness

- A difference is often obtained between the measured apparent WFT and the real applied WFT. This is due to the thixotropy and the surface tension of the paint, which retards the release of air, trapped in the paint film for some time.
- Polymer shrinkage will also affect the final dry film thickness reading. A practical volume solids of 93% is therefore used for estimation of spreading rate

### Measuring dry film thickness

- The DFT should be measured using a calibration foil of known thickness placed in between the coating and the measuring device

Spreading rate and film thickness	
DFT	Theoretical spreading rate
20.0 mils (500 µm)	80 ft <sup>2</sup> /US gal (2.0 m <sup>2</sup> /l)
30.0 mils (750 µm)	53 ft <sup>2</sup> /US gal (1.3 m <sup>2</sup> /l)

Overcoating interval for DFT up to 1000 µm (40.0 mils)							
Overcoating with...	Interval	-5°C (23°F)	0°C (32°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself	Minimum	48 hours	24 hours	12 hours	6 hours	4 hours	3 hours
	Maximum	28 days	28 days	28 days	22.5 days	14 days	7 days

Note:

- Surface should be dry and free from any contamination and ice



# NOVAGUARD™ 810 ER

Curing time for DFT up to 1000 µm (40.0 mils)		
Substrate temperature	Dry to handle	Full cure
40°F (4°C)	18 hours	5 days
50°F (10°C)	12 hours	3 days
68°F (20°C)	6 hours	48 hours
86°F (30°C)	4.5 hours	30 hours
104°F (40°C)	less than 3 hours	24 24 - 48 hours

Notes:

- Adequate ventilation must be maintained during application and curing
- For storage and transport of drinking water the recommended working procedure should be followed
- Holiday test can be done after dry to handle time

Pot life (at application viscosity)	
Mixed product temperature	Pot life
77°F (25°C)	15 minutes
110°F (43°C)	7 minutes

Note:

- It is recommended to use plural airless equipment due to the short pot life

### Product Qualifications

- Compliant with EI 1541, Performance requirements for protective coating systems used in aviation fuel storage tanks and piping

### SAFETY PRECAUTIONS

- Although this is a solvent-free paint, care should be taken to avoid inhalation of spray mist, as well as contact between the wet paint and exposed skin or eyes
- For paint and recommended thinners see INFORMATION SHEET 1411 and relevant Material Safety Data Sheets
- No solvent present; however, spray mist is not harmless, a fresh air mask should be used during spraying
- Ventilation should be provided in confined spaces to maintain good visibility

### WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.



# NOVAGUARD™ 810 ER

## REFERENCES

- Information sheet | Explanation of product data sheets
- 

## WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

---

## LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at [www.ppgpmc.com](http://www.ppgpmc.com). The English text of this sheet shall prevail over any translation thereof.

---

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

