

SIGMAGUARD™ 603

DESCRIPTION

Two-component, solvent-free, amine-cured epoxy coating

PRINCIPAL CHARACTERISTICS

- One-coat protection for maintenance or major refurbishment of ballast water tanks and crude oil tanks
- Tolerant to marginal surface preparation
- Good corrosion resistance
- Can be applied by heavy-duty, single-feed, airless spray equipment (60:1)
- Reduced explosion risk and fire hazard
- Good visibility due to light color

COLOR AND GLOSS LEVEL

- Offwhite, light gray
- Gloss

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.3 kg/l (10.8 lb/US gal)
Volume solids	100%
VOC (Supplied)	Directive 1999/13/EC, SED: max. 111.0 g/kg max. 144.0 g/l (approx. 1.2 lb/US gal)
Recommended dry film thickness	300 µm (12.0 mils)
Theoretical spreading rate	3.3 m ² /l for 300 µm (134 ft ² /US gal for 12.0 mils)
Dry to touch	8 hours
Overcoating Interval	Minimum: 24 hours Maximum: 20 days
Full cure after	5 days
Shelf life	Base: at least 24 months when stored cool and dry Hardener: at least 24 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time

SIGMAGUARD™ 603

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Steel; blast cleaned to ISO-Sa2½, blasting profile 50 – 100 µm (2.0 – 4.0 mils)
- Steel; blast cleaned to ISO-Sa2 or power tool cleaned to ISO-St2 for good corrosion protection
- Coated steel; hydro jetted to VIS WJ2/3 L (blasting profile 50 – 100 µm (2.0 – 4.0 mils))
- Previous coat of approved coating must be dry and free from any contamination
- Pitted steel; blast cleaned to ISO-Sa2½ is recommended
- Suitable primer; SIGMACOVER 280
- Suitable for damp surfaces

Substrate temperature and application conditions

- Substrate temperature during application and curing should be above 5°C (41°F)
- There are no restrictions regarding dew point temperature and relative humidity

SYSTEM SPECIFICATION

- SIGMAGUARD 603: 1 x 300 µm (12.0 mils)

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 80:20 (4:1)

- The temperature of the mixed base and hardener should preferably be at least 20°C (68°F)
- At lower temperature, the viscosity will be too high for spray application
- No thinner should be added

Induction time

None

Pot life

1 hour at 20°C (68°F)

Note: See ADDITIONAL DATA – Pot life

SIGMAGUARD™ 603

Airless spray

- Use heavy-duty, single-feed, airless spray equipment, preferably 60:1 pump ratio and suitable high-pressure hoses/in-line heating or insulated hoses may be necessary to avoid cooling down of paint in hoses at low air temperature
- In-line heating or insulated hoses may be necessary to avoid cooling down of paint in hoses at low air temperature
- Application with 45:1 airless spray equipment is possible, provided in-line, heated high-pressure hoses are used
- Length of hoses should be as short as possible

Recommended thinner

No thinner should be added

Nozzle orifice

Approx. 0.53 – 0.64 mm (0.021 – 0.025 in)

Nozzle pressure

At 20°C (68°F) paint temperature min. 28.0 MPa (approx. 280 bar; 4061 p.s.i.). At 30°C (86°F) min. 22.0 MPa (approx. 220 bar; 3191 p.s.i.)

Note: In case of using 45:1 airless spray equipment, the paint must be heated to approximately 30°C (86°F) in order to obtain the right application viscosity

Brush/roller

- For stripe coating and spot repair only

Recommended thinner

No thinner should be added

Cleaning solvent

THINNER 90-53 or THINNER 90-83

Note: All application equipment must be cleaned immediately after use. Paint inside the spraying equipment must be removed before the pot life has been expired.

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
300 µm (12.0 mils)	3.3 m ² /l (134 ft ² /US gal)
400 µm (16.0 mils)	2.5 m ² /l (100 ft ² /US gal)

Note: Maximum DFT when brushing: 200 µm (8.0 mils)

Measuring wet film thickness

- A difference is often obtained between the measured apparent WFT and the real applied WFT. This is due to the thixotropy and the surface tension of the paint, which retards the release of air, trapped in the paint film for some time
- Recommendation is to apply a WFT, which is equal to the specified DFT plus 60 µm (2.4 mils)

SIGMAGUARD™ 603

Maximum dry film thickness

- Because of low initial hardness the DFT cannot be measured within some days, due to the penetration of the measuring device into the soft paint film
- The DFT should be measured using a calibration foil of known thickness placed in between the coating and the measuring device

Overcoating interval for DFT up to 300 µm (12.0 mils)

Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)
itself	Minimum	3.5 days	36 hours	24 hours	16 hours
	Maximum	20 days	20 days	20 days	14 days

Note: Surface should be dry and free from any contamination

Curing time for DFT up to 300 µm (12.0 mils)

Substrate temperature	Dry to handle	Service- water immersion	Full cure
5°C (41°F)	60 hours	10 days	15 days
10°C (50°F)	30 hours	5 days	7 days
20°C (68°F)	16 hours	4 days	5 days
30°C (86°F)	10 hours	48 hours	3 days

Note: Adequate ventilation must be maintained during application and curing (please refer to INFORMATION SHEETS 1433 and 1434)

Pot life (at application viscosity)

Mixed product temperature	Pot life
20°C (68°F)	1 hour
30°C (86°F)	45 minutes

Note: Due to exothermic reaction, temperature during and after mixing may increase

SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- Although this is a solvent-free paint, care should be taken to avoid inhalation of spray mist, as well as contact between the wet paint and exposed skin or eyes
- No solvent present; however, spray mist is not harmless, a fresh air mask should be used during spraying
- Ventilation should be provided in confined spaces to maintain good visibility

SIGMAGUARD™ 603

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

• CONVERSION TABLES	INFORMATION SHEET	1410
• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431
• SAFE WORKING IN CONFINED SPACES	INFORMATION SHEET	1433
• DIRECTIVES FOR VENTILATION PRACTICE	INFORMATION SHEET	1434
• CLEANING OF STEEL AND REMOVAL OF RUST	INFORMATION SHEET	1490
• SPECIFICATION FOR MINERAL ABRASIVES	INFORMATION SHEET	1491
• RELATIVE HUMIDITY – SUBSTRATE TEMPERATURE – AIR TEMPERATURE	INFORMATION SHEET	1650

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

