

CENTRIFUGON EAP EVO

DESCRIPTION

Two-component, polyamide-cured phenolic epoxy coating

PRINCIPAL CHARACTERISTICS

- Suitable for atmospheric exposure conditions
- Resists accidental contact with diluted acids and bases, as well as aromatic, aliphatic and chlorinated solvents
- PIA/PIB/PIC/PID qualified by EDF for use in nuclear power plants
- EDF/ORANO (ex AREVA/COGEMA) and CEA-approved product

COLOR AND GLOSS LEVEL

- A wide range of colors
- Gloss

Note:

- Two coats may be required for low opacity colors

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.26 kg/l (10.52 lb/US gal)
Volume solids	62 ± 2%
VOC (Supplied)	Directive 2010/75/EU, SED: max. 305.0 g/kg max. 385.0 g/l (approx. 3.2 lb/US gal)
Recommended dry film thickness	40 - 60 µm (1.6 - 2.4 mils) depending on system
Theoretical spreading rate	15.5 m ² /l for 40 µm (622 ft ² /US gal for 1.6 mils) 10.3 m ² /l for 60 µm (414 ft ² /US gal for 2.4 mils)
Dry to touch	3 hours
Dry to handle	12 hours
Overcoating Interval	Minimum: 12 hours Maximum: 12 months
Shelf life	Base: at least 24 months when stored cool and dry Hardener: at least 24 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals



CENTRIFUGON EAP EVO

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Steel; blast cleaned to ISO Sa2½, blasting profile 40 – 70 µm (1.6 – 2.8 mils)
 - Careful dust-removal in line with standard ISO 8502-1 to 4
 - Concrete must be sound, dry, free from laitance and any contamination
 - Compatible previous coat must be dry and free from any contamination
 - The substrate must always be sound, dry and clean, in line with DTU 59-1 and DTU 59-3, before application
-

Substrate temperature and application conditions

- Substrate temperature during application and curing should be above 5°C (41°F)
 - Substrate temperature during application and curing should be at least 3°C (5°F) above dew point
 - Relative humidity during application and curing should not exceed 80%
 - Substrate temperature during application should not exceed 35°C (95°F)
-

SYSTEM SPECIFICATION

- Can be applied on primers CENTREPOX N EVO, CENTREPOX PZ EVO, ENDUIT PANTOXY NF
-

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 2.33:1

- The temperature of the mixed base and hardener should be above 10°C (50°F), otherwise extra thinner may be required to obtain application viscosity
 - Adding too much thinner results in reduced sag resistance and slower cure
 - Thinner should be added after mixing the components
-

Induction time

0 minute

Note:

- No induction time required
-

Pot life

8 hours at 20°C (68°F)

CENTRIFUGON EAP EVO

Air spray

Recommended thinner

THINNER 91-92 or DILUANT N°1 Bis

Volume of thinner

15 - 20%, depending on required thickness and application conditions

Nozzle orifice

1.0 - 2.0 mm (approx. 0.040 - 0.079 in)

Nozzle pressure

0.3 - 0.4 MPa (approx. 3 - 4 bar; 44 - 58 p.s.i.)

Airless spray

Recommended thinner

THINNER 91-92 or DILUANT N°1 Bis

Volume of thinner

15 - 20%, depending on required thickness and application conditions

Nozzle orifice

Approx. 0.38 - 0.43 mm (0.015 - 0.017 in)

Nozzle pressure

18.0 - 20.0 MPa (approx. 180 - 200 bar; 2611 - 2901 p.s.i.)

Brush/roller

- For stripe coating and spot repair only

Recommended thinner

THINNER 91-92 or DILUANT N°1 Bis

Volume of thinner

0 - 10%

Cleaning solvent

- THINNER 91-92 or DILUANT N°1 Bis
-

CENTRIFUGON EAP EVO

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
40 µm (1.6 mils)	15.5 m ² /l (622 ft ² /US gal)
60 µm (2.4 mils)	10.3 m ² /l (414 ft ² /US gal)

Overcoating interval for DFT up to 50 µm (2.0 mils)		
Overcoating with...	Interval	20°C (68°F)
itself	Minimum	12 hours
	Maximum	12 months

Note:

- Surface should be dry and free from any contamination

SAFETY PRECAUTIONS

- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes
- See Safety Data Sheet and product label for complete safety and precaution requirements

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

- Information sheet | Explanation of product data sheets

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.



CENTRIFUGON EAP EVO

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

