

SIGMAFAST™ 278 D

(Standard bases with SIGMAFAST 278 D hardener)

DESCRIPTION

Two-component, high solids, zinc phosphate epoxy primer and buildcoat

PRINCIPAL CHARACTERISTICS

- Epoxy primer or buildcoat in protective coating systems
- Excellent corrosion resistance in atmospheric exposure
- Cures at temperatures down to -5°C (23°F)
- Speed curing in steel fabrication
- Easy application by airless spray
- Wide application range
- ACQPA 27962-certified

COLOR AND GLOSS LEVEL

- Selected range of colors available
- Semi-gloss

Notes:

- Epoxy coatings will chalk and fade upon exposure to sunlight, elevated temperatures, or chemical exposure. Discoloration and normal chalking do not impact performance. Light colors will darken over time. Some batch-to-batch variation in color is to be expected. Color matches are approximate.
- The addition of a UV stable topcoat should be considered when using epoxy coatings in cosmetic areas

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.5 kg/l (12.5 lb/US gal)
Volume solids	80 ± 2%
VOC (Supplied)	Directive 2010/75/EU, SED: max. 153.0 g/kg UK PG 6/23(92) Appendix 3: max. 230.0 g/l (approx. 1.9 lb/US gal) EPA Method 24: 220.0 g/ltr (1.8 lb/USgal)
Recommended dry film thickness	75 - 250 µm (3.0 - 10.0 mils)
Theoretical spreading rate	6.4 m ² /l for 125 µm (257 ft ² /US gal for 5.0 mils)
Dry to touch	1 hour
Overcoating Interval	Minimum: 2 hours Maximum: 28 days
Full cure after	4 days
Shelf life	Base: at least 24 months when stored cool and dry Hardener: at least 24 months when stored cool and dry

Notes:



SIGMAFAST™ 278 D

(Standard bases with SIGMAFAST 278 D hardener)

- See ADDITIONAL DATA – Spreading rate and film thickness
 - See ADDITIONAL DATA – Overcoating intervals
 - See ADDITIONAL DATA – Curing time
-

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- Apply this product to the specified thickness as soon as possible after the surface is prepared
-

Substrate conditions

- Steel; blast cleaned to ISO-Sa2½ or minimum SSPC SP-6, blasting profile 40 – 70 µm (1.6 – 2.8 mils) or power tool cleaned to minimum ISO-St3 / SSPC SP3
-

Primed steel or previous coat

- Previous suitable coat must be dry and free from any contamination
 - Surface of previous coat should be sufficiently roughened if necessary
 - When applied to zinc silicate, a mist coat and full coat technique is required
-

Galvanized steel

- The surface must be properly prepared, dry, clean and free of any contamination
 - The surface should be sufficiently roughened by sweep blasting to achieve a uniform matt appearance
 - Sweep blast in accordance with the SSPC-SP 16 guidelines
-

Stainless steel

- The surface must be properly prepared, dry, clean and free of any contamination
 - The surface should be sufficiently roughened by sweep blasting with inert non-metallic abrasives
 - Sweep blast in accordance with the SSPC-SP 16 guidelines
-

Thermal Sprayed Metallization (TSM)

- Surface must be dry and free from any contamination
 - The mist coat / full coat technique is required. See mist coat thinning recommendation in the Instructions For Use part below
-

Substrate temperature and application conditions

- Substrate temperature during application and curing should be at least 3°C (5°F) above dew point
 - Substrate temperature during application and curing down to -5°C (23°F) is acceptable; provided the substrate is free from ice and dry
-

SIGMAFAST™ 278 D

(Standard bases with SIGMAFAST 278 D hardener)

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 3:1

- The temperature of the paint should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
 - Adding too much thinner results in reduced sag resistance and slower cure
 - Thinner should be added after mixing the components
-

Pot life

1 hour at 20°C (68°F)

Air spray

Recommended thinner

THINNER 91-92

Volume of thinner

0 - 10%, depending on required thickness and application conditions

Nozzle orifice

1.7 – 2.0 mm (approx. 0.070 – 0.079 in)

Nozzle pressure

0.3 - 0.4 MPa (approx. 3 - 4 bar; 44 - 58 p.s.i.)

Airless spray

Recommended thinner

THINNER 91-92

Volume of thinner

0 - 10%, 30 - 50% when mist coat applied

Nozzle orifice

Approx. 0.46 – 0.53 mm (0.018 – 0.021 in)

Nozzle pressure

20.0 - 25.0 MPa (approx. 200 - 250 bar; 2901 - 3626 p.s.i.)

SIGMAFAST™ 278 D

(Standard bases with SIGMAFAST 278 D hardener)

Brush/roller

Recommended thinner

THINNER 91-92

Volume of thinner

0 – 5%

Notes:

- A roller suitable for epoxy application must be used
- Application by roller will leave roller marking and is suitable for minimum DFT requirements only
- Application by brush may show brush marking, due to the thixotropic nature of the paint and is most suitable to small areas, tight angle areas or for stripe coating or touch-up

Cleaning solvent

- THINNER 90-53

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
75 µm (3.0 mils)	10.7 m ² /l (428 ft ² /US gal)
125 µm (5.0 mils)	6.4 m ² /l (257 ft ² /US gal)
250 µm (10.0 mils)	3.2 m ² /l (128 ft ² /US gal)

Overcoating interval for DFT up to 125 µm (5.0 mils)						
Overcoating with...	Interval	-5°C (23°F)	0°C (32°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)
various epoxy coatings, polyurethane coatings, and PSX	Minimum	24 hours	14 hours	4 hours	2 hours	1 hour
	Maximum	2.5 months	2 months	1.5 months	1 month	21 days

Note:

- The surface must be dry and free from all contaminations (oil, grease, chalking, etc...) which would require cleaning and/or abrading

Curing time for DFT up to 125 µm (5.0 mils)			
Substrate temperature	Dry to touch	Dry to handle	Full cure



SIGMAFAST™ 278 D

(Standard bases with SIGMAFAST 278 D hardener)

Curing time for DFT up to 125 µm (5.0 mils)			
-5°C (23°F)	16 hours	38 hours	N/A
0°C (32°F)	11 hours	24 hours	21 days
10°C (50°F)	4 hours	8 hours	8 days
20°C (68°F)	2 hours	4 hours	4 days
30°C (86°F)	1 hour	2 hours	3 days

Note:

- Adequate ventilation must be maintained during application and curing

Pot life (at application viscosity)	
Mixed product temperature	Pot life
0°C (32°F)	10 hours
10°C (50°F)	3 hours
20°C (68°F)	1 hour
30°C (86°F)	30 minutes

SAFETY PRECAUTIONS

- See Safety Data Sheet and product label for complete safety and precaution requirements
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

- Information sheet | Explanation of product data sheets

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.



SIGMAFAST™ 278 D

(Standard bases with SIGMAFAST 278 D hardener)

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

