

## CA1800CX VOC Compliant Thinner

### Product description

CA1800CX thinner can be used with Desoprime™ HS primers and Desothane® HS topcoats to improve spray characteristics and film appearance. CA1800CX can be used in hot weather conditions (above 29°C/85°F) to increase the wet edge of the coating.

- Zero VOC per EPA method 24
- Improves the spray characteristics at high temperatures
- Compatible with Desothane® HS topcoats
- Compatible with Desoprime™ HS primers
- Can be used in all environments including high temperature and humidity
- Service temperature -54°C to 177°C (-65°F to 350°F)

### Specifications

CA1800CX is qualified to the following specifications:

- BAMS 565-009

CA1800CX is listed on the following application specification:

- GAMPS 3209

*Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.*

### **Product compatibility:**

CA1800CX is compatible with the following primer specifications:

- 299-947-322 Type I
- AMS 3095
- A2MS 565-008
- BAMS 565-008
- BMS 10-72 Ty VIII & IX Class NC
- BMS 10-79 Type II & III
- BMS 10-103 Type I Grade A
- BMS 10-118 Type I & II Grade B
- BMS 10-123 Type I Grade B
- CMS-CT-201 Cl A & B Gr A & B
- CMS-CT-206 Type I Class A
- DHMS C4.01 Type 3 Grade A
- DHMS C4.18 Ty III Cl A Gr B
- GAMPS 3103
- GP110AEE
- HMS 16-1738
- HMS 16-2122
- MEP 10-060 Ty I & II Class A & B
- MEP 10-068 Class A & B
- MEP 10-070
- MM1275 Type I & II
- MS100016E Class S
- PWA 36525 Type 1
- SMS-111204 Ty 1 Cl 1 Form 1&2
- SMS-111207 Type 7
- STMGK 189
- TCE-M-20710-14
- VMS C4.01 Type 3 Grade A
- VMS C4.18 Ty 3 Class A Grade B

# CA1800CX VOC Compliant Thinner

CA1800CX is compatible with the following topcoat specifications:

- AMS 3095
- A2MS 565-002
- A2MS 565-009
- A2MS 565-018
- A2MS 565-019
- BAMS 565-002
- BAMS 565-009
- BAMS 565-018
- BAMS 565-019
- BMS 10-60 Type II Cl B Gr D
- BMS 10-72 Type VIII
- BMS 10-125 Type III Grade D
- BMS 10-126 Type I Grade D
- CMFS037
- CMFS038
- CMS-CT-101 Type I
- DHMS C4.04 Type VI Cl B Gr B
- DMS 2143 Ty 1 Cl 1 Comp C
- GAMPS 3209
- GP110AEE
- MEP 10-069
- MM1276 Type II
- MM1279
- MS100029E Class HS
- PWA 567
- RMS 430 Type II
- RPS 13.97
- SMS-111207 Type 1
- VMS C4.04 Type VI Cl B Gr B

## Instructions for use



### **Mixing instructions:**

CA1800CX thinner must be added at the time the base component and activator component are mixed together. Mix with Desothane® HS topcoat and Desoprime™ HS primer as directed on the can label.

Add CA1800CX may be added until the desired viscosity is achieved, as long as the volume doesn't exceed the maximum listed in the note below.

CA1800CX cannot be used to reclaim a mixed coating that is near the end of its pot life.

*Note: Do not add more than 25% by volume of CA1800CX to the mixed epoxy primer.*

*Note: Do not add more than 25% by volume of CA1800CX to the mixed polyurethane topcoat.*

*Note: Exceeding the recommended thinning level will cause runs and sags. When using CA1800CX during high temperature the wet edge of the coating may be reduced.*

*Note: It is important to condition the paint for 24 hours prior to mixing by placing all materials in the shop or hangar, with ambient temperatures between 13° and 35°C (55° to 95°F). The minimum temperature of the paint components should be 13°C (55°F) prior to mixing.*

# CA1800CX VOC Compliant Thinner

## Physical properties (product)



**Color:** Clear



**VOC (EPA method 24):**

CA1800CX

0 grams/liter



**Flash point closed cup:**

CA1800CX

-10°C (15°F)

### **Shelf life:**


12 months from date of manufacture to most OEM material specifications. Consult the specification to verify shelf life requirements.

24 months from date of manufacture for PRC-DeSoto Standard.

*Note: Shelf life is provided for the original, unopened containers.*

*Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.*

## Storage recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

*Note: When procuring to a qualified material specification, follow those storage instructions.*

## Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

# CA1800CX VOC Compliant Thinner

**For industrial use only. Keep away from children.**

**Additional information can be found at: [www.ppgaerospace.com](http://www.ppgaerospace.com)**

**For sales and ordering information call the local PPG office at the numbers listed below:**

## **Asia Pacific**

### **ASC – Australia**

Tel 61 (3) 9335 1557  
Fax 61 (3) 9335 3490

### **ASC – Japan**

Tel 81 561 35 5200  
Fax 81 561 35 5201

### **ASC – South East Asia**

Tel 65 6861 1119  
Fax 65 6861 6162

### **ASC – Suzhou**

Tel (86-512) 6661 5858  
Fax (86-512) 6661 6868

### **ASC – Tianjin**

Tel (86-022) 2482 8625  
Fax (86-022) 2482 8600

## **Americas**

1 (818) 362-6711 or 1-800-AEROMIX

## **Europe and Middle East**

### **ASC – Central Europe**

Tel 49 (40) 742 193 10  
Fax 49 (40) 742 139 69

### **ASC – Middle East & India**

Tel (971) 4 883 9666  
Fax (971) 4 883 9665

### **ASC – North Europe**

Tel 44 (0) 1388 770222  
Fax 44 (0) 1388 770288

### **ASC – South Europe**

Tel 33 (0) 235 53 43 71  
Fax 33 (0) 235 53 54 44

**Desoprime and Desothane are trademarks of PRC-DeSoto International, Inc.**

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

*This document has been reviewed by the PPG Aerospace Export Control Department and has been determined to contain only EAR99 controlled data*

PRC-DeSoto International, Inc.  
12780 San Fernando Road  
Sylmar, CA 91342

[www.ppgaerospace.com](http://www.ppgaerospace.com)

Issue Date: 9/21  
Lit: 2029