

Etch Prime - Gray

SXA1031

ONECHOICE® SXA1031 Etch Prime - Gray is designed to provide excellent adhesion and corrosion resistance to properly prepared steel and aluminum.



Features & Benefits

- Packaged in aerosol cans
- Ready to spray
- Offers superior adhesion
- May be used for spot repairs
- Non-Chrome
- Lower finishing costs

Compatible Surfaces

- Properly cleaned and sanded steel
- Properly cleaned and sanded galvanized metal
- Properly cleaned and sanded stainless steel
- Properly cleaned and sanded aluminum

Compatible Products

- DELTRON® NXT Basecoat
- DELTRON® 2000 (DBC) Basecoat
- ENVIROBASE® High Performance Waterborne Basecoat
- *Deltron* Undercoats
- *Envirobase* High Performance Undercoats

Directions for Use:**Surface Preparation:**

- Clean surface thoroughly with appropriate PPG wax and grease remover.
- Sand with 320 grit paper. Blow off and clean again with PPG wax and grease remover.

Mix Ratio:

SXA1031 is Ready to Spray

Agitate thoroughly. Shake can vigorously for one minute after mixing ball rattles to ensure color uniformity and to prevent clogging. For best results, use only when can temperature is approximately 70°F (21°C).

Application:**Apply:** 2 - 3 medium coats

If clogging develops, remove spray button with a twisting motion and clean with material compliant with VOC regulations in your area. Do not stick pin or other object into can. Gently replace spray button with top of can and spray button pointed away from you.



Note: When finished spraying aerosol products, hold can upside down and spray until valve is cleared. This will prevent clogging of the internal valve.

Dry Times:**Between coats:** 3 - 5 minutes**Dry to touch:** 15 minutes**Dry to sand:** 30 minutes**Note:** Must be sanded and re-coated if not top coated within 24 hours.**Note:**

When the material in the aerosol can is spent, turn can upside down and depress the nozzle until all propellant is exhausted. Place empty can or cans that are no longer to be used into properly labeled metal containers. The waste containers should be managed as a hazardous waste pursuant to local, state and federal regulations.

Technical Data:**Properties:****RTS Combinations:****SXA1031**

Volume Ratio	As is (aerosol)
Applicable Use Category	Auto Body Primer
VOC Actual (g/L)	495
VOC Actual (lbs./gal.)	4.13
VOC Regulatory (less water less exempt) (g/L)	640
VOC Regulatory (less water less exempt) (lbs./gal.)	5.34
Solids by weight (RTS)	14.3
Solids by volume (RTS)	11.7
Sq. Ft. Coverage / US Gal., 0.5 mil at 100% transfer efficiency	187

See Material Safety Data Sheet and Labels for additional safety information and handling instructions.

EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION (412) 434-4515; IN CANADA (514) 645-1320

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the public. Products mentioned may be hazardous and should only be used according to directions, while observing precautions and warning statements listed on label. Statements and methods described are based upon the best information and practices known to PPG Industries. Procedures for applications mentioned are suggestions only and are not to be construed as representations or warranties as to performance, results, or fitness for any intended use, nor does PPG Industries warrant freedom from patent infringement in the use of any formula or process set forth herein.

We protect and
beautify the world™PPG Industries
19699 Progress Drive
Strongsville, OH 44149PPG Canada Inc.
2301 Royal Windsor Drive Unit #6
Mississauga, Ontario Canada L5J 1K5

© 2024 PPG Industries, Inc. All rights reserved
Deltron, Envirobase, OneChoice, and The PPG Logo are registered trademarks and *We protect and beautify the world* is a trademark of PPG Industries Ohio, Inc.