

# AQUAPON® | 97-670 VOC SERIES

## DESCRIPTION

Three-component, zinc rich epoxy

## PRINCIPAL CHARACTERISTICS

- >90% zinc in dry film
- Provides outstanding corrosion resistance
- Fast dry times for rapid topcoating

## COLOR AND GLOSS LEVEL

- Reddish gray, Green
- Flat

## BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Three
Volume solids	60 ± 3%
VOC (Supplied)	max. 2.7 lb/US gal (approx. 328 g/l)
Recommended dry film thickness	3.0 - 5.0 mils (75 - 125 µm) depending on system
Theoretical spreading rate	276 ft <sup>2</sup> /US gal for 3.0 mils (6.8 m <sup>2</sup> /l for 75 µm)
Shelf life	Base: at least 36 months when stored cool and dry Hardener: at least 36 months when stored cool and dry

### Notes:

- See ADDITIONAL DATA - Overcoating intervals
- See ADDITIONAL DATA - Curing time

## RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- Coating performance is proportional to the degree of surface preparation. All previous coats must dry and free of contaminants



# AQUAPON® | 97-670 VOC SERIES

## **Steel**

- Abrasive blast with an angular abrasive to an SSPC SP-6 cleanliness or higher for optimum performance. Achieve a surface profile of 1.0 – 3.0 mils (25 – 75 µm)
- Higher surface profiles up to 5 mils (125 µm) are acceptable, but the product must be applied in a thickness great enough to achieve a minimum of 2.5 mils (65 µm) dry film thickness
- Apply this product as soon as possible to prevent blasted surface from rusting.
- Keep moisture, oil, grease, or other organic matter off surface before coating
- For touch up and repair, power tool cleaning in accordance with SSPC SP-3 is acceptable for small areas and SSPC SP-11 should be specified for large repair areas where blasting is not allowed.

---

## **Substrate temperature and application conditions**

- Surface temperature during application should be between 32°F (0°C) and 120°F (49°C)
- Surface temperature during application should be at least 5°F (3°C) above dew point
- Ambient temperature during application and curing should be between 32°F (0°C) and 100°F (38°C)
- Relative humidity during application and curing should not exceed 85%

Note: Product can be applied without accelerator at surface and air temperatures down to 32°F. Material temperature must be maintained at 40°F to 90°F at the time of application.

---

## **Warning**

Removal of old paint by sanding, scraping or other means may generate dust or fumes which contain lead. EXPOSURE TO LEAD DUST OR FUMES MAY CAUSE ADVERSE HEALTH EFFECTS, ESPECIALLY IN CHILDREN OR PREGNANT WOMEN. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted and approved (e.g., NIOSH approved) respirator and proper containment and cleanup. For additional information, contact the USEPA/Lead Information Hotline at 1-800-424-LEAD or the regional Health Canada office

---

## **SYSTEM SPECIFICATION**

- Primers: Direct to metal, can be used to touch up inorganic zincs such as METALHIDE 2000
- Topcoats: PITTGUARD 97-946, DURETHANE DTM, PITTHANE Ultra, AMERSHIELD, PSX 700, AMERCOAT 450 H, AMERLOCK 2/400, AMERCOAT 385, AMERCOAT 370, AMERCOAT 399

---

## **INSTRUCTIONS FOR USE**

### **Mix as packaged**

- Pre-mix base component with a pneumatic air mixer at moderate speeds to homogenize the container. Add hardener to base and agitate with a power mixer for 1-2 minutes until completely dispersed. Add powder component slowly under agitation until fully mixed. Strain the mixture from one container to another through a 30 mesh filter/strainer to remove any undispersed lumps

---

### **Pot life**

24 hours at 70°F (21°C)



# AQUAPON® | 97-670 VOC SERIES

---

## **Application**

- Area should be sheltered from airborne particulates and pollutants
- Ensure good ventilation during application and curing
- Provide shelter to prevent wind from affecting spray patterns

## **Material temperature**

Material temperature during application should be between 32°F (0°C) and 90°F (32°C)

---

## **Air spray**

- Separate air and fluid pressure regulators and a moisture and oil trap in the main air supply line are recommended.
- Use standard conventional equipment

## **Recommended thinner**

THINNER 21-85 (97-739) or THINNER 50-01 (AMERCOAT 12V)

## **Volume of thinner**

0 - 5%

## **Nozzle orifice**

Approx. 0.070 in (1.8 mm)

---

## **Airless spray**

- 45:1 pump or larger

## **Recommended thinner**

THINNER 21-85 (97-739) or THINNER 50-01 (AMERCOAT 12V)

## **Volume of thinner**

0 - 5%

## **Nozzle orifice**

0.017 in (approx. 0.43 mm)

---

## **Brush/roller**

- Use a high-quality natural-bristle brush. Brush application is only recommended for small touch-up and/or repair areas. Roller application is not recommended
- Ensure brush is well loaded to avoid air entrainment
- Multiple coats may be required to achieve proper film build and hiding with brush application

## **Recommended thinner**

THINNER 21-85 (97-739) or THINNER 50-01 (AMERCOAT 12V)

## **Volume of thinner**

0 - 5%



# AQUAPON® | 97-670 VOC SERIES

## Cleaning solvent

THINNER 90-58 (AMERCOAT 12) or THINNER 50-01 (AMERCOAT 12V)

## ADDITIONAL DATA

Overcoating interval for DFT up to 3.0 mils (75 µm)					
Overcoating with...	Interval	32°F (0°C)	50°F (10°C)	70°F (21°C)	90°F (32°C)
Itself and recommended topcoats	Minimum	6 hours	2 hours	1 hour	30 minutes
	Maximum	Unlimited	Unlimited	Unlimited	Unlimited

Note: Maximum interval is only unlimited when the surface is free from any contamination

Curing time for DFT up to 3.0 mils (75 µm)		
Substrate temperature	Dry to touch	Dry to handle
32°F (0°C)	1 hour	6 hours
40°F (4°C)	45 minutes	4 hours
50°F (10°C)	30 minutes	2 hours
70°F (21°C)	15 minutes	1 hour
90°F (32°C)	5 minutes	30 minutes

## Product Qualifications

- SSPC Paint 20, Type II, Level 1
- RCSC Class B slip coefficient for high strength bolted connections
- Zinc dust meets ASTM D520 type 2 standards

## DISCLAIMER

- For industrial or professional use only

## SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

## Danger

Rags, steel wool or waste soaked with this product may spontaneously catch fire if improperly discarded. Immediately after use, place rags, steel wool or waste in a sealed water-filled metal container. Refer to [www.pittsburghpaints.com](http://www.pittsburghpaints.com), Spontaneous Combustion Advisory for additional information



# AQUAPON® | 97-670 VOC SERIES

## WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

## REFERENCES

• CONVERSION TABLES	INFORMATION SHEET	1410
• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431

## WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

## LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at [www.ppgmc.com](http://www.ppgmc.com). The English text of this sheet shall prevail over any translation thereof.

## AVAILABILITY

### Packaging

1-gallon and 3.86-gallon kits (Do not mix components of different kit sizes)

Product codes	Description
97V-670A	Red base
97V-670B	Hardener
97-670Z	Zinc powder
97V-675A	Green base

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

