

PPG Flooring 920 MMA Primer

Formerly known as AC200 MMA Primer

DESCRIPTION

Non-pigmented, low-viscosity acrylic resin for use as a primer in MMA systems

PRINCIPAL CHARACTERISTICS

- Rapid cure
- Excellent adhesion to concrete
- Good wetting properties
- Allows for curing at lower temperatures
- Resistant to water and chemicals
- Meets USGBC LEED Requirements
- TYPICAL USES:
- Primer used as base coat for other MMA binder and sealer resins

COLOR AND GLOSS LEVEL

- Clear gold tone
- Satin

Note:

- Not to be pigmented

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	8.3 lb/US gal (1.0 kg/l)
Volume solids	99% ± 2%
VOC (Supplied)	EPA Method 24: 0.8 lb/US gal (93.3 g/l)
Recommended dry film thickness	13.0 - 20.0 mils (330 - 508 µm) per coat
Theoretical spreading rate	120 ft ² /US gal for 13.0 mils (2.9 m ² /l for 330 µm) 80 ft ² /US gal for 20.0 mils (2.0 m ² /l for 508 µm)
Dry to touch	30 minutes
Dry to overcoat	30 minutes
Full cure after	55 minutes
Shelf life	Base: at least 12 months

Notes:



PPG Flooring 920 MMA Primer

Formerly known as AC200 MMA Primer

- Basic product data is based on final mixed product of 5 US gallons (19 L) PPG Flooring 920 MMA resin and 20 fl. oz. (591 mL) of PPG Flooring 6492 MMA Catalyst at 70°F (21°C)
- Material should be stored in dry conditions, out of direct sunlight, in unopened original factory containers, at temperatures above 50°F (10°C) and below 75°F (24°C)
- See ADDITIONAL DATA – Curing time

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Concrete

- All surfaces must be sound, dry, clean, free of oil, grease, dirt, mildew, curing compounds, loose and flaking paint, and other foreign substances
- New concrete must cure a minimum of 28 days prior to application of this product
- Prepare surface as per SSPC-SP13 guidelines
- Abrade surface to achieve a surface profile equivalent to CSP 3 to CSP 5 in accordance with ICRI 310.2R-2013

Substrate temperature and application conditions

- Substrate temperature during application should be between 30°F (-1°C) and 90°F (32°C)
- The surface temperature must be at least 5°F (3°C) above dew point
- For slabs on grade, test for moisture in accordance with ASTM F1869 (calcium chloride test)
- Vapor transmission should be less than 3 lbs./1000 sq. ft. per 24 hr period
- Maximum relative humidity during application and curing is 80%

SYSTEM SPECIFICATION

- Resin product must be mixed with PPG Flooring™ 6492 MMA Catalyst at the volumes shown below prior to applying the mixed product to the prepared substrate.

Catalyst volumes by temperature

- Above 70°F (21.1°C) use 4 fl oz (118 ml) of the catalyst per gallon (3.8 L) of resin
- At 60°F (15.6°C) use 4-5 fl oz (118-148 ml) of the catalyst per gallon (3.8 L) of resin
- At 50°F (10.0°C) use 5-7 fl oz (148-207 ml) of the catalyst per gallon (3.8 L) of resin
- At 40°F (4.4°C) use 7-9 fl oz (207-266 ml) of the catalyst per gallon (3.8 L) of resin
- At temperatures below 40°F (4°C), PPG Flooring™ 6493 Cold Temperature Accelerator must be added to the resin before adding the catalyst. See below for more information on using 6493 CTA.
- At 30°F (-1.1°C) use 9-10 fl oz (266-296 ml) of the Catalyst per gallon (3.8 L) of resin

PPG Flooring 920 MMA Primer

Formerly known as AC200 MMA Primer

INSTRUCTIONS FOR USE

Preparation

- Mixing preparation is dependent on ambient, substrate, and material temperature.
- Pre-mix base component to homogenize the container. Add hardener and stir until completely dispersed. Blend at least 2-3 minutes with a slow speed (200-400 rpm) mixer
- Only mix subsets which can be processed within the pot life, due to rapid curing
- Apply immediately after mixing

Note:

- Under dosage may result in curing disturbances; over dosage may result in color alterations
-

Application

- Apply by notched trowel or squeegee and back roll
- Apply two coats on very porous substrates
- To help with application of subsequent coatings, it is recommended to lightly broadcast 20 mesh sand or color quartz at 1-2 lb/100 ft² (0.5-0.9 kg/9.3 m²) into the wet primer
- Do not perform broadcast to rejection of aggregate, lightly broadcast only
- Ensure good ventilation during application and curing
- No thinner should be added

Note:

- Do not use as binder resin for troweled and slurry coatings
-

Material temperature

- Material temperature during application should be between 30°F (-1°C) and 90°F (32°C)
-

Pot life

8 minutes at 70°F (21°C)

Note:

- See ADDITIONAL DATA – Pot life
-

Cleaning solvent

- Acetone or Ethyl Acetate
-

CLEANING PROCEDURE

- All application equipment must be cleaned immediately after use
 - Fully cured material can only be removed from equipment or surfaces through mechanical methods
-

PPG Flooring 920 MMA Primer

Formerly known as AC200 MMA Primer

ADDITIONAL DATA

Curing Time	
Substrate temperature	Dry to touch
30°F (-1°C)	30 minutes
40°F (4°C)	30 minutes
50°F (10°C)	30 minutes
60°F (16°C)	30 minutes
70°F (21°C)	30 minutes
80°F (27°C)	30 minutes

Pot life (at application viscosity)	
Mixed product temperature	Pot life
30°F (-1°C)	10 - 12 minutes
40°F (4°C)	8 minutes
50°F (10°C)	8 minutes
60°F (16°C)	8 minutes
70°F (21°C)	8 minutes
90°F (32°C)	6 minutes

DISCLAIMER

- For industrial or professional use only
- This product is specifically suitable for use on the substrates mentioned in this document. For application on any other substrates, please always contact your distributor or PMC representative for specific instructions and in order to make sure that the product performance can be safeguarded.

SAFETY PRECAUTIONS

- Read all label and Safety Data Sheet (SDS) information prior to use

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

- Information sheet | Explanation of product data sheets



PPG Flooring 920 MMA Primer

Formerly known as AC200 MMA Primer

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

