

Low Gloss Single Stage Polyurethane Enamel

ESSS

ESSS Low Gloss Single Stage Polyurethane Enamel is an easy-to-use product designed to offer variable gloss levels in a wide array of solid and metallic colors. It is available as a 2.8 VOC topcoat and can be used over all properly prepared OEM finishes, cured air-dried finishes, as well as any DELFLEET ESSENTIAL[®] primer.

Additional Products

- | | |
|------------------------------------|--------|
| • Essential Color | ESSS |
| • Hardener | ESU449 |
| • Slow Activator (68° -76°F) | ESX520 |
| • Very Slow Activator (76° - 88°F) | ESX530 |
| • Extra Slow Activator (> 88°F) | ESX540 |

Compatible Surfaces

ESSS may be applied over:

- Property cleaned and sanded OEM enamels and cured finishes
- ESU400 Wash Primer*
- ESU410 Polyurethane Primer
- ESU420/ESU421 3.5 VOC Epoxy Primers White/Gray
- ESU430 Epoxy Primer
- ESU440 3.5 VOC Primer Surfacer
- ESU460/ESU461/ESU462 4.6 VOC Epoxy Primers Gray/White/Black
- ESU470 2.1 VOC Epoxy Primer
- ESU480/481/482 2.1 VOC Epoxy Primers Gray/White/Black

When sanding prior to the application of ESSS topcoat, use 220 – 320 grit wet or dry.

*Wash and Etch primers must be sealed before applying topcoat for optimum performance.

Selection Of Substrate Cleaner - ONECHOICE[®] Commercial CFX Cleaners

Code	Product	Purpose
CFX435LV	Low VOC Cleaner	Compliant cleaner suitable for removing dirt, grease or other contaminants before or during the painting process.
CFX436	Wax & Grease Remover	Suitable for removing dirt, grease or other contaminants before or during the painting process.
CFX437	Heavy Duty Wax & Grease Remover	Used to remove heavy milling oils and grease from bare substrates prior to the painting process.



Application Guide

Preparation:



- Wash the area to be painted with soap and water, and then clean with CFX435LV, CFX436 or CFX437 cleaner.



- Sand with 180 – 240 grit on old finishes and body filler before priming, then re-clean with CFX436 or CFX437 cleaner.



- Prime all substrates immediately after cleaning.

Mixing Ratio:



- 6 : ESSS Low Gloss Topcoat
1 : ESU449 Hardener
1 : ESX520/530/540 activator

If additional thinning is needed, up to 10% of ESR300 or ESR310 may be added.

Pot Life:



Pot life of this product is variable depending on temperature and on activator choice.

2 hours @ 70°F (21°C)/50% RH

Spray Viscosity:



#2 EZ ZAHN: 20 – 30 seconds @ 77°F (25°C)

NOTE: High heat and humidity will shorten pot life of this material.

Additives:



N/A

Spray Gun Setup:

HVLP

COMPLIANT



Fluid Tip	1.3 - 1.7 mm or equivalent	1.3 - 1.7 mm or equivalent
Air Pressure	8-10 PSI at the air cap	50-60 PSI at the spray gun

Pressure Pot Setup: Starting setup, adjust from here for best results

HVLP

COMPLIANT



Fluid Tip	1.0 - 1.4 mm	1.0 - 1.4 mm
Fluid Delivery	8 -12 fluid ounces per minute	8 -12 fluid ounces per minute

Number of Coats:



2 coats with 10 minutes flash between coats

Film Build:	Wet Film (per coat)	Dry Film (total)
-------------	---------------------	------------------

Minimum	2.0 mils	2.0 mils
Maximum	4.0 mils	4.0 mils

Flash Time:



Between coats	5 – 10 minutes @ 70°F (21°C) before force drying
---------------	--

Dry Times:



To Touch:	30 - 60 minutes @ 70°F (21°C)
-----------	-------------------------------



To Handle:	60 - 90 minutes @ 70°F (21°C)
------------	-------------------------------

To Tape:	2 - 4 hours @ 70°F (21°C)
----------	---------------------------

Force Dry:	30 minutes @ 140°F (60°C)
------------	---------------------------



Activator used in ESSS	Min time before Recoat/Topcoat	Max time before Recoat/Topcoat
ESX520	30 minutes	16 hours
ESX530	3 hours	72 hours
ESX540	4 hours	96 hours

After 72 hours, sand ESSS color with 400 grit (wet or dry) before applying another coat of color.

Note: Force drying times are for quoted surface temperature. Additional time should be allowed in the force-drying schedule to allow surface to reach recommended temperature.

Theoretical Coverage:

619 - 701 sq. ft. (Color formula dependent)

Theoretical coverage in sq. ft. / US gal. Ready-to-spray (RTS), giving 1mil. (25µm) dry film thickness (Assuming 100% Transfer Efficiency)

Physical Characteristics:	6:1:1	6:1:1+10%
	ESSS : ESU449 : ESX5X0	ESSS : ESU449 : ESX5X0 : ESR3XX
Total Solids		
By Weight (RTS)	41.5% - 57.0%	37.6% - 52.7%
Total Solids		
By Volume (RTS)	38.6% - 43.7%	35.1% - 39.7%

Application Guide (continued)

RTS Combinations:	ESSS color	ESSS : ESU449 : ESX5X0	ESSS : ESU449 : ESX5X0 : ESR3XX
Volume Ratio	Package (as is)	6 : 1 : 1	6 : 1 : 1 + 10%
Applicable Use Category	Single-Stage Coating	Single-Stage Coating	Single-Stage Coating
VOC Actual	153-183 (g/L)	146-169 (g/L)	133-153 (g/L)
VOC Actual	1.28-1.53 (lbs/gal)	1.22-1.41 (lbs/gal)	1.11-1.28 (lbs/gal)
VOC Regulatory			
(less water less exempt)	261-262 (g/L)	265-266 (g/L)	265-266 (g/L)
VOC Regulatory			
(less water less exempt)	2.18-2.19 (lbs/gal)	2.21-2.22 (lbs/gal)	2.21-2.22 (lbs/gal)
Density	1233-1684 (g/L)	1243-1583 (g/L)	1248-1559 (g/L)
Density	9.56-13.06 (lbs/gal)	9.64-12.27 (lbs/gal)	9.68-12.07 (lbs/gal)
Volatiles wt.	36.4-54.8%	43.0-58.5%	47.3-62.4%
Water wt.	0.0-0.1%	0.0-0.1%	0.0-0.1%
Exempt wt.	24.7-41.3%	31.5-45.7%	36.7-50.9%
Water vol.	0.0%	0.0-0.1%	0.0-0.1%
Exempt vol.	30.2-41.1%	36.5-44.7%	42.2-49.7%

Health and Safety:

Safety Data Sheets (SDS) for the PPG products mentioned in this publication are available through www.ppgcommercialcoatings.com (Safety, SDS Search) or your PPG Distributor.

For additional information regarding this product, see the SDS and LABEL information.

EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION (412) 434-4515; IN CANADA (514) 645-1320 AND IN MEXICO 01-800-00-21-400.

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public. Products mentioned may be hazardous and should only be used according to directions, while observing precautions and warning statements listed on label. Statements and methods described are based upon the best information and practices known to PPG Industries. Procedures for applications mentioned are suggestions only and not to be construed as representations or warranties as to performance, results or fitness for any intended use, nor does PPG Industries warrant freedom from patent infringement in the use of any formula or process set forth herein.



PPG Industries
Commercial Coatings
19699 Progress Drive
Strongsville, OH 44149
1-800-647-6050

PPG Canada Inc.
2301 Royal Windsor Drive, Unit #6
Mississauga, Ontario L5J 1K5
1-888-310-4762