



# MP17x Series Epoxy Primers

## Background

OMNI<sup>®</sup> MP17x Series Epoxy Primers are two-component, non-chrome epoxies designed to provide superior corrosion protection and adhesion when applied over properly cleaned and sanded bare metal, fiberglass and painted surfaces. They are available in gray, white or black

#### Components

Primer	
MP170 Epoxy Primer - Gray	
MP171 Epoxy Primer - White	
MP172 Epoxy Primer - Black	

Catalyst MP175 Epoxy Primer Catalyst Reducer Acetone (optional)

## **Compatible Products**

#### Can be applied over:

Properly cleaned, sanded, bare or primed steel, galvanized and aluminum. Sanded and cleaned body filler, SMC and gel-coated fiberglass Properly cleaned and sanded E-coat Cleaned, cured and sanded OEM and refinish coatings. MP246 Polyester Primer MP281 1K Light Gray Primer Surfacer MP282 High Build 2K Primer Surfacer OneChoice® Plastic Adhesion Promoter

\*Note: MP17x Series Epoxy Primers should not be applied over any Etch Primer

#### Can be topcoated with:

MP246 Polyester Primer MP281 1K Light Gray Primer Surfacer MP282 High Build 2K Primer Surfacer MP213 GP Sealer MP23x 2K Urethane Sealers MBP *Omni* Plus Acrylic Urethane Basecoat MBC Acrylic Basecoat MTK Acrylic Urethane Single Stage MAE Acrylic Enamel MAE Acrylic Enamel with Hardener

## Preparation

Surface Cleaning: MX190 Cleaner MX192 Plastic Cleaner SXA330 Wax and Grease Remover SWX350 (H<sub>2</sub>O-SO-CLEAN<sup>®</sup>) Waterborne Pre-Cleaner

## Sanding

120 - 180 grit on bare metal

220 - 320 grit on old finishes, body filler.

#### Mixing

Ratios:	MP17x Series :	MP175	:	Acetone*	
	<b>2</b> : *Optional	1	:	up to ½ part	
Note:	Allow a 15 minute induction period before applying				
Pot Life:	8 hours at 70°F (21°C)				
Additives:	None				

#### Air Pressure and Gun Setup



8 - 10 psi at the air cap Compliant: 29 - 40 psi at the gun

Gun Setup:

Coats:

HVLP:

1.3 - 1.6 mm or equivalent

Note: For best overall results, refer to spraygun manufacturer's recommendations for inlet air pressures.

## Application



1 or 2 coats

## **Dry Times**

<u>}</u>	Between Coats:	1 coat 2 coats	15 minutes at 70°F (21°C) 30 minutes at 70°F (21°C)	
	Dry Times:	1 coat 2 coats	15 minutes at 70°F (21°C) 30 minutes at 70°F (21°C)	
		MP17x Series Epoxy Primers <u>must</u> be scuffed and reapplied if allowed to sit mo than 3 days (72 hours)		

## **Clean Up**

Clean spray guns, gun cups, storage pots, etc., thoroughly with MR Reducer, MS251 Multi Purpose Solvent or other appropriate clean up solvent after each use.

Follow EPA guidelines for proper storage and disposal of solvent-borne waste paint.

#### **Properties**

VOC	
Applied (2:1)	MP170 4.53 lbs./ gal (551 g/L)
	MP171 4.54 lbs./ gal (539 g/L)
	MP172 4.54 lbs./ gal (539 g/L)
Solids by weight	56.4%
Applied (2:1) + up to 0.5 part acetone	4.53 - 4.54 lbs./ gal (543 - 544 g/L)
Film build per coat	
Applied (2:1)	0.9 - 1.1 mils
Square foot coverage at 1.0 mils	
Applied (2:1)	577 sq. ft. per US gallon at 100% transfer
Limitations	

Omni products should not be combined with components of other product lines.

Precautionary Information:

The contents of this package may have to be blended with other components before the product can be use. Before opening the packages be sure you understand the warning messages on the labels of all components since the mixture will have the hazards of all of its parts. Spray equipment must be handled with due care and in accordance with manufacturer's recommendations. Follow label directions for respirator use. Wear eye and skin protection. Observe all applicable precautions.

#### Medical Response: EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION (412) 434-4515; IN CANADA (514)-645-1320

#### See Safety Data Sheet and Labels for additional safety information and handling instructions.

Data Safety Sheets for the PPG products mentioned in this publication are available through your PPG *Omni* brand distributor. To the best of our knowledge, the technical information in this bulletin is accurate; however, since PPG Industries is constantly improving its coating and paint formulas, the current technical data may vary somewhat from what was available when this bulletin was printed. Contact your *Omni* brand distributor or visit www.ppgrefinish.com for the most up-to-date information.



© 2025 PPG Industries, Inc. All rights reserved The PPG Logo, H2O-So-Clean, OneChoice and Omni are registered trademarks and We protect and beatify the world is a trademark of PPG Industries Ohio, Inc